UNIVERSITY OF LEEDS

This is a repository copy of *Amine-responsive bilayer films with improved illumination stability and electrochemical writing property for visual monitoring of meat spoilage*.

White Rose Research Online URL for this paper:
<http://eprints.whiterose.ac.uk/151925/>

Version: Supplemental Material

Article:

Zhai, X, Zou, X, Shi, J et al. (10 more authors) (2020) Amine-responsive bilayer films with improved illumination stability and electrochemical writing property for visual monitoring of meat spoilage. *Sensors and Actuators, B: Chemical*, 302. 127130. ISSN 0925-4005

<https://doi.org/10.1016/j.snb.2019.127130>

© 2019, Elsevier B.V. This manuscript version is made available under the CC-BY-NC-ND 4.0 license <http://creativecommons.org/licenses/by-nc-nd/4.0/>.

Reuse

This article is distributed under the terms of the Creative Commons Attribution-NonCommercial-NoDerivs (CC BY-NC-ND) licence. This licence only allows you to download this work and share it with others as long as you credit the authors, but you can't change the article in any way or use it commercially. More information and the full terms of the licence here: <https://creativecommons.org/licenses/>

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.

eprints@whiterose.ac.uk
<https://eprints.whiterose.ac.uk/>

Supporting Information

Amine-responsive bilayer films with improved illumination stability and electrochemical writing ability for visual monitoring of meat spoilage

Xiaodong Zhai ^a, Xiaobo Zou ^{a,*}, Jiyong Shi ^{a,*}, Xiaowei Huang ^a, Zhihua Li ^a, Yue Sun ^a, Yanxiao Li ^a,
Xin Wang ^a, Melvin Holmes ^b, Yunyun Gong ^b, Megan Povey ^b, Jianbo Xiao ^c

^a Agricultural Product Processing and Storage Lab, School of Food and Biological Engineering, Jiangsu University, Zhenjiang, Jiangsu 212013, China

^b School of Food Science and Nutrition, University of Leeds, Leeds LS2 9JT, United Kingdom

^c Institute of Chinese Medical Sciences, State Key Laboratory of Quality Research in Chinese Medicine, University of Macau, Taipa, Macau, China

*Corresponding author. Tel.: +86 511 88780174; Fax: +86 511 88780201; Email: zou_xiaobo@ujs.edu.cn
(Xiaobo Zou), Shi_jiyong@ujs.edu.cn (Jiyong Shi).

Fig. S1. Transparencies of the films in the UV-Vis spectrum range. The transparency of the colorimetric films decreased with the increase of TiO₂ content in the visible ranges (~ 400-800 nm), indicating the barrier ability of TiO₂ nanoparticles towards visible light through physical reflection.

Fig. S2. The images of the AG-AN/GG-2%TiO₂ film after being exposed to ammonia, dimethylamine, trimethylamine and aniline. The test condition was 25 °C and 75% relative humidity.

Fig. S3. The images of the AG-AN/GG-2%TiO₂ film (Control), and after being exposed to 0.255 mM trimethylamine under different relative humidity (RH). The test temperature was 25 °C.

Fig. S4. The packaging box with colorimetric films for meat spoilage indicating. Film 1: the AG-AN/GG-2%TiO₂ film with an electrochemical writing pattern (yellow color); Film 2: the AG-AN/GG-2%TiO₂ film without electrochemical writing pattern.

Table S1. Cost of materials needed to fabricate the AG-AN/GG-2%TiO₂ film (diameter 53 mm)

Chemicals	Concentration	Volume	Price*	Price per 1000 units
Agar	20 g/L	6 mL	\$ 0.068/g	\$ 8.16
Gellan gum	20 g/L	6 mL	\$ 0.033/g	\$ 3.96
TiO ₂	0.4 g/L	6 mL	\$ 0.097/g	\$ 0.24
CaCl ₂ ·2H ₂ O	0.4 g/L	6 mL	\$ 0.008/g	\$ 0.02
Anthocyanins	80 mg/L	6 mL	\$ 9.942/g**	\$ 4.77
Total	-	-	-	\$ 17.15

*Prices of standard chemicals in the list are from Sinopharm Chemical Reagent Co., Ltd (Shanghai, China)

** Price of anthocyanins was calculated according to the mass of anthocyanins extracted from dried rose.