



This is a repository copy of *Bespoke Cationic Nano-objects via RAFT Aqueous Dispersion Polymerisation*.

White Rose Research Online URL for this paper:
<http://eprints.whiterose.ac.uk/101500/>

Version: Accepted Version

Article:

Williams, M., Penfold, N.J.W., Lovett, J.R. et al. (6 more authors) (2016) Bespoke Cationic Nano-objects via RAFT Aqueous Dispersion Polymerisation. *Polymer Chemistry*, 7 (23). pp. 3864-3873. ISSN 1759-9954

<https://doi.org/10.1039/C6PY00696E>

Reuse

Unless indicated otherwise, fulltext items are protected by copyright with all rights reserved. The copyright exception in section 29 of the Copyright, Designs and Patents Act 1988 allows the making of a single copy solely for the purpose of non-commercial research or private study within the limits of fair dealing. The publisher or other rights-holder may allow further reproduction and re-use of this version - refer to the White Rose Research Online record for this item. Where records identify the publisher as the copyright holder, users can verify any specific terms of use on the publisher's website.

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.



eprints@whiterose.ac.uk
<https://eprints.whiterose.ac.uk/>

Bespoke Cationic Nano-objects via RAFT Aqueous Dispersion Polymerisation

M. Williams^a, N. J. W. Penfold^a, J. R. Lovett^a, N. J. Warren^a, C. W. I. Douglas^b, N. Doroshenko^b, P. Verstraete^c, J. Smets^c and S. P. Armes^a

Received 00th January 20xx,
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

www.rsc.org/

A range of cationic diblock copolymer nanoparticles are synthesised via polymerisation-induced self-assembly (PISA) using a RAFT aqueous dispersion polymerisation formulation. The cationic character of these nanoparticles can be systematically varied by utilising a binary mixture of two macro-CTAs, namely non-ionic poly(glycerol monomethacrylate) (PGMA) and cationic poly[2-(methacryloyloxy)ethyl] trimethylammonium chloride (PQDMA), with poly(2-hydroxypropyl methacrylate) (PHPMA) being selected as the hydrophobic core-forming block. Thus a series of cationic diblock copolymer particles with the general formula $[(1-n) \text{PGMA}_x + [n] \text{PQDMA}_y] - \text{PHPMA}_z$ were prepared at 20 % w/w solids, where n is the mol fraction of the cationic block and x , y and z are the mean degrees of polymerisation of the non-ionic, cationic and hydrophobic blocks, respectively. These cationic diblock copolymer nanoparticles were analysed in terms of their chemical composition, particle size and morphology and cationic character using ^1H NMR spectroscopy, dynamic light scattering (DLS), transmission electron microscopy (TEM), and aqueous electrophoresis, respectively. Systematic variation of the above PISA formulation enabled the formation of spheres, worms and vesicles that remain cationic over a wide pH range. However, increasing the cationic character favors the formation of kinetically-trapped spheres, since it leads to more effective steric stabilisation which prevents sphere-sphere fusion. Furthermore, the cationic worm phase forms a soft free-standing gel at 25 °C that undergoes reversible degelation on cooling, as indicated by variable temperature oscillatory rheology studies. Finally, the antimicrobial activity of this thermo-responsive cationic worm gel towards the well-known pathogen *Staphylococcus aureus* is examined via direct contact assays.

Introduction

It has been widely reported that the self-assembly of block copolymers can produce spherical micelles,¹ worm-like micelles,^{2,3} rod-like micelles,^{4,5,6} vesicles,^{1,7,8,9,10} nanotubes^{11,12} and toroids.¹³ Traditionally, block copolymer self-assembly involves a post-polymerisation processing step that is typically conducted in dilute solution.^{1,14,15,16} However, recent advances in polymerisation-induced self-assembly (PISA) via reversible addition-fragmentation chain transfer (RAFT) polymerisation^{17,18,19} has enabled diblock copolymers to be prepared in the form of sterically-stabilised nanoparticles at relatively high solids (25-50%), ensuring much lower solution viscosities compared to conventional solution polymerisations. The broad applicability of this PISA approach is now widely

recognised, with successful formulations being reported in aqueous solution (via either dispersion^{20,21,22,23} or emulsion^{24,25,26,27,28} polymerisation), as well as polar solvents such as lower alcohols^{29,30,31} and non-polar solvents like *n*-alkanes.³² Furthermore, controlled/living radical polymerisation techniques enable efficient polymerisations (~99% conversion within 2 h) and relatively narrow molecular weight distributions ($M_w/M_n < 1.30$).³³ In a typical aqueous PISA formulation, the water-soluble steric stabiliser block is prepared first, with the subsequent growth of the water-insoluble block driving *in situ* phase separation. The final particle morphology in such aqueous PISA-based systems is dictated by (i) the copolymer concentration, (ii) the targeted AB diblock copolymer composition and (iii) the mean degree of polymerisation of the stabiliser block.^{34,35} RAFT polymerisation of 2-hydroxypropyl methacrylate (HPMA) using a poly(glycerol monomethacrylate)-based macromolecular chain transfer agent (PGMA macro-CTA) using a RAFT aqueous dispersion polymerisation protocol has been intensively investigated by our group.^{22,23,35,36,37,38} This prototypical aqueous PISA formulation allows the efficient formation of AB block copolymer nanoparticles with precise control over particle size and morphology by fixing the degree of polymerisation of the PGMA stabiliser block and systematically varying the degree of polymerisation of the core-forming

^a Department of Chemistry, University of Sheffield, Brook Hill, Sheffield, South Yorkshire, S3 7HF

^b School of Clinical Dentistry, University of Sheffield, Claremont Crescent, Sheffield S10 2TA

^c Procter & Gamble, Temselaan 100, 1853 Strombeek Bever, Belgium

Electronic Supplementary Information (ESI) available: Aqueous gel permeation chromatograms of PQDMA macro-CTAs, TEM images of PQDMA-PHPMA spheres, DMF gel permeation chromatograms of PGMA-PHPMA di-block copolymers, TEM images of cationic worms, critical gelation concentration determination of cationic worms and rheology studies of cationic and non-ionic worms. See DOI: 10.1039/x0xx00000x




Figure 1. Synthesis of cationic diblock copolymer nanoparticles with the general formula $[(1-n) \text{PGMA}_x + [n] \text{PQDMA}_y] - \text{PHPMA}_z$ by RAFT aqueous dispersion polymerisation of HPMA using a binary mixture of non-ionic and cationic macro-CTAs. Optimisation of n , x , y , and z enable the formation of cationic spheres, worms or vesicles.

PHPMA block. The construction of detailed phase diagrams has enabled pure spheres, worms, or vesicles to be reproducibly targeted.²³ Furthermore, PGMA-PHPMA worms form free-standing soft hydrogels at 25 °C due to multiple inter-worm contacts, with reversible degelation occurring on cooling to 4 °C as a result of a worm-to-sphere order-order transition.^{35, 36, 38} Such thermo-responsive worm gels are readily sterilisable via cold ultrafiltration and have potential biomedical applications for the long-term storage and preservation of human stem cells³⁹ or red blood cells.⁴⁰

In principle, the nanoparticle surface chemistry can be fine-tuned by varying the stabiliser block used in such PISA formulations. One approach is to use a polyelectrolyte as a stabiliser block to produce highly charged nanoparticles. However, this approach typically leads to just spherical morphologies being obtained, because the strong electrostatic repulsion between the adjacent cationic or anionic chains within the steric stabiliser layer prevents the efficient sphere-sphere fusion required to form higher order morphologies such as worms or vesicles.^{24, 27, 41, 42}

It has been widely reported that colloiddally stable cationic nanoparticles can possess anti-microbial properties.^{43, 44, 45, 46} Previously, we have utilised a cationic polyelectrolytic block based on quaternised poly(2-(dimethylamino)ethyl methacrylate) (PQDMA) to polymerise HPMA in order to form sterically-stabilised nanoparticles via PISA.⁴² In the absence of salt, block copolymer self-assembly was somewhat problematic due to the strong repulsion between the neighbouring cationic PQDMA stabiliser chains. However, in the presence of salt the unfavourable electrostatics could be overcome by reducing the charge density within the coronal stabiliser layer by either (i) statistically copolymerising QDMA monomer with a non-ionic GMA comonomer or (ii) using a binary mixture of a PQDMA macro-CTA and a PGMA macro-CTA. In practice, the latter approach proved to be particularly useful in allowing access to worm and vesicle copolymer morphologies.⁴²

In the present work, this binary macro-CTA approach is revisited. In particular, the effect of varying the relative

degrees of polymerisation of the PQDMA and PGMA stabiliser blocks on the nanoparticle surface charge is investigated (see Figure 1). A detailed phase diagram is constructed to examine how the degree of polymerisation of the core-forming PHPMA block and the proportion of cationic stabiliser block affects the formation of cationic spheres, worms and vesicles. Finally, a preliminary investigation of the anti-microbial properties of a cationic thermo-responsive worm gel against a strain of the well-known pathogen *Staphylococcus aureus* is reported.

Experimental Section

Materials

Glycerol monomethacrylate (GMA) was donated by GEO Specialty Chemicals (Hythe, UK) and used without further purification. 4-Cyano-4-(2-phenylethanesulfanylthiocarbonyl) sulfanylpentanoic acid (PETTC) RAFT agent and its methylated analogue were synthesised as previously reported.^{31,47} [2-(methacryloyloxy)ethyl]trimethylammonium chloride solution (QDMA; 80 % w/w in H₂O), 2-hydroxypropyl methacrylate (HPMA; 97%), 4,4'-azobis(4-cyanopentanoic acid) (ACVA; 99%), ethanol, methanol, dichloromethane and deuterium oxide (D₂O) were purchased from Sigma-Aldrich (UK) and were used as received. Acetonitrile and dimethyl formamide were purchased from Fisher scientific (Loughborough, UK). Methanol-*d*₄ (CD₃OD) was purchased from Goss Scientific Ltd. (Cheshire, UK). Deionised water was used for all experiments.

Synthesis of poly(glycerol monomethacrylate) (PGMA) macro-CTA via RAFT solution polymerisation

A typical protocol for the synthesis of PGMA₆₂ was as follows. 4-Cyano-4-(2-phenylethanesulfanylthiocarbonyl)sulfanylpentanoic acid (PETTC) RAFT agent (2.40 mmol, 0.815 g, ACVA initiator (0.50 mmol, 0.135 g, CTA/ACVA molar ratio = 5.0) and GMA monomer (0.156 mol, 25.0 g) were weighed into a 100 mL round-bottom flask. Ethanol (25.9 mL) was added to afford a 50 % w/w GMA solution and the resulting solution was purged with nitrogen for 30 min. The sealed flask was immersed into an oil bath set at 70 °C for 105 min (final GMA conversion = 84 %, as judged by ¹H NMR spectroscopy)

and the polymerisation was subsequently quenched by immersion in liquid nitrogen. Methanol (50 mL) was added to the reaction solution, followed by precipitation into a ten-fold excess of dichloromethane (1 L). The precipitated PGMA macro-CTA was redissolved in methanol and the precipitation was repeated. After dissolution using deionised water, the resulting aqueous polymer solution was freeze-dried overnight. ^1H NMR analysis indicated a mean degree of polymerisation of 62 for this PGMA macro-CTA. Its M_n and M_w/M_n were $16\,500\text{ g mol}^{-1}$ and 1.12, respectively, as judged by DMF GPC using a refractive index detector and a series of near-monodisperse poly(methyl methacrylate) calibration standards.

Synthesis of poly[2-(methacryloyloxy)ethyl]trimethylammonium chloride (PQDMA) macro-CTA via RAFT solution polymerisation

A typical protocol for the synthesis of PQDMA₉₅ was as follows. 4-Cyano-4-(2-phenylethanesulfanylthiocarbonyl)sulfanylpentanoic acid (PETTC) RAFT agent (0.58 mmol, 0.196 g, ACVA initiator (0.12 mmol, 0.032 g, CTA/ACVA molar ratio = 5.0) and QDMA monomer (0.058 mol, 15.0 g, 80 % w/w in water) were weighed into a 100 mL round-bottom flask. Ethanol (25.6 mL) was added to afford a 30 % w/w QDMA solution in a 9:1 ethanol/water solution and the resulting solution was purged with nitrogen for 30 min. The sealed flask was immersed into an oil bath set at 70 °C for 180 min (final QDMA conversion = 79 %, as judged by ^1H NMR spectroscopy) and the polymerisation was subsequently quenched by immersion in liquid nitrogen. Purification was achieved by precipitation into a ten-fold excess of acetonitrile (0.5 L). The isolated PQDMA macro-CTA was redissolved in deionised water and this precipitation purification protocol was repeated. Following dissolution with deionised water, the aqueous polymer solution was freeze-dried overnight. ^1H NMR analysis indicated a mean degree of polymerisation of 95 for this PQDMA macro-CTA. Aqueous GPC analysis, using a pH 2 aqueous eluent, a refractive index detector, and a series of near-monodisperse poly(ethylene oxide) calibration standards, indicated an M_n and M_w/M_n of $25\,300\text{ g mol}^{-1}$ and 1.19, respectively. The same protocol was used to synthesise a PQDMA₂₆ macro-CTA with an M_n and M_w/M_n of $9\,500\text{ g mol}^{-1}$ and 1.23, as well as a PQDMA₄₈ macro-CTA with an M_n of $15\,500\text{ g mol}^{-1}$ and an M_w/M_n of 1.23.

Synthesis of PGMA-PPHMA diblock copolymer nanoparticles by RAFT aqueous dispersion polymerisation

The typical protocol for the synthesis of PGMA₆₂-PPHMA₂₀₀ nanoparticles at 20 % w/w solids was as follows. PGMA₆₂ macro-CTA (0.300 g, 0.030 mmol), ACVA (3.0 mg, 0.01 mmol, CTA/ACVA molar ratio = 3.0) and HPMa monomer (0.836 g, 6.00 mmol; target DP = 200) were weighed into a 25 mL round-bottomed flask. Deionised water (4.6 mL) was then added to give a 20.0% w/w aqueous solution, which was degassed for 30 min prior to immersion in an oil bath set at 70 °C. The reaction solution was stirred for 5 h to ensure complete HPMa monomer conversion (as judged by ^1H NMR) and then quenched by cooling and exposure to air.

Synthesis of PQMA-PPHMA diblock copolymer nanoparticles by RAFT aqueous dispersion polymerisation

The typical protocol for the synthesis of PQDMA₂₆-PPHMA₂₀₀ at 10 % w/w solids was as follows. PQMA₂₆ macro-CTA (0.080 g, 0.014 mmol), ACVA (1.30 mg, 0.005 mmol, CTA/ACVA molar ratio = 3.0) and HPMa monomer (0.394 g, 2.8 mmol; target DP = 200) were weighed into a 25 mL round-bottomed flask. Deionised water (4.3 mL) was then added to give a 10.0% w/w aqueous solution, which was degassed for 30 min prior to immersion in an oil bath set at 70 °C. The reaction solution was stirred for 5 h to ensure complete HPMa monomer conversion (as judged by ^1H NMR) and then quenched by cooling and exposure to air.

Synthesis of [(1-n) PGMA_x + [n] PQDMA_y] – PPHMA_z diblock copolymer nanoparticles by RAFT aqueous dispersion polymerisation using a binary mixture of macro-CTAs

The typical protocol for the synthesis of (0.9 PGMA₆₂ + 0.1 PQDMA₉₅) – PPHMA₂₀₀ at 20 % w/w solids was as follows. PGMA₆₂ macro-CTA (0.241 g, 0.023 mmol), PQDMA₉₅ macro-CTA (0.052 g, 0.003 mmol), ACVA (2.40 mg, 0.009 mmol, CTA/ACVA molar ratio = 3.0) and HPMa monomer (0.746 g, 5.20 mmol; target DP = 200) were weighed into a 25 mL round-bottomed flask. Deionised water (4.2 mL, producing a 20.0% w/w aqueous solution) was then added and the solution was degassed for 30 min prior to immersion in an oil bath set at 70 °C. The reaction solution was stirred for 5 h to ensure complete HPMa monomer conversion (as judged by ^1H NMR), with quenching achieved by cooling and exposure to air.

Evaluation of the antimicrobial activity of a cationic worm gel

Diblock copolymer nanoparticles with the general formula (0.95 PGMA₆₂ + 0.05 PQDMA₉₅) – PPHMA₂₀₀ were synthesised at 20 % w/w solids using the above protocol. The resulting cationic worm gel was diluted to 12.5 % w/w solids by cooling to 2 °C, followed by addition of the desired volume of deionised water and warming to room temperature. As a control, a non-ionic worm gel was also prepared using methylated PETTC as a RAFT CTA, which was synthesised using a previously reported protocol.⁴⁷ The effect of each copolymer gel on a clinical isolate of *Staphylococcus aureus* S235 was assessed using two methods: a qualitative direct contact method referred to as the 'drop on' technique, and a quantitative 'viable count' method.

'Drop on' technique.

S. aureus cells were spread evenly over cold blood agar plates (Columbia base + 5% (v/v) horse blood; Oxoid Ltd, UK). The cationic worm gel and the non-ionic worm gel (control) were each cooled on ice until liquefied and 20 μL droplets were applied directly to the cold *S. aureus* lawns using chilled micropipet tips. Plates were then incubated overnight at 37 °C to allow bacterial growth to occur.

'Viable count' assay.

To *S. aureus* in a cold Eppendorf tube was added 100 μL of ice-cold cationic or non-ionic worm gel (or phosphate-buffered saline), then each tube were allowed to warm up to room temperature in order to induce copolymer gelation. After an appropriate incubation period at room temperature, tubes were returned to an ice bath to induce degelation. Ice-cold aqueous PBS solution (1.0 mL) was then added to each tube, vortex-mixed and immediately serially-diluted ten-fold using cold PBS. 10 μL aliquots of each dilution were spotted

in duplicate onto blood agar plates and incubated at room temperature overnight to allow growth of surviving bacteria and the resulting colonies were counted. All experiments were conducted in duplicate.

Polymer Characterisation

¹H NMR spectroscopy

All NMR spectra were recorded using a 400 MHz Bruker Avance-400 spectrometer at 298 K with 64 scans being averaged per spectrum.

DMF gel permeation chromatography (GPC)

The PGMA macro-CTA and PGMA-PPHMA diblock copolymer molecular weights and polydispersities were determined using a DMF GPC set-up operating at 60 °C comprising two Polymer Laboratories PL gel 5 µm Mixed-C columns connected in series to a Varian 390-LC multi-detector suite (refractive index detector only) and a Varian 290-LC pump injection module. The GPC eluent was HPLC-grade DMF containing 10 mM LiBr at a flow rate of 1.0 mL min⁻¹. DMSO was used as a flow-rate marker. Calibration was conducted using a series of ten near-monodisperse poly(methyl methacrylate) standards ($M_n = 625$ to $618\,000$ g mol⁻¹). Chromatograms were analysed using Varian Cirrus GPC software (version 3.3).

Aqueous GPC

Aqueous GPC was used to characterise the series of PQDMA macro-CTAs. The GPC protocol involved using an Agilent 1260 Infinity series degasser and pump, 8 µm Agilent PL Aquagel-OH 30 and 8 µm Agilent PL Aquagel-OH 40 columns, and both a UV and an RI detector. The eluent was an acidic aqueous buffer (pH 2) containing 0.50 M acetic acid, 0.30 M NaH₂PO₄ and acidified with HCl at a flow rate of 1.0 mL min⁻¹. Calibration was achieved using a series of near-monodisperse poly(ethylene oxide) standards with M_n values ranging from 1 080 to 905 000 g mol⁻¹.

Dynamic Light Scattering (DLS)

The intensity-average hydrodynamic diameter of diblock copolymer nanoparticles was determined by DLS using a Malvern Zetasizer NanoZS instrument via the Stokes-Einstein equation, which assumes perfectly monodisperse, non-interacting spheres. Aqueous 0.01 w/v % copolymer dispersions were analysed using disposable plastic cuvettes, and data were averaged over three consecutive runs. Deionised water was used to dilute each dispersion and ultra-filtered through a 0.20 µm membrane to remove dust prior to use.

Aqueous Electrophoresis

Zeta potentials for diblock copolymer nanoparticles were analysed using a Malvern Zetasizer Nano ZS instrument. All measurements were conducted in the presence of 1 mM KCl, with either dilute NaOH or HCl being used for pH adjustment as required.

Transmission electron microscopy (TEM)

Copper/palladium TEM grids (Agar Scientific, UK) were surface-coated to yield a thin film of amorphous carbon. The grids were then plasma glow-discharged for 30 seconds to create a hydrophilic surface. A small volume (10 µL) of a dilute aqueous copolymer

dispersion was placed on a freshly-prepared grid for 20 seconds and then carefully blotted with filter paper to remove excess solution. To stain the aggregates, a 0.75% w/v uranyl formate solution (10 µL) was placed on the sample-loaded grid for 15 seconds and then carefully blotted to remove excess stain. The grids were then dried using a vacuum hose. Imaging was performed using a FEI Tecnai Spirit microscope fitted with a Gatan 1KMS600CW CCD camera operating at 80 KV.

Rheology measurements

An AR-G2 rheometer equipped with a variable temperature Peltier plate and a 40 ml 2° aluminium cone was used for all experiments. The loss modulus (G'') and storage modulus (G') were measured as a function of percentage strain, angular frequency and temperature to assess the critical gelation temperature (CGT) and gel moduli (G' and G''). Percentage strain sweeps were conducted at 25 °C using a fixed angular frequency of 1.0 rad s⁻¹. Angular frequency sweeps were conducted at 25 °C using a constant percentage strain of 1.0%. Temperature sweeps were conducted using a constant percentage strain of 1.0% and a constant angular frequency of 1.0 rad s⁻¹. In these latter experiments, the temperature was lowered from 25 to 2 °C at 1.0 °C intervals, allowing 1 min for thermal equilibrium in each case. After 5 min at 2 °C, the dispersion was heated up to 25 °C in 1.0 °C intervals.

Results and Discussion

In this study, we revisit our earlier PISA formulation reported by Semsarilar and co-workers⁴² in order to prepare sterically-stabilised cationic diblock copolymer nanoparticles via RAFT aqueous dispersion polymerisation using a binary mixture of macro-CTAs. More specifically, a binary mixture of PQDMA (cationic) and PGMA (non-ionic) macro-CTAs are chain-extended simultaneously using HPMA to produce either spheres, worms or vesicles (see Figure 1). Initially, three PQDMA macro-CTAs with differing mean degrees of polymerisation were synthesised by RAFT solution polymerisation using a 9:1 ethanol/water mixture. PETTC was used as the RAFT agent and 4,4'-azobis(4-cyanopentanoic acid) (ACVA) was utilised as the free radical initiator at a CTA/initiator molar ratio = 5.0. Following QDMA polymerisation at 30 % w/w solids and 70 °C for 3 h, any unreacted monomer was removed via precipitation into excess acetonitrile. ¹H NMR studies confirmed that the three PQDMA macro-CTAs had mean degrees of polymerisation (DP) of 26, 48 and 95 respectively, while aqueous GPC analysis (vs PEO calibration standards) indicated that each macro-CTA had an M_w/M_n of less than 1.25 (see Figure S1).

It is well-known that using a polyelectrolyte as the sole stabiliser block during the PISA synthesis of AB diblock copolymer nanoparticles in aqueous solution invariably results in only spherical morphologies being obtained as a result of the strong electrostatic repulsion between the charged stabiliser chains.^{24, 27, 41, 42} To examine this phenomenon, a range of PQDMA₂₆-PPHMA_z diblock copolymer nanoparticles were prepared at 10 % w/w solids using RAFT aqueous dispersion polymerisation, where z was varied from 100 to 500. DLS and TEM studies confirmed that indeed only spherical nanoparticles with mean diameters ranging from 100 to 300 nm could be produced (see Figure S2). Previously, it has been




Figure 2. Zeta potential vs pH curves and corresponding transmission electron microscopy images recorded for diblock copolymer nanoparticles with the general formula $(0.9 \text{ PGMA}_{62} + 0.1 \text{ PQDMA}_y) - \text{PHPMA}_{200}$ where $y = 0, 26, 48$ or 95 . The scale bar applies to all images.

shown that increasing the copolymer concentration in RAFT aqueous dispersion formulations using either *non-ionic* or *zwitterionic* steric stabiliser blocks can lead to the formation of so-called ‘higher order’ morphologies such as worms or vesicles.^{23, 34} However, attempts to synthesise PQDMA_{26} - PHPMA_z diblock copolymers at 20 % w/w solids only resulted in the formation of highly viscous solutions that appeared to be rather polydisperse after dilution for DLS studies.

To evaluate using a binary mixture of macro-CTAs as reported by Semsarilar and co-workers, a non-ionic PGMA macro-CTA was synthesised according to a previously reported protocol.⁴⁷ More specifically, a PGMA_{62} macro-CTA ($M_n = 16\,500$; $M_w/M_n = 1.12$) was prepared by RAFT solution polymerisation of GMA in ethanol using a PETTC RAFT agent and ACVA initiator at a PETTC/ACVA molar ratio of 5.0.

Using various combinations of the PQDMA and PGMA macro-CTAs, several series of $([1-n] \text{ PGMA}_x + [n] \text{ PQDMA}_y) - \text{PHPMA}_z$ diblock copolymer nanoparticles were synthesised by RAFT aqueous dispersion polymerisation (see Figure 1). As reported previously,^{41, 42} diluting the cationic PQDMA macro-CTA with the non-ionic PGMA macro-CTA leads to entropic mixing with the stabiliser coronal layer, which enables fine control of the surface charge density in the resulting nanoparticles. In such a PISA formulation, several variables require optimisation, including (i) the DPs (x, y) of the PGMA and PQDMA of the stabiliser blocks, (ii) the PHPMA core-forming DP (z) and (iii) the PQDMA/PGMA molar ratio (n). In addition, the copolymer concentration is often found to be an important parameter, with pure worm and vesicle phases typically being observed only at higher concentrations.^{23, 34} To minimise the parameter space to be explored for this binary mixture of macro-CTAs formulation, all PISA syntheses were conducted at 20 % w/w solids. It is also worth emphasising that no added salt was required, whereas Semsarilar et al.^{41, 42} reported that addition of 0.30 M NaCl




Figure 3. Phase diagram constructed for a series of diblock copolymer nanoparticles of general formula $([1-n] \text{ PGMA}_{62} + [n] \text{ PQDMA}_{95}) - \text{PHPMA}_z$ prepared by RAFT aqueous dispersion polymerisation of HPMA at 20 % w/w solids. S = spheres, W = worms, V = vesicles, S + W = mixed phase of spheres plus worms, W + V = mixed phase of worms plus vesicles.

was necessary to screen the unfavourable electrostatics in order to access higher morphologies.

The first step in optimising this PISA formulation was to fix the DP of the non-ionic PGMA stabiliser and vary the DP of the PQDMA stabiliser in order to examine the cationic character of the resulting nanoparticles. More specifically, RAFT solution polymerisation was utilised to prepare a PGMA_{62} macro-CTA and three PQDMA macro-CTAs with DPs (or y) of 26, 48 or 95, respectively. A series of PISA formulations were then conducted, targeting a fixed PHPMA core-forming block DP (or z) of 200 using a PQDMA mol fraction, n , of 0.10 (i.e. 10 mol % PQDMA). Figure 2 shows the TEM images and aqueous electrophoresis data obtained for the resulting nanoparticles prepared with the general formula $(0.9 \text{ PGMA}_{62} + 0.1 \text{ PQDMA}_y) - \text{PHPMA}_{200}$ where $y = 26, 48$ or 95 . Purely non-ionic PGMA_{62} - PHPMA_{200} diblock copolymer nanoparticles with no PQDMA present (i.e. $n = 0$) were also synthesised as a control. TEM analysis confirms that all of the nanoparticles have the same characteristic worm-like morphology. The zeta potential vs. pH curve for the non-ionic PGMA_{62} - PHPMA_{200} diblock copolymer worms indicates that these nanoparticles possess essentially no surface charge at around pH 4, but become weakly anionic (-15 to -18 mV) above pH 6. This is attributed to ionisation of the terminal carboxylic acid group ($\text{pK}_a \sim 4.7$)⁴⁷ located at the end of the stabiliser chains. Incorporating 10 mol % of a relatively short PQDMA_{26} stabiliser (i.e. $(0.9 \text{ PGMA}_{62} + 0.1 \text{ PQDMA}_{26}) - \text{PHPMA}_{200}$) leads to weakly cationic character (around +17 mV at pH 3, gradually reducing to 0 mV at around pH 9.5). Clearly the cationic nature of the quaternised PQDMA_{26} stabiliser is partially shielded by the longer non-ionic PGMA_{62} stabiliser. The worms become significantly more cationic (+15 to +23 mV) over the entire pH range when the PQDMA_{26} stabiliser is replaced with PQDMA_{48} . As expected, using the PQDMA_{95} stabiliser produces the most cationic worms (around +30 mV up to pH 9), since these longer chains protrude beyond the non-ionic PGMA_{62} stabiliser chains. It is noteworthy that this represents a marked improvement over the electrophoretic data reported by Semsarilar and co-workers, who obtained cationic worms only at relatively low pH.⁴² Clearly, increasing the cationic stabiliser block DP beyond that of the non-




Figure 4. Representative transmission electron microscopy images obtained for selected diblock copolymer nanoparticles of general formula $[(1-n) \text{PGMA}_{62} + [n] \text{PQDMA}_{95}] - \text{PHPMA}_{250}$ prepared by RAFT aqueous dispersion polymerisation of HPMA at 20 % w/w solids when n is varied from 0 to 0.30. The scale bar shown applies to all images. A pure vesicle phase is obtained when $n = 0$, a worms plus vesicles mixed phase is observed when $n = 0.10$, a spheres plus worms mixed phase is produced when $n = 0.2 - 0.3$ and a pure sphere phase is found when $n = 0.40 - 0.50$.

ionic block DP enables the cationic character of worms (and presumably other copolymer morphologies) to be maximised. Thus this design principle was adopted for the remaining part of the current study, which was focused on exploring the judicious combination of the PQDMA₉₅ and PGMA₆₃ stabiliser blocks. The remaining two variables in this system, namely the PHPMA core-forming DP (z), and the PQDMA₉₅/PGMA₆₂ stabiliser molar ratio (n) were systematically varied in order to construct a phase diagram as judged by TEM and DLS studies, see Figure 3. Each data point on this phase diagram corresponds to an individual PISA synthesis for which a final HPMA conversion of at least 99 % was achieved. First, a series of non-ionic PGMA₆₂-PHPMA₂ diblock copolymer nanoparticles were prepared. Determining the precise PHPMA DP corresponding to pure phases of spheres, worms or vesicles provided a good starting point for the gradual introduction of the cationic PQDMA₉₅ auxiliary stabiliser. Furthermore, these PGMA₆₂-PHPMA₂ diblocks could be readily characterised by DMF GPC. It was found that the PGMA₆₂ macro-CTA ($M_w/M_n = 1.12$) could be chain-extended to produce a PGMA₆₂-PHPMA₄₅₀ diblock copolymer




Figure 5. Zeta potential vs pH curves recorded for diblock copolymer nanoparticles of general formula $[(1-n) \text{PGMA}_{62} + [n] \text{PQDMA}_{95}] - \text{PHPMA}_{200}$ when n is varied from 0 to 0.20.

($M_w/M_n = 1.17$), see Figure S3. Inspecting Figure S3, a high molecular weight shoulder can be observed, which has been previously attributed to light branching caused by the relatively low level (< 0.30 mol %) of dimethacrylate impurity in HPMA monomer.^{22, 33} This feature becomes more prominent as the target DP of the PHPMA core-forming block is increased, but it is emphasised that this has no discernible effect on the final particle morphology.^{22, 23, 33} This suggests reasonably good living character, as expected for such RAFT-mediated PISA syntheses.³³ Unfortunately, it was not feasible to characterise the cationic diblock copolymer nanoparticles prepared using binary mixtures of macro-CTAs as there is no suitable common solvent that dissolves PQDMA, PGMA and PHPMA. However, given the relatively high blocking efficiency exhibited by the PGMA₆₂ macro-CTA, and our previous reports describing the use of a wide range of macro-CTAs to polymerise HPMA via RAFT aqueous dispersion polymerisation,⁴⁸ reasonably good living character should be expected under such conditions when using such a binary mixture of methacrylic macro-CTAs. From the phase diagram shown in Figure 3, pure phases of spheres ($z = 100$ to 125), worms ($z = 150$ -to 200) and vesicles ($z = 225$ to 500) can be clearly identified when using the reference PGMA₆₂-PHPMA₂ PISA formulation. Crossing the phase diagram horizontally from left to right, the effect of systematically varying the proportion of PQDMA₉₅ macro-CTA can be assessed. For a fixed PHPMA core block DP (e.g. 350), increasing the mol fraction (n) of this cationic stabiliser typically results in a gradual change in copolymer morphology from vesicles to spheres. This trend holds for all PHPMA DPs from 150 to 500, but for a DP of 100 only spheres can be obtained, regardless of the value of n . Figure 4 shows representative TEM images used to assign the morphology of a series of diblock copolymer nanoparticles with the general formula $[(1-n) \text{PGMA}_{62} + [n] \text{PQDMA}_{95}] - \text{PHPMA}_{250}$, where n ranges from 0.0 to 0.50. When no cationic PQDMA₉₅ macro-CTA is present (i.e. if $n = 0$), a well-defined vesicular morphology is observed. However, the addition of just 10 mol % ($n = 0.10$) PQDMA₉₅ stabiliser results in the formation of a mixed phase comprising vesicles and worms, while a mixture of worms and spheres is observed for $n = 0.20$ to 0.30 and only spheres are obtained at $n = 0.40$. Considering the effect of varying the PHPMA core-forming block DP from 100 to 500 at a fixed PQDMA₉₅ stabiliser is also instructive. For




Figure 6. Temperature-dependent rheology studies for a 12.5 % w/w aqueous dispersion of cationic diblock copolymer worms of general formula $(0.95 \text{ PGMA}_{62} + 0.05 \text{ PQDMA}_{95}) - \text{PHPMA}_{200}$. The angular frequency was held constant at 1.0 rad s^{-1} at an applied strain of 1.0%.

example, when no cationic stabiliser is present ($n = 0$), a PHPMA DP of just 225 results in a pure vesicle morphology. However, when $n = 0.10$ there is a gradual change from spheres (DP = 100) to worms (DP = 150 to 200) to a mixed worm/vesicle phase (DP = 225 to 300) to finally a pure vesicle phase (DP = 350 to 500). Clearly, introducing a polyelectrolytic stabiliser block leads to greater inter-chain repulsive forces, which makes so-called higher order morphologies (i.e. worms or vesicles) more difficult to access. Furthermore, larger mixed phase regions are produced as the proportion of PQDMA₉₅ is increased. For example, for $n = 0.20$ (or 20 mol % PQDMA₉₅ stabiliser), no pure worm phase could be obtained, and for a rather broad PHPMA DP range of 150 to 400, only mixed phases could be identified prior to the eventual formation of a pure vesicle phase at a DP of 450. No pure vesicle phase was accessible for $n = 0.30$, while at $n = 0.50$ inter-chain repulsion becomes so strong that only kinetically-trapped spheres can be produced even when targeting a DP of 500. This is comparable to observations for PQDMA₉₅-PHPMA₂ diblock copolymer nanoparticles (i.e. in the absence of any non-ionic PGMA₆₂ stabiliser).

Figure 5 shows the corresponding zeta potential vs pH curves obtained for a series of diblock copolymer nanoparticles with the general formula $([1-n] \text{ PGMA}_{62} + [n] \text{ PQDMA}_{95}) - \text{PHPMA}_{200}$, i.e. for a fixed PHPMA DP of 200 where n is varied from 0 to 0.20. As the proportion of PQDMA₉₅ is increased, the nanoparticle zeta potential gradually becomes less anionic/more cationic over the whole pH range. For example, at pH 9 the zeta potential increases monotonically from -20 mV when no PQDMA₉₅ is present (i.e. $n = 0$), to +35 mV for $n = 0.20$. Clearly, using a binary mixture of macro-CTAs enables fine-tuning of the cationic character of the nanoparticles. Furthermore, as the PQDMA₉₅ stabiliser is longer than the non-ionic PGMA₆₂ stabiliser, strongly cationic zeta potentials can be maintained over the entire pH range. Given the phase diagram shown in Figure 3, then in principle judicious variation of the mol fraction of the cationic stabiliser block (n) and the target DP of the PHPMA core-forming block (z), enables nanoparticles with a desired copolymer morphology and zeta potential to be targeted reproducibly.

We have previously reported that PGMA-PHPMA diblock copolymer worms form relatively soft free-standing gels at high concentration

due to inter-worm entanglements.^{35, 36, 38} These worms are thermo-sensitive, with degelation occurring on cooling below the critical gelation temperature (CGT) as a result of a worm-to-sphere transition. If performed above the critical gelation concentration (CGC), this transition is fully reversible: multiple sphere-sphere fusion commences on returning to room temperature, the original worms are reformed and a new gel is formed with essentially identical physical properties to that of the original gel. This thermo-reversible enables convenient sterilisation of the worm gels via cold ultrafiltration,³⁵ which suggests various biomedical applications.^{39, 40} It is well-known that many cationic polymers exhibit anti-bacterial properties.^{44, 49, 50, 51, 52, 53, 54} In principle, incorporating appreciable cationic character into such worm gels might confer anti-microbial properties.⁴⁵ From the phase diagram constructed in Figure 3, worm phase space can be reproducibly targeted by optimising the PISA formulation, e.g. by targeting a PHPMA DP (z) of 150 – 200 when utilising a PQDMA₉₅ mol fraction of $0 < n \leq 0.15$ (when $n = 0.20$ a gel is also obtained, but TEM analysis indicates that this sample comprises a mixture of worms and spheres, see Figure S4). Such aqueous cationic worms form free-standing gels when prepared directly at 20 % w/w solids. After their PISA synthesis at 20 % w/w, these worm gels were serially diluted using deionised water until degelation was observed. This copolymer concentration was taken to be the critical gelation concentration (CGC). The CGC of the reference non-ionic PGMA₆₂-PHPMA₂₀₀ diblock copolymer worms was estimated to be 5.0 % w/w, which is in fairly good agreement with previous work.³⁶ The corresponding CGC values for copolymers containing 5, 10, 15 and 20 mol % PQDMA₉₅ were 10.0, 12.5, 15.0 and 17.5 % w/w, respectively (see Figure S4). According to Figure 5, increasing the proportion of PQDMA₉₅ stabiliser results in a systematic increase in nanoparticle zeta potential. Thus the monotonic increase in CGC is most likely the result of weaker inter-worm interactions as the increasing cationic character leads to greater electrostatic repulsion between neighbouring worms. This also leads to a gradual reduction in the storage modulus (G') for this series of worm gels.

To investigate how the introduction of cationic character affects the thermo-responsive properties of the worm gels, a $(0.95 \text{ PGMA}_{62} + 0.05 \text{ PQDMA}_{95}) - \text{PHPMA}_{200}$ diblock copolymer was diluted to 12.5 % w/w and subjected to variable temperature rheology studies, see Figure 6. The aqueous dispersion, which formed a soft free-standing gel at 25 °C, was cooled to 2 °C at 1 °C intervals before warming up to 25 °C using the same temperature ramp. Both temperature sweeps were conducted at a strain of 1.0 % and an angular frequency of 1.0 rad s^{-1} . This particular frequency was selected because G' exceeds G'' at 25 °C which indicates gel formation under these conditions, while the strain sweep conducted at this same frequency confirmed that an applied strain of 1.0 % falls well within the linear viscoelastic regime (see Figure S5). Inspecting the cooling data (red and blue open circles) shown in Figure 6, the storage modulus (G') initially exceeds the loss modulus (G'') at 25 °C, which suggests the formation of a viscoelastic gel. Degelation is observed at a critical gelation temperature (CGT) of 7 °C, which corresponds to the point where the G'' (open blue circles) and G' (open red circles) curves intersect. Below this CGT, the dispersion behaves as a free-flowing liquid. On heating the cold dispersion (red and blue closed circles), the G' (closed red circles) and G'' (closed blue circles)




Figure 7. Images obtained for lawns of *S. aureus* S235 on agar plates upon which drops of either copolymer worm gels or PBS were applied prior to incubation at 37°C overnight: (A) cationic worm gel, (B) non-ionic worm gel, (C) PBS. Bacterial growth was observed when employing the non-ionic worm gel and the PBS control, but not for the cationic worm gel. Arrow shows the location of the PBS droplet.

curves cross at 11 °C, indicating mild hysteresis. This is because the dissociation of worms to form spheres is relatively rapid, whereas the multiple sphere fusion required to reform worms is a highly cooperative process, which requires a longer time scale. Such hysteresis can be minimised by either warming at a slower rate or working at a higher copolymer concentration to aid the sphere-to-worm transition. Nevertheless the rheology data presented in Figure 6 confirms that this particular cationic worm gel (+20 mV at pH 6) exhibits essentially the same thermo-responsive behaviour as the non-ionic reference PGMA₆₂-PHPMA₂₀₀ worm gel (see Figure S6). Variable temperature ¹H NMR spectroscopy studies performed by Blanazs et al.³⁵ suggest that the thermo-sensitive core-forming PHPMA block becomes more hydrated on cooling. This leads to a subtle increase in the packing parameter for the copolymer chains, which in turn induces the worm-to-sphere transition.⁵⁵ Although this cationic worm gel is thermo-responsive, its gel strength of 137 Pa is significantly lower than the G' of 185 Pa observed for the non-ionic PGMA₆₂-PHPMA₂₀₀ worm gel at 25 °C (see Figure S6). Furthermore, increasing the proportion of PQDMA₉₅ from 5 to 10 mol % (n = 0.05 to n = 0.10) led to *irreversible* thermally-triggered degelation; regelation was no longer observed on warming from 2 °C to 20 °C on the time scale of the rheology experiment. This is consistent with our hypothesis that greater cationic character reduces the gel strength.

It has been widely reported that cationic nanoparticles often exhibit useful anti-microbial activity.^{43, 44, 45, 46} Thus the antimicrobial properties of the cationic thermo-responsive (0.95 PGMA₆₂ + 0.05 PQDMA₉₅) – PHPMA₂₀₀ worm gel were investigated. Using a direct contact assay between bacteria and the 12.5 % w/w copolymer gel (the so-called 'drop on' technique), no growth of *S. aureus* S235 was observed beneath the cationic worm gel (see Figure 7A), whereas bacterial growth was clearly discernible underneath the non-ionic copolymer control gel (and also where the aqueous PBS droplet had been placed), see Figures 7B and 7C, respectively. This suggests a bacteriostatic effect for the cationic worm gel. *S. aureus* S235 was also exposed to either the cationic worm gel, the non-ionic worm gel or to PBS at room temperature for 18 h under non-growth conditions. The number of surviving, cultivable bacteria was assessed by separating the bacteria from the worm gels by cooling to induce degelation, followed by dilution using cold PBS (see Figure 8). No nutrients were available during this period and the number of cultivable bacteria declined in PBS over that period by 56 ± se 16%. However, exposure to the cationic worm gel resulted in a




Figure 8 *S. aureus* S235 incubated with cationic and non-ionic worm gels for varying times under non-growth conditions. Data are viable counts per ml of surviving bacteria; error bars are +/- standard error.

reduction in viable bacteria count of 73 ± se 10%, which was significantly greater (p = 0.04, t-test) than that obtained on exposure of the bacteria to the control non-ionic worm gel (48 ± se 14%). These preliminary data suggest a mild bactericidal effect for the cationic worm gel.

Conclusions

A series of cationic diblock copolymer nano-objects with the general formula $([1-n] \text{PGMA}_x + [n] \text{PQDMA}_y) - \text{PHPMA}_z$ has been synthesised at 20 % w/w solids via RAFT aqueous dispersion polymerisation of HPMA utilising a binary mixture of non-ionic and cationic macro-CTAs. If the cationic PQDMA stabiliser is longer than the non-ionic PGMA stabiliser, the resulting diblock copolymer nanoparticles retain their cationic character over the entire pH range. By fixing the PGMA and PQDMA DPs at 62 and 95 respectively, phase boundaries can be identified for cationic spheres, worms and vesicles when systematically varying (i) the PQDMA mol fraction (n) and (ii) the mean DP of the core-forming PHPMA block (z). Furthermore, increasing the proportion of cationic stabiliser in these diblock copolymer nano-objects at a fixed PHPMA DP enables the zeta potential to be adjusted at a given pH. However, the greater cationic character observed for PQDMA-rich formulations also tends to favour a spherical morphology. Variable temperature rheology studies indicate that a thermo-responsive cationic worm gel exhibiting a zeta potential of +20 mV and a storage modulus of 137 Pa can be prepared when using 5 mol % PQDMA stabiliser in the PISA formulation. Moreover, this soft free-standing gel at 25 °C undergoes degelation on cooling 7 °C as a result of a worm-to-sphere transition and this order-order transition is fully reversible at 12.5 % w/w solids. Finally, these cationic thermo-responsive gels were shown to be both bacteriostatic and mildly bactericidal against *S. aureus*, whereas the non-ionic reference worm gel exhibited no discernible anti-microbial activity.

Acknowledgements

We thank P & G (Belgium) for financial support. SPA acknowledges EPSRC (EP/J007846/1) and ERC grants (PISA 320372).

Notes and references

- L. F. Zhang and A. Eisenberg, *Science*, 1995, **268**, 1728-1731.
- Y. Geng, P. Dalhaimer, S. Cai, R. Tsai, M. Tewari, T. Minko and D. E. Discher, *Nature Nanotechnology*, 2007, **2**, 249-255.
- Y. Y. Won, H. T. Davis and F. S. Bates, *Science*, 1999, **283**, 960-963.
- X. Wang, G. Guerin, H. Wang, Y. Wang, I. Manners and M. A. Winnik, *Science*, 2007, **317**, 644-647.
- T. Gaedt, N. S. Jeong, G. Cambridge, M. A. Winnik and I. Manners, *Nature Materials*, 2009, **8**, 144-150.
- N. Petzetakis, A. P. Dove and R. K. O'Reilly, *Chemical Science*, 2011, **2**, 955-960.
- B. M. Discher, Y. Y. Won, D. S. Ege, J. C. M. Lee, F. S. Bates, D. E. Discher and D. A. Hammer, *Science*, 1999, **284**, 1143-1146.
- D. E. Discher and A. Eisenberg, *Science*, 2002, **297**, 967-973.
- J. Rodriguez-Hernandez and S. Lecommandoux, *Journal of the American Chemical Society*, 2005, **127**, 2026-2027.
- G. Battaglia and A. J. Ryan, *Nature Materials*, 2005, **4**, 869-876.
- S. Stewart and G. Liu, *Angewandte Chemie-International Edition*, 2000, **39**, 340-+.
- D. Chen, S. Park, J.-T. Chen, E. Redston and T. P. Russell, *Acs Nano*, 2009, **3**, 2827-2833.
- D. J. Pochan, Z. Y. Chen, H. G. Cui, K. Hales, K. Qi and K. L. Wooley, *Science*, 2004, **306**, 94-97.
- G. Battaglia and A. J. Ryan, *Journal of the American Chemical Society*, 2005, **127**, 8757-8764.
- A. Blanazs, M. Massignani, G. Battaglia, S. P. Armes and A. J. Ryan, *Advanced Functional Materials*, 2009, **19**, 2906-2914.
- J. Z. Du, Y. Q. Tang, A. L. Lewis and S. P. Armes, *Journal of the American Chemical Society*, 2005, **127**, 17982-17983.
- S. Perrier and P. Takolpuckdee, *Journal of Polymer Science Part a-Polymer Chemistry*, 2005, **43**, 5347-5393.
- G. Moad, E. Rizzardo and S. H. Thang, *Polymer*, 2008, **49**, 1079-1131.
- G. Moad, E. Rizzardo and S. H. Thang, *Accounts of Chemical Research*, 2008, **41**, 1133-1142.
- Z. An, Q. Shi, W. Tang, C.-K. Tsung, C. J. Hawker and G. D. Stucky, *Journal of the American Chemical Society*, 2007, **129**, 14493-14499.
- J. Rieger, C. Gazon, B. Charleux, D. Alaimo and C. Jerome, *Journal of Polymer Science Part a-Polymer Chemistry*, 2009, **47**, 2373-2390.
- Y. Li and S. P. Armes, *Angewandte Chemie-International Edition*, 2010, **49**, 4042-4046.
- A. Blanazs, A. J. Ryan and S. P. Armes, *Macromolecules*, 2012, **45**, 5099-5107.
- S. Boisse, J. Rieger, K. Belal, A. Di-Cicco, P. Beaunier, M.-H. Li and B. Charleux, *Chemical Communications*, 2010, **46**, 1950-1952.
- X. Zhang, S. Boisse, W. Zhang, P. Beaunier, F. D'Agosto, J. Rieger and B. Charleux, *Macromolecules*, 2011, **44**, 4149-4158.
- I. Chaduc, W. Zhang, J. Rieger, M. Lansalot, F. D'Agosto and B. Charleux, *Macromolecular Rapid Communications*, 2011, **32**, 1270-1276.
- S. Boisse, J. Rieger, G. Pembouong, P. Beaunier and B. Charleux, *Journal of Polymer Science Part a-Polymer Chemistry*, 2011, **49**, 3346-3354.
- W. Zhang, F. D'Agosto, O. Boyron, J. Rieger and B. Charleux, *Macromolecules*, 2011, **44**, 7584-7593.
- W.-M. Wan and C.-Y. Pan, *Polymer Chemistry*, 2010, **1**, 1475-1484.
- C.-Q. Huang and C.-Y. Pan, *Polymer*, 2010, **51**, 5115-5121.
- E. R. Jones, M. Semsarilar, A. Blanazs and S. P. Armes, *Macromolecules*, 2012, **45**, 5091-5098.
- L. A. Fielding, M. J. Derry, V. Ladmiral, J. Rosselgong, A. M. Rodrigues, L. P. D. Ratcliffe, S. Sugihara and S. P. Armes, *Chemical Science*, 2013, **4**, 2081-2087.
- A. Blanazs, J. Madsen, G. Battaglia, A. J. Ryan and S. P. Armes, *Journal of the American Chemical Society*, 2011, **133**, 16581-16587.
- S. Sugihara, A. Blanazs, S. P. Armes, A. J. Ryan and A. L. Lewis, *Journal of the American Chemical Society*, 2011, **133**, 15707-15713.
- A. Blanazs, R. Verber, O. O. Mykhaylyk, A. J. Ryan, J. Z. Heath, C. W. I. Douglas and S. P. Armes, *Journal of the American Chemical Society*, 2012, **134**, 9741-9748.
- R. Verber, A. Blanazs and S. P. Armes, *Soft Matter*, 2012, **8**, 9915-9922.
- L. P. D. Ratcliffe, A. J. Ryan and S. P. Armes, *Macromolecules*, 2013, **46**, 769-777.
- V. J. Cunningham, L. P. D. Ratcliffe, A. Blanazs, N. J. Warren, A. J. Smith, O. O. Mykhaylyk and S. P. Armes, *Polymer Chemistry*, 2014, **5**, 6307-6317.
- I. W. Canton, N. J.; Chahal, A.; Amps, K.; Wood, A.; Weightman, R.; Wang, E.; Moore, H.; Armes, S. P., *ACS Central Science*, 2016, DOI: 10.1021/acscentsci.5b00370.
- D. E. L. Mitchell, J. R.; Armes, S. P.; Gibson, M. I., *Angewandte Chemie-International Edition*, 2016, DOI: 10.1002/ange.201511454.
- M. Semsarilar, V. Ladmiral, A. Blanazs and S. P. Armes, *Langmuir*, 2012, **28**, 914-922.
- M. Semsarilar, V. Ladmiral, A. Blanazs and S. P. Armes, *Langmuir*, 2013, **29**, 7416-7424.
- E.-R. Kenawy, S. D. Worley and R. Broughton, *Biomacromolecules*, 2007, **8**, 1359-1384.
- H. Murata, R. R. Koepsel, K. Matyjaszewski and A. J. Russell, *Biomaterials*, 2007, **28**, 4870-4879.

45. M. Malmsten, *Soft Matter*, 2011, **7**, 8725-8736.
46. W. Yuan, J. Wei, H. Lu, L. Fan and J. Du, *Chemical Communications*, 2012, **48**, 6857-6859.
47. J. R. Lovett, N. J. Warren, L. P. D. Ratcliffe, M. K. Kocik and S. P. Armes, *Angewandte Chemie-International Edition*, 2015, **54**, 1279-1283.
48. N. J. Warren and S. P. Armes, *Journal of the American Chemical Society*, 2014, **136**, 10174-10185.
49. V. Sambhy, B. R. Peterson and A. Sen, *Angewandte Chemie-International Edition*, 2008, **47**, 1250-1254.
50. A. Munoz-Bonilla and M. Fernandez-Garcia, *Progress in Polymer Science*, 2012, **37**, 281-339.
51. E. F. Palermo and K. Kuroda, *Applied Microbiology and Biotechnology*, 2010, **87**, 1605-1615.
52. S. Lenoir, C. Pagnoulle, C. Detrembleur, M. Galleni and R. Jerome, *Journal of Polymer Science Part a-Polymer Chemistry*, 2006, **44**, 1214-1224.
53. J. Hoque, P. Akkapeddi, V. Yarlagadda, D. S. S. M. Uppu, P. Kumar and J. Haldar, *Langmuir*, 2012, **28**, 12225-12234.
54. A. Colomer, A. Pinazo, M. A. Manresa, M. P. Vinardell, M. Mitjans, M. R. Infante and L. Perez, *Journal of Medicinal Chemistry*, 2011, **54**, 989-1002.
55. J. Madsen, S. P. Armes, K. Bertal, S. MacNeil and A. L. Lewis, *Biomacromolecules*, 2009, **10**, 1875-1887.

