

This is a repository copy of *On the Effect of Microwave Energy on Lipase-Catalyzed Polycondensation Reactions*.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/id/eprint/105047/>

Article:

Farmer, Thomas James orcid.org/0000-0002-1039-7684, Pellis, Alessandro and Guebitz, Georg (2016) On the Effect of Microwave Energy on Lipase-Catalyzed Polycondensation Reactions. *MOLECULES*. 1245. pp. 1-11. ISSN: 1420-3049

<https://doi.org/10.3390/molecules21091245>

Reuse

Items deposited in White Rose Research Online are protected by copyright, with all rights reserved unless indicated otherwise. They may be downloaded and/or printed for private study, or other acts as permitted by national copyright laws. The publisher or other rights holders may allow further reproduction and re-use of the full text version. This is indicated by the licence information on the White Rose Research Online record for the item.

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.

Supplementary Materials: On the Effect of Microwave energy on Lipase-Catalyzed Polycondensation Reactions

Alessandro Pellis, Georg M. Guebitz and Thomas J. Farmer

Table S1. Solvent-free reactions catalyzed by Novozym 435® after 4 h of reaction.

| Entry (n°) | Diester (A) | Diol (B) | Heating | | T (°C) | Vessel Open/Close | Conversion (%) * | M _w (Da) ^λ | M _n (Da) ^λ | PDI ^λ |
|------------|-------------|----------|---------|----------|--------|-------------------|------------------|----------------------------------|----------------------------------|------------------|
| | | | MW | Oil Bath | | | | | | |
| Blank | DMA | BDO | + | | 50 | Open | - | - | - | - |
| Blank | DMA | BDO | | + | 50 | Close | - | - | - | - |
| 2 | DMA | BDO | + | | 50 | Close | 39 | 509 | 483 | 1.054 |
| 2 | DMA | BDO | | + | 50 | Close | 40 | 515 | 488 | 1.055 |
| 4 | DMS | BDO | + | | 50 | Open | 44 | 546 | 456 | 1.197 |
| 4 | DMS | BDO | | + | 50 | Open | 47 | 599 | 528 | 1.134 |
| 7 | DMS | BDO | + | | 50 | Open | 11 | 391 | 335 | 1.167 |
| 7 | DMS | BDO | | + | 50 | Open | 46 | 611 | 543 | 1.125 |

* Calculated via ¹H-NMR spectra; ^λ Calculated via GPC. Abbreviations: DMA: dimethyl adipate; DMS: dimethyl succinate; BDO: 1,4-butanediol.

Table S2. Reactions in organic media catalyzed by Novozym 435® after 4 h of reaction.

| Entry (n°) | Diester (A) | Diol (B) | Heating | | T (°C) | Conversion (%) * | M _w (Da) ^λ | M _n (Da) ^λ | PDI ^λ |
|------------|-------------|----------|---------|----------|--------|------------------|----------------------------------|----------------------------------|------------------|
| | | | MW | Oil Bath | | | | | |
| Blank | DMS | BDO | + | | 38 | - | - | - | - |
| Blank | DMS | BDO | | + | 38 | - | - | - | - |
| 9 | DMS | BDO | + | | 30 | 39 | 373 | 330 | 1.130 |
| 9 | DMS | BDO | | + | 30 | 38 | 303 | 287 | 1.056 |
| 11 | DMS | BDO | + | | 38 | 45 | 480 | 399 | 1.203 |
| 11 | DMS | BDO | | + | 38 | 46 | 479 | 391 | 1.225 |
| 13 | DMS | BDO | + | | 38 | 47 | 553 | 514 | 1.076 |
| 13 | DMS | BDO | | + | 38 | 48 | 530 | 505 | 1.050 |

* Calculated via ¹H-NMR spectra; ^λ Calculated via GPC. Abbreviations: DMA: dimethyl adipate; DMS: dimethyl succinate; BDO: 1,4-butanediol.




Figure S1. ¹H-NMR spectrum of the polycondensation products of DMS with BDO catalyzed by 10% w/w Novozym 435 at 4 h. Entry 2 Table 1 and Table S1.




Figure S2. Time-course monitoring of the monomers conversion via ^1H -NMR spectra of the bulk reaction performed in a closed vessel at 50 °C without using the Power Max function.




Figure S3. Time-course monitoring of the monomers conversion via ^1H -NMR spectra of the bulk reaction performed in an open vessel at 50 °C without using the Power Max function.




Figure S4. Time-course monitoring of the monomers conversion via ^1H -NMR spectra of the bulk reaction performed in an open vessel at 50 °C using the Power Max function.