



Deposited via The University of Sheffield.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/id/eprint/172125/>

Version: Published Version

Article:

Shao, H., Ying, G., Lennon, S.A. et al. (2020) Purcell enhancement of a deterministically coupled quantum dot in an SU-8 laser patterned photonic crystal heterostructure. *Applied Physics Letters*, 117 (4). 043103. ISSN: 0003-6951

<https://doi.org/10.1063/5.0018673>

This article may be downloaded for personal use only. Any other use requires prior permission of the author and AIP Publishing. The following article appeared in *Applied Physics Letters* 117:4 and may be found at <https://doi.org/10.1063/5.0018673>.

Reuse

Items deposited in White Rose Research Online are protected by copyright, with all rights reserved unless indicated otherwise. They may be downloaded and/or printed for private study, or other acts as permitted by national copyright laws. The publisher or other rights holders may allow further reproduction and re-use of the full text version. This is indicated by the licence information on the White Rose Research Online record for the item.

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.

Purcell enhancement of a deterministically coupled quantum dot in an SU-8 laser patterned photonic crystal heterostructure

Cite as: Appl. Phys. Lett. **117**, 043103 (2020); <https://doi.org/10.1063/5.0018673>

Submitted: 17 June 2020 . Accepted: 15 July 2020 . Published Online: 27 July 2020

H. Shao, G. Ying, S. A. Lennon, F. S. F. Brossard, J. P. Griffiths, L. P. Nuttall, V. Osokin , E. Clarke , H. He , and R. A. Taylor 



View Online



Export Citation



CrossMark

ARTICLES YOU MAY BE INTERESTED IN

[Thermally enhanced hole injection and breakdown in a Schottky-metal/p-GaN/AlGaN/GaN device under forward bias](#)

Applied Physics Letters **117**, 043501 (2020); <https://doi.org/10.1063/5.0011831>

[Light propagation in aperiodic photonic lattices created by synthesized Mathieu–Gauss beams](#)

Applied Physics Letters **117**, 041102 (2020); <https://doi.org/10.1063/5.0013174>

[Organic polariton lasing with molecularly isolated perylene diimides](#)

Applied Physics Letters **117**, 041103 (2020); <https://doi.org/10.1063/5.0012461>

Lock-in Amplifiers
up to 600 MHz



Purcell enhancement of a deterministically coupled quantum dot in an SU-8 laser patterned photonic crystal heterostructure

Cite as: Appl. Phys. Lett. **117**, 043103 (2020); doi: [10.1063/5.0018673](https://doi.org/10.1063/5.0018673)

Submitted: 17 June 2020 · Accepted: 15 July 2020 ·

Published Online: 27 July 2020



View Online



Export Citation



CrossMark

H. Shao,¹ G. Ying,² S. A. Lennon,² F. S. F. Brossard,³ J. P. Griffiths,⁴ L. P. Nuttall,² V. Osokin,²  E. Clarke,⁵  H. He,^{1,a)} 
and R. A. Taylor^{2,b)} 

AFFILIATIONS

¹State Key Laboratory of Mechanics and Control of Mechanical Structures, Nanjing University of Aeronautics and Astronautics, Yuda Street No. 29, Nanjing, Jiangsu 210016, China

²Clarendon Laboratory, Department of Physics, University of Oxford, Oxford OX1 3PU, United Kingdom

³Hitachi Cambridge Laboratory, Hitachi Europe Ltd, Cambridge CB3 0HE, United Kingdom

⁴Cavendish Laboratory, University of Cambridge, J. J. Thomson Avenue, Cambridge CB3 0HE, United Kingdom

⁵Centre for Nanoscience and Technology, University of Sheffield, Broad Lane, Sheffield S3 7HQ, United Kingdom

^{a)}Electronic mail: hehuan@nuaa.edu.cn

^{b)}Author to whom correspondence should be addressed: robert.taylor@physics.ox.ac.uk

ABSTRACT

Enhancement of single photon source emission through cavity quantum electrodynamics is key to the realization of applicable emitters in many quantum optics technologies. In this work, we present a flexible and convenient cavity fabrication process that writes a SU-8 microstrip onto a photonic crystal waveguide deterministically, in which InGaAs/GaAs quantum dots are present as emitters. The strip cavity is laser patterned at the location of a quantum dot with a chosen emission wavelength. Micro-photoluminescence studies are undertaken, which demonstrate an enhanced emission intensity by a factor of 2.1 with weak coupling to a single quantum dot, and time-resolved photoluminescence further shows a Purcell enhancement factor of 2.16. The fabrication process is, thus, verified as a reliable recipe to introduce deterministic cavity coupling to a chosen quantum dot.

Published under license by AIP Publishing. <https://doi.org/10.1063/5.0018673>

Single photon sources (SPSs) are highly sought after for application in the fields of quantum information processing and quantum communication,^{1–3} such as for the well-known BB84 quantum key distribution protocol.⁴ A common approach to creating a SPS based on a single quantum dot (QD) is to embed it into an optical cavity. By achieving spectral resonance between a QD emission line and a cavity mode, a coupling can be achieved in which photons are emitted into the cavity mode. This coupled cavity-emitter system enables modification of the spontaneous emission dynamics of the QD, known as the Purcell effect.^{5,6} Coupling of a photonic crystal (PhC) cavity mode to a single QD can offer the potential to realize a Purcell-enhanced SPS with highly directional free-space emission.^{7,8} Such SPSs can also be coupled into optical fibers⁹ or waveguides.^{10–12} Early work on QD-cavity coupling had many dots coupling to a single cavity because of the high density of QDs in the samples.¹³ Progress in growth techniques now allows reliable fabrication of low-density QD samples,¹⁴

which are suited to achieving coupling between a single QD and a cavity in order to achieve a Purcell-enhanced SPS.^{15,16} More extensive research studies on coupling in low-density samples can be found in Refs. 6 and 17–19. It remains a challenge to produce a cavity mode that couples to an individual dot, as the positional accuracy has to be within the cavity mode volume and, simultaneously, the mode wavelength needs to match that of the chosen dot. In this paper, we demonstrate a convenient method of achieving deterministic coupling between a single QD and a PhC cavity mode. Using microphotoluminescence (μ PL) techniques, a target single QD in a PhC waveguide is identified, and a laser-patterning procedure incorporating SU-8 negative photoresist is used to create a PhC cavity mode to couple to the target QD. In the resulting device, a PhC cavity mode with a good Q/V_0 ratio is defined by a cross-linked SU-8 structure on top of the PhC waveguide.^{20,21} The technique allows this cavity mode to be positioned to achieve the spatial overlap with the target QD; close spectral

proximity between the emitter and the cavity is achieved by selecting the target QD based on known properties of the cavity mode.

The photonic crystal sample was grown by molecular beam epitaxy and consisted of a GaAs wafer with a $1\ \mu\text{m}$ thick sacrificial layer of $\text{Al}_{0.7}\text{Ga}_{0.3}\text{As}$ capped with $100\ \text{nm}$ of GaAs. A $0.7\ \text{nm}$ layer of InAs was then deposited followed by $6\ \text{nm}$ of InGaAs, resulting in the formation of QDs $\sim 20\ \text{nm}$ wide, at a density of $\sim 5 \times 10^8\ \text{cm}^{-2}$, and a capping layer of $94\ \text{nm}$ of GaAs.²² This structure is later processed via e-beam lithography and reactive ion etching to produce a series of 2D PhC waveguide as shown in Fig. 1.²¹

The deposition of a SU-8 film on the PhC waveguide red shifts the waveguide band edge as shown in SFig. 1. This shift is sufficient to create a mode gap cavity^{23,24} when patterning a SU-8 strip across the PhC waveguide (SFig. 2). This confinement of photons in the mode gap cavity is akin to the electronic quantum confinement in a

quantum well. Previous theoretical and experimental results confirm that a cavity mode is created successfully by writing either a SU-8 disk or a SU-8 strip (running perpendicular to the waveguide) on top of a PhC waveguide.^{20,21}

Figure 1(a) demonstrates how SU-8 photoresist can be processed to fabricate the mode gap cavity on a registered dot. A mixture of SU-8 and cyclopentanone (ratio of 1:7) is first spin coated onto the sample surface, followed by baking at $95\ ^\circ\text{C}$ for 5 min to give a green colored film [Fig. 1(b)].²⁰ Then, the coated sample is cooled down to $4\ \text{K}$ in a cryostat. A weak $532\ \text{nm}$ continuous wave (CW) laser (which does not expose the SU-8 photoresist) is used to excite the sample through an optical fiber to look for dots of the desired emission wavelength within the missing line of holes by using a piezo-controlled scanning objective. Once a dot has been identified and registered (to an accuracy of $\pm 40\ \text{nm}$),²⁵ a $405\ \text{nm}$ continuous wave laser, which is coupled into the same fiber, is then focused onto the deposited SU-8 layer with a power of $210\ \mu\text{W}$ to expose a line passing over the selected QD perpendicular to the missing line of holes with a writing speed of $0.04\ \mu\text{m}\ \text{s}^{-1}$. Thus, the registration and exposure occur in one experimental session, and many such mode gap cavities can be written on different PhC waveguides in succession or on the same PhC waveguide to create a photonic molecule.²⁰ After laser patterning, the sample is removed from the cryostat and is heated at $90\ ^\circ\text{C}$ again for 5 min and the surrounding unexposed SU-8 residue is then washed out using PGMEA. The resulting SU-8 strip acts as an optical cavity. The overall mode volume is determined by both the waveguide and the SU-8 strip.²⁰

A schematic and an image of a typical fabricated cavity are shown in Figs. 1(c) and 1(d). A comparison of parameters for strip writing processes at $4\ \text{K}$ and $298\ \text{K}$ to give a similar strip size of $1 - 2\ \mu\text{m}$ width and $0.1\ \mu\text{m}$ thickness is shown in Table I to illustrate the change in exposure power and dose necessary at cryogenic temperatures.²⁰ Previous mode gap cavities defined by patterning strips on the surface of PhCs were created at room temperature;^{26,27} here, we demonstrate PhC cavity creation at cryogenic temperatures, allowing deterministic coupling with a quantum dot. The SU-8 strip has a width of $1 - 2\ \mu\text{m}$ and a predicted thickness of $0.1\ \mu\text{m}$, which is patterned on a PhC waveguide with a lattice spacing of $340\ \text{nm}$, a hole diameter of $185\ \text{nm}$, and a slab thickness of $200\ \text{nm}$. This produces a cavity mode resonance wavelength of $1283\ \text{nm}$ at $4\ \text{K}$. This wavelength is within the spectral region of possible InGaAs/GaAs QD emission and determines the QD emission wavelength that is chosen for a registered dot to enable cavity coupling.

At cryogenic temperatures, the emission of a single QD itself becomes visible at a relatively low excitation power ($< 0.25\ \mu\text{W}$) as thermally induced broadening through phonon coupling is less prominent. However, collective emission from an ensemble of QDs can still undergo inhomogeneous broadening due to uncontrollable minor variations in their geometries and sizes, which is inevitable in the sample




FIG. 1. (a) Cavity fabrication via laser exposure of SU-8 at $4\ \text{K}$. (b) Microscope image of the spin-coated SU-8 thin film with the color scale for thickness reference; left: coated uniform film of $\sim 500\ \text{nm}$ thickness; right: Thinning of the SU-8 film on top of the photonic crystal for a thin spin-coated layer (about $300\ \text{nm}$ thick). (c) 3D schematic of the SU-8 strip cavity. The green transparent cone represents excitation laser $532\ \text{nm}$. Cyan strip marks the cavity, and red dots represent QDs. (d) An image of our fabricated cavity.

TABLE I. A comparison of parameters for strip writing processes at $4\ \text{K}$ and $298\ \text{K}$ onto a film of thickness $100\ \text{nm}$ to give a strip of $1-2\ \mu\text{m}$ width.

	$4\ \text{K}$	$298\ \text{K}$
Exposure laser power (μW)	210	17.5
Writing speed (μs^{-1})	0.04	0.25–0.50

growth process as shown in Fig. 2(a).²⁸ It is, hence, necessary to pick out a single emitter by filtering out a QD both spatially and spectrally. μ PL studies of devices doped with high and low densities of dots before depositing SU-8 (Fig. 2) show that in the case of a sample with a low density of QDs, the individual emission lines can be distinguished clearly enough from each other for a $1 \mu\text{m}^2$ excitation area and a single emitter can then be spectrally addressed via cavity coupling. In Fig. 2(b), a single QD emission at the predicted cavity mode wavelength of an SU-8 strip is indicated at 1283.5 nm and the cavity is then drawn at the same location to evaluate the coupling effect. The challenge in finding a QD at the exact same wavelength as the cavity mode is reduced by having many dots lying within the missing line of holes along the waveguide. Thus, performing a 1D μ PL scan to choose a particular QD becomes feasible. This procedure together with the ease of writing a strip cavity anywhere along the waveguide makes the production of a coupled system much more likely and allows for reproducible coupling. The μ PL emission as a function of temperature was measured after creating an SU-8 cavity on top of the location of a single QD with matching emission wavelength, to enable temperature tuning of the coupling. Figure 2(c) shows enhanced emission from the coupling effect at 6 K when the QD wavelength coincides with the cavity mode, with a maximum enhancement in intensity of 2.1 ± 0.1 at resonance. As the QD line redshifts with temperature and weakens the coupling effect, both lines exhibit a drop in intensity until the QD becomes almost invisible next to the background ensemble emission at 30 K. This crossover of the two emissions clearly demonstrates a coupled system where the emitter is at resonance with the optical cavity. Ideally, this crossover should be engineered to occur at a low temperature to preserve the best emission characteristics of the QD. The coupling at 6 K, therefore, fulfills this enhancement condition. Coupling of another system, but at 10 K, is shown in the supplementary material (SFig. 3). The FWHM of the emission is 0.64 nm and results in a quality factor of over 2000, which is large enough to enable the system to enter the weak coupling regime with Purcell enhancement. Limitation

factors such as non-perfect cavity geometry, thick cavity strip, defects in the substrate, and the morphology of the QD itself can prevent the quality factor from getting even higher; however, this quality factor is a more realistic number for practical weak coupling performance.²⁹

In order to verify Purcell enhancement, a comparison of the decay lifetime is performed at 6 K and 30 K (Fig. 3) when the QD emission is on ($\tau = 0.793 \pm 0.102$ ns) and off ($\tau = 1.712 \pm 0.146$ ns) resonance with the SU-8 cavity mode. These lifetimes were obtained after deconvoluting the instrument response function of the detector (130 ps FWHM). A micrometer-controlled output slit together with a multimode fiber of $25 \mu\text{m}$ core is used to spectrally filter the emission line and transmit it to an InGaAs avalanche photodiode to measure the photons. A clear reduction in the lifetime is observed at 6 K consistent with weak coupling. The maximum Purcell factor $F_P = \frac{3}{4\pi^2} \left(\frac{\lambda}{n}\right)^3 \left(\frac{Q}{V}\right)$ derived from Fermi's golden rule, using our quality factor of 2000 and mode volume of $1.3(\lambda/n)^3$, is estimated to be 117, while the measured enhancement at resonance is 2.16 ± 0.14 compared to the uncoupled emission. Such a difference from the theoretically predicted value can be explained by the non-perfect spatial matching between the QD and the cavity and to the fact that the excitation is non-resonant.⁶ Indeed, the position of the cavity mode antinodes created by the presence of the strip is dictated by the lattice geometry, not by the strip as shown in SFig. 2. The position of the strip dictates the intensity of these nodes, and this can be generalized to all multilayer PhC slabs.²⁴ Thus, if a QD is located between the antinodes, no coupling would occur even though the cavity is created at the strip location where the QD has been registered. However, additional markers on the PhC sample could help determine if the chosen QD is at an ideal location within the PhC waveguide for cavity coupling (see the mode pattern in SFig. 2). Other reasons for the discrepancy could be due to the polarization mismatch, crystalline imperfections, and a background contribution from other uncoupled QDs.¹³

We have tested a fabrication method for writing a SU-8 cavity on a PhC waveguide and used a μ PL setup to obtain deterministic coupling between a QD emitter and the cavity mode. The SU-8 strip can




FIG. 2. (a) PL of an ensemble of high density InGaAs/GaAs quantum dots at 4 K. (b) PL of target QDs near 1283.5 nm well separated from the emission from other QDs before cavity deposition. (c) Temperature run after creating the SU-8 cavity at the location from (b) showing coupled emission at 6 K; the QD starts shifting away from the cavity mode as the temperature increases.




FIG. 3. Time-resolved photoluminescence comparison from cavity coupled emission at 6 K toward uncoupled emission at 30 K. A Purcell enhancement factor of 2.16 is calculated.

be developed via a laser patterning procedure at cryogenic temperatures at the QD position. The QD is chosen so that its emission wavelength coincides with the predicted cavity mode resonance and, therefore, increases the likelihood of coupling. The writing process further provides convenience and flexibility in creating a cavity after finding the emitter. The μ PL temperature dependence clearly demonstrates coupling of a single QD emission, a cavity mode, and an increased intensity as they overlap spectrally. Our procedure enables us to simultaneously identify a suitable QD and pattern a PhC cavity at the same position and opens the possibility for scaling the system to coupled cavities with QDs in one or both cavities, allowing electric field control of emission via a photon blockade mechanism. There is also the possibility of forming a series of coupled cavities, resulting in electromagnetically induced transparency.

See the [supplementary material](#) for a comparison of one band of a PhC waveguide with and without a layer of 0.1 μm thick cross-linked SU-8 on the top surface, a schematic of the strip-defined mode gap cavity with the electric field envelope, and a further example of deterministic coupling from a different cavity.

AUTHOR'S CONTRIBUTIONS

H. Shao and G. Ying contributed equally to this work, and other authors contributed to the analysis and the text and planned the experiments.

We acknowledge the Engineering and Physical Sciences Research Council (EPSRC) (Grant No. EP/K014978/1) and the Hitachi Cambridge Research Laboratory.

DATA AVAILABILITY

The data that support the findings of this study are openly available at the Oxford Research Archive <https://doi.org/10.5287/bodleian:ErJbzzO84>.

REFERENCES

- P. Senellart, G. Solomon, and A. White, "High-performance semiconductor quantum-dot single-photon sources," *Nat. Nanotechnol.* **12**, 1026 (2017).
- D. Ladd, F. Jelezko, R. Laflamme, Y. Nakamura, C. Monroe, and J. L. O'Brien, "Quantum computers," *Nature* **464**, 45–53 (2010).
- E. Waks, K. Inoue, C. Santori, D. Fattal, J. Vuckovic, G. S. Solomon, and Y. Yamamoto, "Quantum cryptography with a photon turnstile," *Nature* **420**, 762–762 (2002).
- C. H. Bennett and G. Brassard, "Quantum cryptography: Public key distribution and coin tossing," *Proceedings of the IEEE International Conference on Computers Systems and Signal Processing* (IEEE, New York, 1984), pp. 175–179.
- P. Michler, A. Kiraz, C. Becher, W. Schoenfeld, P. Petroff, L. Zhang, E. Hu, and A. Imamoglu, "A quantum dot single-photon turnstile device," *Science* **290**, 2282–2285 (2000).
- F. Liu, A. J. Bash, J. O'Hara, L. M. Martins, C. Philips, R. Coles, B. Royall, E. Clarke, C. Benthams, N. Prtljaga, I. E. Itskevich, L. R. Wilson, M. S. Skolnick, and A. M. Fox, "High purcell factor generation of indistinguishable on-chip single photons," *Nat. Nanotechnol.* **13**, 835–840 (2018).
- D. Englund, D. Fattal, E. Waks, G. Solomon, B. Zhang, T. Nakaoka, Y. Arakawa, Y. Yamamoto, and J. Vuckovic, "Controlling the spontaneous emission rate of single quantum dots in a two-dimensional photonic crystal," *Phys. Rev. Lett.* **95**, 013904 (2005).
- S. Laurent, S. Varoutsis, L. L. Gratiot, A. Lemaitre, I. Sagnes, F. Raineri, A. Levenson, I. Robert-Philip, and I. Abram, "Indistinguishable single photons from a single-quantum dot in a two-dimensional photonic crystal cavity," *Appl. Phys. Lett.* **87**, 163107 (2005).
- A. Muller, E. B. Flagg, M. Metcalfe, J. Lawall, and G. S. Solomon, "Coupling an epitaxial quantum dot to a fiber-based external-mirror microcavity," *Appl. Phys. Lett.* **95**, 173101 (2009).
- A. Schwagmann, S. Kalliakos, D. J. Ellis, I. Farrer, J. P. Griffiths, G. A. Jones, D. A. Ritchie, and A. J. Shields, "In-plane single-photon emission from a L3 cavity coupled to a photonic crystal waveguide," *Opt. Express* **20**, 28614–28624 (2012).
- R. Bose, D. Sridharan, G. Solomon, and E. Waks, "Observation of strong coupling through transmission modification of a cavity-coupled photonic crystal waveguide," *Opt. Express* **19**, 5398–5409 (2011).
- A. Javadi, I. Söllner, M. Arcari, S. L. Hansen, L. Midolo, S. Mahmoodian, G. Kirsanskė, T. Pregolato, E. Lee, J. Song *et al.*, "Single-photon non-linear optics with a quantum dot in a waveguide," *Nat. Commun.* **6**, 1–5 (2015).
- J. Gérard, B. Sermage, B. Gayral, B. Legrand, E. Costard, and V. Thierry-Mieg, "Enhanced spontaneous emission by quantum boxes in a monolithic optical microcavity," *Phys. Rev. Lett.* **81**, 1110 (1998).
- B. Alloing, C. Zinoni, V. Zwiller, L. Li, C. Monat, M. Gobet, G. Buchs, A. Fiore, E. Pelucchi, and E. Kapon, "Growth and characterization of single quantum dots emitting at 1300 nm," *Appl. Phys. Lett.* **86**, 101908 (2005).
- J. Vuckovic, D. Fattal, C. Santori, G. S. Solomon, and Y. Yamamoto, "Enhanced single-photon emission from a quantum dot in a micropost microcavity," *Appl. Phys. Lett.* **82**, 3596–3598 (2003).
- A. Bennett, D. Unitt, P. Atkinson, D. Ritchie, and A. Shields, "High performance single photon sources from photolithographically defined pillar microcavities," *Opt. Express* **13**, 50–55 (2005).
- F. Brossard, X. Xu, D. Williams, M. Hadjipanayi, M. Hugues, M. Hopkinson, X. Wang, and R. Taylor, "Strongly coupled single quantum dot in a photonic crystal waveguide cavity," *Appl. Phys. Lett.* **97**, 111101 (2010).
- J. P. Reithmaier, G. Şek, A. Löffler, C. Hofmann, S. Kuhn, S. Reitzenstein, L. Keldysh, V. Kulakovskii, T. Reinecke, and A. Forchel, "Strong coupling in a single quantum dot-semiconductor microcavity system," *Nature* **432**, 197–200 (2004).
- P. Lodahl, S. Mahmoodian, and S. Stobbe, "Interfacing single photons and single quantum dots with photonic nanostructures," *Rev. Mod. Phys.* **87**, 347 (2015).
- S. A. Lennon, F. S. Brossard, L. P. Nuttall, J. Wu, J. Griffiths, and R. A. Taylor, "Photonic molecules defined by SU-8 photoresist strips on a photonic crystal waveguide," *Opt. Express* **26**, 32332–32345 (2018).
- L. P. Nuttall, F. S. Brossard, S. A. Lennon, B. P. Reid, J. Wu, J. Griffiths, and R. A. Taylor, "Optical fabrication and characterisation of SU-8 disk photonic waveguide heterostructure cavities," *Opt. Express* **25**, 24615–24622 (2017).
- D. Leonard, K. Pond, and P. Petroff, "Critical layer thickness for self-assembled inas islands on gaas," *Phys. Rev. B* **50**, 11687 (1994).
- B.-S. Song, S. Noda, T. Asano, and Y. Akahane, "Ultra-high-q photonic double-heterostructure nanocavity," *Nat. Mater.* **4**, 207–210 (2005).
- S. Tomljenovic-Hanic, C. M. de Sterke, M. J. Steel, B. J. Eggleton, Y. Tanaka, and S. Noda, "High-q cavities in multilayer photonic crystal slabs," *Opt. Express* **15**, 17248–17253 (2007).
- K. H. Lee, A. M. Green, R. A. Taylor, D. N. Sharp, J. Scrimgeour, O. M. Roche, J. H. Na, A. F. Jarjour, A. J. Turberfield, F. S. Brossard *et al.*, "Registration of single quantum dots using cryogenic laser photolithography," *Appl. Physics Lett.* **88**, 193106 (2006).
- F. S. Brossard, V. Pecunia, A. J. Ramsay, J. P. Griffiths, M. Hugues, and H. Sirringhaus, "Inkjet-printed nanocavities on a photonic crystal template," *Adv. Mater.* **29**, 1704425 (2017).
- S. Gardin, F. Bordas, X. Letartre, C. Seassal, A. Rahmani, R. Bozio, and P. Viktorovitch, "Microlasers based on effective index confined slow light modes in photonic crystal waveguides," *Opt. Express* **16**, 6331–6339 (2008).
- E. Clarke and R. Murray, "Optical properties of in (Ga) As/GaAs quantum dots for optoelectronic devices," in *Handbook of Self Assembled Semiconductor Nanostructures for Novel Devices in Photonics and Electronics* (Elsevier, 2008), pp. 84–131.
- G. Solomon, M. Pelton, and Y. Yamamoto, "Single-mode spontaneous emission from a single quantum dot in a three-dimensional microcavity," *Phys. Rev. Lett.* **86**, 3903 (2001).