



Deposited via The University of Sheffield.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/id/eprint/202459/>

Version: Accepted Version

Article:

Fish, K.E., Clarizia, L. and Meegoda, J. (2023) Microplastics in aquatic environments – a review of recent advances. *Journal of Environmental Engineering and Science*, 18 (4). pp. 138-156. ISSN: 1496-2551

<https://doi.org/10.1680/jenes.23.00018>

© 2023 Emerald Publishing Ltd. This is an author-produced version of a paper subsequently published in *Journal of Environmental Engineering and Science*. Uploaded in accordance with the publisher's self-archiving policy.

Reuse

Items deposited in White Rose Research Online are protected by copyright, with all rights reserved unless indicated otherwise. They may be downloaded and/or printed for private study, or other acts as permitted by national copyright laws. The publisher or other rights holders may allow further reproduction and re-use of the full text version. This is indicated by the licence information on the White Rose Research Online record for the item.

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.

Accepted manuscript

As a service to our authors and readers, we are putting peer-reviewed accepted manuscripts (AM) online, in the Ahead of Print section of each journal web page, shortly after acceptance.

Disclaimer

The AM is yet to be copyedited and formatted in journal house style but can still be read and referenced by quoting its unique reference number, the digital object identifier (DOI). Once the AM has been typeset, an ‘uncorrected proof’ PDF will replace the ‘accepted manuscript’ PDF. These formatted articles may still be corrected by the authors. During the Production process, errors may be discovered which could affect the content, and all legal disclaimers that apply to the journal relate to these versions also.

Version of record

The final edited article will be published in PDF and HTML and will contain all author corrections and is considered the version of record. Authors wishing to reference an article published Ahead of Print should quote its DOI. When an issue becomes available, queuing Ahead of Print articles will move to that issue’s Table of Contents. When the article is published in a journal issue, the full reference should be cited in addition to the DOI.

Submitted: 01 March 2023

Published online in ‘accepted manuscript’ format: 12 August 2023

Manuscript title: Microplastics in aquatic environments – a review of recent advances

Authors: Katherine E. Fish¹, Laura Clarizia², Jay Meegoda³

Affiliations: ¹Civil and Structural Engineering, The University of Sheffield, UK. ²Department of Chemical, Materials and Industrial Production Engineering, University of Naples “Federico II”, Naples, Italy. ³Department of Civil and Environmental Engineering, New Jersey Institute of Technology, Newark, NJ, USA.

Corresponding author: Katherine E. Fish, Civil and Structural Engineering, The University of Sheffield, S1 3JD, UK

E-mail: k.fish@sheffield.ac.uk

Abstract

Global production and usage of plastics have skyrocketed to 368 million tons in 2019, resulting in increasing amounts of plastic waste concentrating in our natural and urban ecosystems (especially rivers and oceans), via landfill, incineration, or illegal disposal. As highlighted herein, due to the production and degradation of larger plastics, micro and nano plastics are introduced to these ecosystems, causing detrimental impact to plants and animals, including humans, through accumulation in living systems. Though toxicity or health impact are not clearly established, long term accumulation of microplastics in living systems can lead to impact on health of such systems. Critically, this review explores state-of-the art physical, chemical, and biological methods to remove and destroy new and legacy microplastics in aquatic ecosystems (natural and urban). Currently, there are no standardised, accepted, and cost-effective methods for complete removal of microplastics from these aquatic ecosystems. Gaps in knowledge and recommendations for future research to help inform practice and legislation are highlighted. A key consideration highlighted through the review is that microplastics cycle through ecosystems – natural and engineered, these do not operate in siloes and waste from treatment processes could be a conduit for (unintended) recontamination of microplastics. Hence there is a need to take a whole systems approach when developing innovative removal or destructive solutions and, ultimately, reducing plastic use remains the best option to best safeguard future environmental and public health.

Introduction

Since the pioneering synthesis of polystyrene in 1839 to the present day, plastics have undergone a phenomenal transformation. Substantial advances in plastic properties and diversification (Alimba and Faggio, 2019; Chen and Patel, 2012; Kroon *et al.*, 2016) have led to a dramatic increase in the world production of plastics from 1.5 million tonnes in 1950 to a staggering 368 million tonnes in 2019 (Alimba and Faggio, 2019; Plastics Europe, 2020). Plastics deliver many benefits and production is expected to double in the coming decades as plastics continue to diversify (MacArthur *et al.*, 2016). However, with this explosion of plastic production and use comes a growing environmental concern: waste plastic pollution.

The construction, building, and packaging industries are the biggest consumers of plastic, with polypropylene (PP), polyethylene (PE), and polyvinyl chloride (PVC) being the most widely used products (Plastics Europe, 2020). Plastic use in these industries is anticipated to continue to increase in coming decades and additives used in plastic manufacture to obtain specific physicochemical properties (e.g.: anti-oxidising and anti-ageing) can include hazardous chemicals, adding complexity to plastic pollution. Often plastics are only cycled through the economy for a short period of time before most (95%) of their value is lost (MacArthur *et al.*, 2016). Local and global initiatives are in place to improve collection and recovery infrastructure (incorporating circular economic principles into the plastics sector) but leakage of plastic remains a significant challenge (Hettiarachchi and Meegoda, 2023).

Plastics that evade collection/recycle systems can accumulate in critical natural ecosystems and urban infrastructure, resulting in substantial environmental and economic costs.

For instance, despite having advanced collection systems, 170,000 tonnes of plastics still escape into the ocean each year in the United States and Europe (Jambeck et al, 2015). Therefore, in addition to preventing unintended plastic disposal, there is a need for innovative solutions to remove or degrade plastics in a biologically benign way when they unintentionally enter the environment. Currently available biodegradable plastics do not truly address this; they often only decompose under controlled conditions (i.e. industrial composting) and additive-mediated fragmentation techniques (e.g. oxo-fragmentation) often lead to fragmentation and the creation of additional microplastics in our oceans (MacArthur et al, 2016).

Plastic debris may exist in various shapes and morphologies including fragments, fibres, pellets, beads, films, which significantly affect their environmental fate (Li *et al.*, 2020). Based on their average size, plastics can be divided into macroplastics (>25 mm), mesoplastics (5-25 mm), microplastics (<5 mm), and nanoplastics (<0.1 μm) (Boyle and Örmeci, 2020).

Microplastics (MPs) and nanoplastics (NPs) have become pervasive in our environments due to anthropogenic activities, wind action, flowing rivers, and ocean currents. Microplastics are emerging as micro-pollutants that pose adverse health effects to aquatic life. Their persistence and ability to adsorb organic pollutants from water results in transportation and bioaccumulation of pollutants in aquatic environments (Bandow et al, 2017). Low trophic level animals and other organisms can ingest MPs and NPs, leading to irreversible accumulative damages to the food chain, where over 690 marine species have already encountered plastic debris (Burgess and Ho, 2017). Additionally, when MPs and NPs are degraded (physically or

chemically) the adsorbed organic pollutants are released back into the environment resulting in unexpected mixtures of persistent organic contaminants even in pristine environments (Bandow *et al.*, 2017). Hence MPs and NPs present both direct and indirect environmental risks, a major concern for environmentalists and policymakers alike (Meegoda and Hettiarachchi, 2023).

Legislation to control plastic contamination is being developed, in response to the growing threat of plastic pollution. The United States passed the Microbead-Free Waters Act (MFWA) in 2015, prohibiting the manufacture, packaging, and distribution of cosmetics containing plastic microbeads. The EU has also taken steps to address MPs, requesting the European Chemical Agency (ECHA) to evaluate regulatory actions throughout the region. In 2019, ECHA proposed an extensive restriction on “*microplastics in products placed on the EU/EEA (European Union/ European Economic Area) market to avoid or reduce their release to the environment,*” essentially banning the addition of MPs to products such as cleansers, cosmetics, fertilizers, and others (Metzler and Simbeck, 2022). However, these are just some of the sources of MPs and such legislation is only addressing the release/leakage of new MPs into the environment. Management of the legacy MPs and NPs already within our natural and urban aquatic environments is critical and requires innovative removal and destruction approaches. Consequently, this review aims to: (i) critically evaluate the state-of-the art of currently available engineered separation and degradation technologies, (ii) outline current gaps in knowledge, and (iii) suggest useful recommendations for further advances in removal of MP and NP from aquatic environments (including freshwater, seawater, drinking and

wastewater).

Sources and occurrence of microplastics in aquatic environments

Whilst MPs are present in different media, they are most abundant in aquatic ecosystems, particularly oceans due to the large body of water. MPs may be introduced into the environment from diverse sources, with specific plastic types having different origins. For instance, PE, PP, and polystyrene (PS) are produced from typical plastic products (e.g. plastic cutlery), polyamide (PA) and polyethylene terephthalate (PET) originate from the textile industry. Polyethersulfone (PES) is produced when tires and plastic particles in roads are crushed or fragmented (Liu *et al.*, 2021). Sources are typically classed as primary (where MPs are directly discharged into the environment) or secondary (where bigger particles fragment and degrade into micro-particles in the environment (Yusuf *et al.*, 2022). Understanding sources and the contamination route is important to mitigate exposure and manage plastic pollution in aquatic systems.

Freshwater (rivers, lakes, reservoirs, groundwater) is the main source of raw water for agriculture, industry, energy production, and human consumption, but in areas where freshwater is scarce, seawater may be used. These sources are vulnerable to MP contamination from agricultural and industrial activities, as well as animal farming discharges (Shen *et al.*, 2020) within the context of drinking water. The abundance of microplastics in freshwater environments varies greatly (from several to millions of tons) due to location, natural conditions, anthropogenic factors and the use of different quantification methods.

Primary sources

Plastics that are manufactured to be of a microscopic size for commercial use are defined as primary MPs. These plastics are typically used in facial-cleansers and cosmetics, while their use in medicine as vectors for drugs is also reported. In addition, the textile industry is a significant source of primary MPs in aquatic systems, with microfibers released through physical agitation in washing machines, contaminating the environment through sewage systems, or settling on the surface of water bodies after being released to the air (Zhang *et al.*, 2021). Similarly, resin powder and pellets, discharged to air during the manufacturing of plastic, have been reported to settle in oceans (Yusuf *et al.*, 2022). Mortula *et al.*, 2021 demonstrated that many plastic materials found in landfills can leach primary MPs, especially polycarbonate (PC), possibly contaminating the groundwater. Manufactured MPs have even been detected in the influent of some drinking water treatment plants (DWTP). One study has shown that whilst the raw water sample from DWTP contained low concentrations of MPs, household drinking water contained greater concentrations, suggesting that the drinking water treatment or distribution systems (DWDS) may be sources of MPs contamination (Shen *et al.*, 2020).

Secondary sources and conduits

Secondary MPs are formed through the (unintentional) fragmentation of larger plastic particles. Secondary MPs may enter surface water environments through wastewater discharges, decomposition of plastic waste in the environment, abrasions of plastic products, and atmospheric deposition. This can occur when plastic products are manually crushed, subjected

to mechanical agitation or UV light, or chemical processes such as oxidation, causing degradation into smaller particles.

Drinking water is treated to a high standard and many MPs are removed, but wastewater treatment plants (WWTP) are reported as a major conduit of MPs in seawater and aquatic environments (Liu *et al.*, 2021; Murphy *et al.*, 2016). MPs in WWTP originate from sources such as textile microfibers, tire dust from roads, paint, microbeads in cosmetics and exfoliants (Yusuf *et al.*, 2022; Zhang *et al.*, 2021). Treatment in WWTP do not entirely remove MPs from the effluent and can cause degradation of MPs into smaller particles, which are then harder to remove during downstream treatment. For instance, Liu *et al.* (2021) reported that the proportion of smaller particles in the effluent of WWTPs (81%-91%) was higher than that of the influent (65.0-86.9%). Conversely, MP removal has been reported to increase from 75% to 91.9% and >98% across the primary, secondary and tertiary (coagulation, ozonation, sand filters) stages of wastewater treatment. Despite this, the concentrations of MPs released into the environment could be substantial; for instance, Bayo *et al.*, 2020 reported wastewater treatment effluent ranges from 5900 MPs/m³ to 3000 MPs/m³. Murphy *et al.*, 2016 studied a UK wastewater treatment plant and showed that MP removal efficiency exceeded 98%, yet despite this high efficiency the effluent still released 65 million MPs into the receiving water body. Additionally, a significant proportion of MPs may remain in sludge (and other waste products from waste and drinking water treatment plants). Sludge is often disposed on land and return MPs to the natural environment (Zhang *et al.*, 2020a), including aquatic bodies where they remain in high concentrations. Indeed, MPs in soil ecosystems can be traced back to

wastewater treatment plants (sewage sludge), as well as solid waste (leaching from landfills) and organic fertilizers (Zhang et al, 2021).

MP loads could increase throughout the drinking water system if the treatment, distribution and point-of-use infrastructure (which includes various plastic components) act as sources of MPs (Ding *et al.*, 2021; Shruti *et. al.*, 2020). For instance, Ding *et al.*, 2021 demonstrated that membrane filters were effective in removing MPs but those same organic membranes can be a source of MPs/NPs. No whole-system evaluation has been undertaken to determine the contributions of different water system components to MP loading of drinking water.

In summary, MP contamination of aquatic environments can occur from the synthetic MPs as well as use and disposal of plastics. Hence there is a need to better understand the consequences of the potential return conduit on MP accumulation in soils, watercourses and produce from land animals, which present other exposure pathways.

Exposure and toxicity of microplastics in aquatic environments

MPs have become a major environmental concern due to their persistence in the environment and the potential harm they can cause to organisms. Health risks from MPs in any environment may stem from physical, chemical or microbiological characteristics or behavior of particles. While several studies have investigated the chronic toxicity of MPs, but there is limited information on their acute fatal effects (Li *et al.*, 2018). Evidence on the exact implications is lacking in part due to difficulty in assessing long-term exposure and compounding effects, in combination with the diverse and complex blend of chemicals that comprise MPs and NPs.

Toxicity of MPs and NPs depends on their chemical structure and additives used, such as polymerization linkage (Sussarellu *et al.*, 2016). Polystyrene MPs in particular can accumulate in blood and are recognized as causing reproductive disruption in marine filter feeders (Law *et al.*, 2014). Critically, most MPs and NPs are resistant to bio-/photo- degradation in the natural environment, making them a growing environmental threat.

Direct exposure of MPs

Studies on MP toxicity have mainly focused on their ecotoxicological impacts in natural environments, with little attention given to engineered ecosystems such as drinking water treatment and distribution systems. Risk is dependent upon toxicity and exposure; if drinking water is contaminated it has the potential to impact vast numbers of people. However, drinking water is of low risk to public health within the context of MPs (WHO, 2019) and the main source of MP human intake (12K – 204K MPs per person per annum) is reported as being from food (Kirstein *et al.*, 2021). MPs have been detected in a drinking water supply from source water to end point of use (Koelmans *et al.*, 2019; Li *et al.*, 2018) but most studies have focused on MPs in freshwater sources used as influent for drinking water treatment. Koelmans *et al.*, 2021 and Kirstein *et al.*, 2019 found just 9 and 26 studies respectively, on MPs specifically in drinking water. The characteristics of MPs in drinking water systems are still debated, but fragments and fibers are reported as the dominant particle types (WHO, 2019) and concentrations are typically low based on the available evidence. For instance, the following concentrations were reported: 0.06 ± 0.04 MPs/L from a Spanish drinking water system (Dalmau-Soler *et al.*, 2021), 0-8 MPs/m³ in a study of a Swiss system (Negrete Velasco *et al.*, 2022) and <0.5 MPs/L in

potable water from a study of eight treatment works in England and Wales (Johnson *et al.*, 2020). It should be noted that quantification of MPs in freshwater systems is still primarily based on modelling with little empirical evidence.

Inconsistencies in studies of exposure to MPs from aquatic environments exist due to differences in sampling, isolating, and analysis methods (Koelmans *et al.*, 2019; Kirstein *et al.*, 2021; Oßmann, 2021) or unreliable data (Koelmans *et al.*, 2019). Koelmans *et al.*, 2019 proposed an assessment of quality across 50 studies of MPs in water sources, from which only four received a positive score with respect to quality assurance of sampling and analysis of MPs. Hence, there is a need for standardized methods before conclusions on MP toxicity and exposure as a consequence of water source, treatment and quality can be justified.

The daily intake of MPs in mineral water was estimated to be 40.1 $\mu\text{g}/\text{kg}/\text{bodyweight}/\text{day}$ and 87.8 $\mu\text{g}/\text{kg}/\text{bodyweight}/\text{day}$ for adults and children, respectively (Zuccarello *et al.*, 2019) and MPs have been detected in various human tissues (Wang *et al.*, 2019), with their adverse effects on human health increasingly recognized. The impacts of MPs on water quality and public health are not well studied. The greatest health risk is perhaps most likely from the smaller NPs than MPs because they can escape water treatment (Li *et al.*, 2021).

Indirect exposure of MPs

MPs may indirectly impact water safety by acting as “transport systems” for microorganisms (including potential pathogens) or other pollutant (Ateia *et al.*, 2020). Biofilm formation in some freshwater studies has illustrated the potential for MPs to act as a transport system of

pathogens, possibly increasing transfer of antimicrobial resistant genes. Whilst there is currently no evidence to suggest that the same would occur within operational drinking water systems, bench-top studies of stagnant drinking water bottles have shown to form biofilms on MPs (Chen *et al.*, 2021). Recent studies have shown that microbial communities associated with microplastics in river (Wang *et al.*, 2020a), estuary and marine waters (Wang *et al.*, 2019; Wang *et al.*, 2020b; Li. *et al.*, 2022) and have a greater occurrence of opportunistic pathogens, antibiotic resistance genes and metal resistance genes. However, Li, *et al.*, 2022 concluded that the structure of bacterial community on MPs within 1L bottles of filtered river water (used as a drinking water source) was determined by the bulk-water quality rather than MP characteristics.

MPs may also release toxic chemicals into water (e.g., phthalates, hydrocarbons, heavy metals) (Cheng *et al.*, 2020) and can be a source of organic carbon (Chen *et al.*, 2021; Lee *et al.*, 2020), impacting water quality by increasing bacterial growth and reducing biostability (Chen *et al.*, 2021). Additionally, leaching of plastic-associated carbon in bench-top beaker tests has been shown to increase disinfection by-products (Ateia *et al.*, 2020), which are potential carcinogens. MPs have also been shown to impact microbial growth and microbiome composition on ultrafiltration membranes used in drinking water treatment (Xiong *et al.*, 2022).

It is possible that MPs not removed from drinking water by upstream treatment processes (or that contaminate in the distribution system, post-treatment) could be reservoirs and vectors of microbial contaminants. The bench top tests are substantially different from the scale of

operational systems and do not replicate all the physical, chemical and microbiological interactions that occur within real systems. Consequently, the impact or risk that such MP-associated processes would contribute to water quality degradation would likely be insignificant compared to the microbial accumulation and mobilization of biofilms that form on the vast internal surface areas of drinking water infrastructure.

Microplastic removal/destruction from water

MPs cycle through our environments, current and emerging removal methods include physical (coagulation and flocculation methods, electro-sorption, membrane technologies), chemical and biological treatments (as summarized in Figure 1). With respect to water treatment, large size plastics are expected to be removed by screen mesh (6 mm size) and grit processes and MPs largely removed during the sedimentation, activated sludge, membrane bioreactor or sand filtration processes (Bayo *et al.*, 2020; Talvitie *et al.*, 2015). Talvitie *et al.*, 2015 showed that treatment had a significantly higher fiber removal efficiency (92%), than secondary treatment (0.2%) which did have a substantial removal rate of synthetic particles (52%). WHO (2019), highlights that the greatest risk to freshwater and drinking water from MPs is most likely where water treatment is unavailable - 67% of low/middle income countries lack sewage connections and 20% of household wastewater is not treated by at least secondary level treatment. Whilst MP contamination does not present the greatest drive for improving water treatment and safe distribution, achieving this will simultaneously improve MP and NP removal.

Physical methods of MP removal from water

Coagulation and flocculation methods

Drinking water treatment plants (DWTP) use coagulation, flocculation, and sedimentation (CFS) to enlarge particles, improving filtration. Inorganic and organic coagulants used in CFS can bind MPs to waste particles facilitating their removal. CFS has proved effective in removing detectable microplastic in aquatic environments (Li *et al.*, 2022, Rajala *et al.*, 2020, Li *et al.*, 2021). Table 1 show that the based-on laboratory-scale studies CFS methods are effective in removing MPs. The exact removal efficiency depends on several factors, including coagulant type and dose, water sample characteristics and MP properties (Table 1).

Several studies have investigated effectiveness of different coagulants and their optimal doses for MP removal. The properties of MPs, particularly their size, have been found to impact removal efficiency. In laboratory studies using alum and polyaluminum chloride (PAC) have shown the effectiveness of removing MPs from water, with aluminum chloride more effective than iron chloride for MPs of size 10-90 μm where the optimal dose reported was 10 mg/L at a pH of 6 (Na *et al.*, 2021) and higher alum doses improved removal of MPs <90 μm (Xue *et al.*, 2021). For removal of smaller MPs from municipal wastewater, iron chloride showed a greater removal efficiency than PAC and polyamine (Rajala *et al.*, 2020). The use of PAC in combination with polyamine-coated sand was found to be effective in removing more MPs than PAC alone, with an optimal alum dose of 20 mg/L and 92.7% of MP particles removed (Shahi *et al.*, 2020). Magnetic magnesium hydroxide (MMHC) has been investigated as a coagulant for the removal of MPs from wastewater, and Mg to OH ratio of 1:1 was found to be

ideal for preparing the most effective MMHC (Zhang *et al.*, 2021). The highest removal efficiency was obtained at a pH range of 5-9 with 93.8% of MPs removed using 200 mg/L of magnesium hydroxide, 120 mg/L of iron oxide, and 5 mg/L of polyacrylamide (PAM). Whilst the coagulant type clearly impacts MP removal, the combination of coagulant(s) used are also important. Interactions between these need to be better characterized to obtain optimum chemical coagulant and the operation conditions for most efficient MP removal.

Water characteristics also impact the removal efficiency of MPs, particularly the pH, which influences the floc characteristics through hydrolysis of the coagulant. The optimal pH for the removal of MPs has been reported as 6-8 depending on the coagulant used (Zhang *et al.* 2021; Rajala *et al.*, 2020). Xue *et al.*, 2021 showed that the removal efficiency of carboxylated MPs (simulating those found in aquatic systems) using CFS and found higher removal in water samples collected from Lake Erie water than those from Grand River, possibly due to the higher turbidity of Lake Erie promoting flocculation. In water samples from both locations CFS was effective in removing MPs, with the addition of alum removing more MPs of 45-90 μm (removal of MPs $\leq 25 \mu\text{m}$ was unimpacted). These studies demonstrate the need for research to better understand the interactions between physical and chemical characteristics of water and coagulant agents in order to develop best practice for MP removal depending on the matrix of polluted water.

Size of MPs has been extensively studied but the existing literature rarely describes the impact of shape of MP on removal efficiency. Shahi *et al.*, 2020 found that MP removal efficiency in treatment plants is also influenced by shape and surface morphology. Elongated

MPs and those with rougher surfaces were removed more efficiently than spherical MPs or those with smoother surfaces. Elongated smooth MPs were easily removed when compared to spherical rough MPs. These findings suggest that there is a need for further research on the effect of MP characteristics on their removal from DWTPs.

Chemical methods of MP removal from water

Electrochemical methods for microplastics removal

Electrolysis degrades or separates MPs from the wastewater through sorption using an electrolyte. Several studies have demonstrated promising potential to use a range of electrolysis-based methods for MP removal from wastewater. Perren *et al.*, 2018 investigated the effectiveness of electrocoagulation (EC) for removing MPs from wastewater. Perren *et al.*, 2018 found that 90% removal efficiency of MPs under optimal pH of 7.5, NaCl concentration of 2 g/L, and current intensity of 11 A/m². Shen *et al.*, 2022 studied various factors and determined that an electrolyte concentration of 0.05 M, pH of 7.2, and applied voltage of 10V resulted in an MP removal efficiency of 91.7%. Fiber MPs and Al anode were preferred to granular MPs and Fe anode, respectively. Xu *et al.*, 2022 used interpenetrating bipolar plate EC to remove mixed pollutants of MPs and heavy metals from wastewater, achieving a high removal efficiency of around 96%. These studies demonstrate that EC is a clean technology capable of reducing the potential harm of MPs and heavy metals to aquatic organisms.

Electro-sorption (ES) is another potential-induced adsorption on the surface of charged electrodes. Following polarization of the electrodes, ions are removed from the electrolyte solution by the imposed electric field and adsorbed onto the surface of the electrodes. Xiong *et*

al., 2020 investigated the efficiency of ES process in treating water contaminated with MPs. The capacity was found to be 0.707 g nano-polystyrene/g AC (70.7 %). This suggested that electro-sorption to be a feasible tertiary treatment method of water contaminated with MPs. Moreover, the laboratory scale study conducted by Mantel *et al.*, 2021 demonstrated high efficiency of removal of MPs using ES. Similarly, electro-oxidation (EO) offers another established electrochemical treatment method; the chief reagent used is an electron, which eliminates the organic matter present in the electrolyte. Developed along similar lines as EC, EO is anodic oxidation on the anode surface that is employed in place of direct chemical oxidation. Its an alternative variation and involves only the generation of an oxidizing species using the chemical pathway being accompanied by direct oxidation of generated oxidizing agents. Critical parameters for EO efficiency include design of electrochemical cell, selection of electrodes, operational parameters and cost of power. A study by Kiendrebeogo *et al.*, 2021 focused on the degradation of synthetic suspension of polystyrene microbeads (26 μm in size). The study employed EO and found that the process can degrade $58 \pm 21\%$ of MPs in one hour. Furthermore, current intensity, anode material, electrolyte type and electrolyte concentration are functions of MPs removal efficiency. It was also discovered that MPs did not break into smaller particles but were degraded directly into gaseous products. This suggests that EO is a safe process for degrading MPs in wastewater. As a credit to EO, other electrochemical methods like EC and ES cannot confirm the long-term sustainability due to the formation of secondary MPs. EO ensures complete MPs mineralization by breaking down olefin chains of MPs through generating oxidizing radicals. Eventually, less harmful products (H_2O and CO_2)

are produced (Ranade and Bhandari, 2014).

Membrane Technologies for microplastics removal

Advanced membrane technologies during tertiary treatment can achieve reduction of microplastics in wastewater. Talvitie *et al.*, 2017 investigated the removal of MPs from effluent in WWTP using different advanced treatment technologies including disc filters, sand filters, dissolved air floatation and membrane bioreactor (MBR). The MBR removed 99.9% of MPs during the treatment (from 6.9 to 0.005 MP L⁻¹), rapid sand filter 97% (from 0.7 to 0.02 MP L⁻¹), dissolved air flotation 95% (from 2.0 to 0.1 MP L⁻¹) and disc filter 40–98.5% (from 0.5 – 2.0 to 0.03–0.3 MP L⁻¹) of the MPs during the treatment. Similar findings were reported using a pilot-scale MBR that removed 98.4% of MPs compared to the conventional activated sludge process (Lares *et al.*, 2018).

Removal efficiency of MPs from wastewater treatment plants is also high when advanced filtration methods are employed. Drinking water treatment works are engineered to produce high quality water, part of this includes the output of low turbidity water, which requires the removal of particles that are similar to, or smaller than, MPs in their physiology (size, density) and detected in far higher concentrations. Dalmau-Soler *et al.*, 2021 demonstrated that for PS and PP dominated intake water in drinking water treatment plant MP removal efficiency was 93%, with sand filtration as a critical MP removal stage (78% efficiency). Similarly, Negrete Velasco *et al.*, 2022 reported a decrease in MPs within a pilot drinking water treatment station from 19.5-143.55 MPs/m³ in raw water to 0.0-8.0 MPs/m³ in drinking water, although this study stressed the importance of coagulation in removing MPs (89% and 97% removal

efficiency without and with coagulant, respectively). The low MP concentrations reported in drinking water (Dalmau-Soler *et al.*, 2021; Negrete Velasco *et al.*, 2022; Johnson *et al.*, 2020) are indicative that current treatment processes are effective at removing MPs from drinking water.

Dynamic membrane (DM) filtration is an emerging technology in the WWTP based on the formation of a cake layer (secondary membrane) formed during the filtration of wastewater through the supporting membrane (Ma *et al.*, 2013). Li *et al.*, 2021 used DM and reduced the effluent turbidity to < 1 NTU (Nephelometric Turbidity Unit) after 20 minutes of filtration an indicator of the effectiveness of the approach. The DM performance was shown by the correlation between the transmembrane pressure and total filtration resistance increasing linearly with filtration time, important considerations to ensure are included in operational practice guidance.

Reverse osmosis is also an advanced system used to water using nanofiltration membranes under high pressure (10-100 bar). It is used in municipal water treatment to recover wastewater by applying high pressure to a concentrated solution forcing the water through a semipermeable membrane leaving all the salts, pollutants and heavy metals in the concentrated solution (Ashfaq *et al.*, 2019). Cai *et al.*, 2019 used an integrated membrane system (IMS) in a coastal reclaimed water plant to remove microplastics. The removal rate of microplastics in the IMS system was 93.2% after membrane bioreactor (MBR) treatment while that further increased to 98.0% after the reverse osmosis (RO). However, a breakthrough for small scale fibres (< 200 μm) was measured in the RO system. Many microplastics (< 10 μm) were still

measured in the WWTP effluent with polyethylene (PE) the most common polymer identified.

Advanced oxidation for microplastics removal

Advanced oxidation processes (AOPs) for chemical degradation of contaminants were introduced in the 1980s (Kim *et al.*, 2022). Advanced oxidation processes (AOPs) are oxidative methods based on the generation of reactive oxygen species (ROS) have been successfully applied for decomposition of different refractory contaminants in the environment. The fact that AOPs could effectively degrade a wide spectrum of pollutants prompted researchers to investigate several AOPs for decomposition of microplastics (MPs). These include ozone, UV photolysis, UV/H₂O₂, UV induced photo-catalysis, Fenton process, photo-Fenton process, and persulfate (PS) treatment. AOPs relies on the formation of reactive oxygen species (ROS) by employing light, plasma, heat, and catalysts. Due to their high redox potentials, the formed radical species (e.g., hydroxyl radicals, 1.89–2.72 V) can attack and degrade several refractory pollutants or at least increase their biodegradation before biological treatment stages. Recently, several studies dealing with the treatment of MPs by AOPs such as ozone, heat/persulfate, UV photolysis, UV/H₂O₂, UV/catalysts, and plasma have been reported (Kim *et al.*, 2022), highlighting the potential options for consideration at full-scale.

Ozone (O₃) is a strong oxidant extensively investigated within AOPs (Kim *et al.*, 2022). Ozone can irreversibly impair the physico-chemical properties of MPs and NPs. Zafar *et al.*, 2021 studied the PE degradation by ozone. PE breakdown was carried out by varying the ozone dosages in the range 4–7 mg/min for 60 min, 120 min and 180 min. Hydroxyl index (HI) and carbonyl index (CI) were recorded throughout the experiments to evaluate MPs

degradation. CI and HI values increased with increasing ozone dosage and reaction time suggesting an enhanced oxidation. Hidayaturahman and Lee, 2019 combined the use of ozone with established wastewater treatment for MPs degradation. Nearly 99% MPs were removed when sequentially applying O₃ treatment and coagulation, indicating the importance of employing multi-step treatment and potentially the specific sequence of those steps which could improve removal.

Persulfate (PS, S₂O₈²⁻) maybe thermally activated to produce sulfate radicals (SO₄^{•-}) for destroying refractory contaminants. Liu *et al.*, 2022 investigated polystyrene and PE MPS degradation through heat-activated PS. Significant changes in physico-chemical properties of PE and polystyrene were observed. In particular, CI and surface roughness increased with increasing the reaction time. On the other hand, average particle size decreased due to MPs breakdown of polystyrene and PE during the experiments. Moreover, several functional groups were formed on the surface of the polystyrene and PE MPs, thus resulting in increased hydrophilicity and O/C ratios. This important change in surface morphology led to enhanced adsorption capacities of MPs subject to ageing in natural environments. Therefore, aged MPs may adsorb hazardous pollutants and cause irreversible effects to ecosystems. Wang *et al.*, 2017 and Ding *et al.*, 2022 reported that peroxymonosulfate (PMS) treatment could provide insight into the ageing of MPs. The active oxidizing agents produced in AOPs are typically free radicals like HO• for Fenton and SO₄• for PS (Jiang *et al.*, 2021). Furthermore, Fenton and persulfate (PS) treatment could provide insight into the aging of MPs (Wang *et al.*, 2017; Ding *et al.*, 2022). Another promising method, the photo-Fenton process has been discussed by

Ricardo *et al.*, 2021 to be effective in MP degradation. Kida *et al.*, 2019 employed the photo-Fenton process to remove a recalcitrant fertilizer. The modification entails iron (II) being replaced by iron (III) as well as improving the process using a chelating agent.

Due to light irradiation, reactive species are formed during UV photolysis (e.g., $\cdot\text{OH}$, $^3\text{OM}\cdot$, $\text{O}_2^{\cdot-}$, $\text{ROO}\cdot$) and may decompose several refractory pollutants (Stefan, 2017). Suhroff and Scholz-Böttcher, 2016 reported that UV oxidation could alter physicochemical properties of plastics. The possibility of employing natural sunlight irradiation represents a great potential advantage of photolytic treatments of plastics in the environment. According to Suhroff and Scholz-Böttcher, 2016 UV irradiation could affect physico-chemical features of polyvinylchloride (PVC), polyethylene (PE), polystyrene, and polyethylene terephthalate (PET), thus leading to their degradation according to complex reaction pathways. At the end of the photolytic treatment, the samples were broken into nanometers and micrometers sizes. Further studies recoded plastics degradation by UV photolysis under wavelengths of 200–280 nm (UV-C), 280–315 nm (UV-B) and 315–400 nm (UV-A) (Kim *et al.*, 2022). The UV method is a potent method but for considerable impact high energy content is desired.

The use of $\cdot\text{OH}$, UV/H₂O₂ has also been extensively investigated in AOPs. Liu *et al.*, 2021 showed UV/H₂O₂ treatment induced irreversible physico-chemical changes to polystyrene, including modification of surface morphology, CI, crystallinity, hydrophobicity and embrittlement. In particular, $\cdot\text{OH}$ oxidation led to an increase in surface roughness, CI, crystallinity, and embrittlement increased due to chemical oxidation by $\cdot\text{OH}$. On the other hand, the formation of various surface functional groups and chain scission reactions resulted

in decreased hydrophobicity and average molecular weight. The combination of UV/H₂O₂ can substantially improve the destruction of MPs.

Fadli *et al.*, 2021 employed UV/photocatalysis with TiO₂ photocatalyst doped with Ag or Ag and reduced graphene oxide (RGO) to enhance PE MP removal by reducing electron-hole recombination on the TiO₂ surface. PE particles with an average size of 100–150 µm were employed for the photocatalytic tests. Nearly 76% PE was decomposed with 3% Ag/TiO₂-1% RGO photocatalyst after 4 h of UV illumination. However, as UV radiations accounts for only 5% of the solar spectrum, visible light-activated photocatalytic processes for MPs and NPs should be extensively investigated. In this regard, Pt-ZnO nanorods were employed by Tofa *et al.*, 2019 to oxidize under visible light low-density PE with a thickness of 50 µm. Pt deposition on ZnO markedly enhanced the visible light absorption of the photocatalyst. Increased surface oxidation of LDPE, CI and vinyl index were recorded during the photocatalytic experiments over time. In addition, SEM analysis revealed cavities and cracks on the LDPE surface. Nabi *et al.*, 2020) successfully employed activated titanium dioxide (TiO₂) film to generate ROS such as OH• and O₂•- to decompose PE and polystyrene under UV illumination. Faldi *et al.*, 2021 used a similar approach. However, they modified TiO₂ using Ag and reduced graphene oxide (RGO) to improve the results. Hence the UV treatment can be enhanced by photocatalysis.

Free electron rich plasma may generate reactive oxygen species (ROS) and O₃ from O₂ and air with potential application for the degradation of MPs in water. Electrical discharge plasma was employed by Zhou *et al.*, 2020 for decomposing PVC MPs. Various functional

groups were detected on the surface of MPs. In addition, surface area, CI, hydrophilicity, crystallinity, and increased. On the other hand, plasma treatment lowered MPs sizes. However, plasma method is an emerging method for destruction of emerging contaminants.

Advanced oxidation processes (AOPs) are effective methods of decomposing pollutants, including microplastics (MPs). AOPs generate reactive oxygen species (ROS) through light, plasma, heat, and catalysts, which attack and degrade pollutants with high redox potentials. AOPs, including ozone, UV photolysis, UV/H₂O₂, UV-induced photocatalysis, Fenton process, photo-Fenton process, and persulfate (PS) treatment, have been reported to effectively degrade MPs. Ozone irreversibly impairs the physico-chemical properties of MPs and NPs, while PS, thermally activated to produce sulfate radicals (SO₄•⁻), can break down refractory contaminants. Reactive species are also formed during UV photolysis, and natural sunlight irradiation is an advantage of photolytic treatments of plastics. The use of UV/H₂O₂ induces irreversible physico-chemical changes in MPs, while UV/photocatalysis with TiO₂ photocatalyst doped with Ag or Ag and reduced graphene oxide (RGO) enhances PE MPs removal. Overall, AOPs will soon have a crucial role in green and sustainable MPs removal in the environment. However, considerable research efforts should be made for complete removal of MPs by employing AOPs. Bench-scale technologies for MPs and NPs removal based on AOPs should be optimized at a large scale with the aim of developing industrial implementation.

Biological methods (biodegradation) for microplastics removal

Biological methods for micro and nano plastics (MNPs) removal from ecosystems remain

increasingly attractive research. These technologies are not only well known due to their low-cost, eco-friendly performance, but also by the capacity of providing in-site and ex-site remediation. Biotechnology to remove MNPs includes complex processes, such as biotransformation, biodegradation, biofilm formation, biosorption, etc. Different microbes have different interactions with MP in the MNP removal. Many researchers are searching for possible solutions for the removal of MPs with different biological organisms. Since biological organisms are sensitive to several factors, such methods require more effort and research for efficient implementations on a larger scale (Badola *et al.* 2022).

Microplastics remain longer in the environment and in food chain because of their low degradability, persistent and cumulative nature (Wahyuningtyas *et al.*, 2017; Urbanek *et al.*, 2017), posing a major risk to human health (Tachibana *et al.*, 2013; Harmaen *et al.*, 2015; Calabrò, and Grosso, 2018 and Suzuki *et al.*, 2018). Also, microplastics have large surface areas and adsorption capacities. This makes them prone to sorb thereby accruing harmful and toxic waterborne pollutants which they usually transport and desorb into new habitats (Rios *et al.*, 2007; Mohsen *et al.*, 2020). Microplastics are quickly colonized by microorganisms such as fungi and bacteria as soon as they are released to the environment (Delacuvellerie *et al.*, 2019; De Tender *et al.*, 2017). This is because, microplastics surfaces provide aquatic and terrestrial microhabitat that support the growth of unique and distinctively different microbial communities (De Tender *et al.*, 2015; Amaral-Zettler *et al.*, 2015; Oberbeckmann *et al.*, 2014; Wu *et al.*, 2019). Certainly, many microorganisms have evolved strategies to survive on the microplastic laden environment where they break them down enzymatically and utilize them as

source of energy (Zeenat *et al.*, 2021).

Biological methods used to eradicate microplastics from the environment, make use of microorganisms and their hydrolytic and proteolytic enzymes with ability to biodegrade various types of microplastics (Pathak, 2017; Danso *et al.*, 2019; Peng *et al.*, 2022). Biodegradation is a process by which plastic debris are reduced into metabolizable harmless products through the aid of microbial digestion (Pathak, 2017). The biodegradation of plastic materials can be influenced by the microorganism species involved, sources of carbon, size, and types of plastic materials (Allouzi *et al.*, 2021). The factors of degradation are categorized into two main groups: biotic and abiotic. Biotic factors refer to microbial growth rate, enzyme activity, culturing feasibility, etc. Abiotic factors include MNPs structure, morphologic surface, functional groups, pH, temperature, level of electronic acceptors such as oxygen, etc. Both aerobic and anaerobic methods can be applied.

Microplastics are mostly made up of non-hydrolysable, hydrophobic and chemically inert groups. This makes them hard to undergo biodegradation unless they are first weakened by abiotic factors that will have to oxidize them first (Yoon *et al.*, 2012; Temporiti *et al.*, 2022; Hakkarainen M, Albertsson, 2004; Arutchelvi *et al.*, 2008; Bryant *et al.*, 2016). Biodegradation of microplastics is therefore reliant on the physical and chemical properties of the constituent microplastic polymers. Some of these physical properties include hardness and complexity. Polymers that are soft, degrade quickly than hard ones (Corcoran, 2021). Other factors affecting biodegradation include the density and molecular weight of the polymer (Zambrano *et al.*, 2020), hydrophobicity of polymers, which increases available functional groups (Bildik

Dal *et al.*, 2021) together with the nature and type of the bonds where amide and ester bonds break easily (Mahesh *et al.*, 2018). Abiotic factors such as light, oxidative stress, thermal heat, pH, ultraviolet rays, atmospheric humidity, hydrolysis, and oxidation also influence the rate of biodegradation (Teixeira *et al.*, 2021). Microplastics exposed to abiotic factors decrease in strength, flexibility and increase in brittleness (Garrido and Costanzo, 2022). Exposure of microplastics to abiotic factors such UV light, contribute to the initial disintegration of plastic polymers by initiating photo-oxidation (Sen and Raut, 2015; Shah *et al.*, 2007). Photo-oxidation modify plastics physically and chemically leading to weight loss, increased viscosity, bond breaking and molecular weight reduction which together promote biodegradation (Koutny *et al.*, 2006; Da Luz *et al.*, 2015). Therefore, biological methods of removing microplastics, utilize the biodegradation capacity of microbial enzymes from bacteria such as actinomycetes (Gram-positive mycelial bacteria) and fungi (Tamoor *et al.*, 2021; Alshehrei, 2017). For this reason, there are several bacterial, fungal, and algal based methods used bio-remediate the environment of microplastics.

Bacterial-enzymatic processes

The mechanisms of MNPs biodegradation by bacteria remain unclear. However, based on multiple studies of bacterial degradation of plastics, Mohanan *et al.*, 2020 and Tiwari *et al.*, 2020 summarized the biodegradation mechanism by bacteria which includes four stages: (1) biodeterioration of plastic surfaces, conducted by changing the chemical and physical properties of plastics by oxidative enzymes released by bacteria; (2) bio-fragmentation of complex polymer into simpler forms via hydrolysis and release of intermediate products; (3)

bio-assimilation of small fragments generated from the stage 2 by bacteria up take or mineralization; (4) mineralization of metabolites into microbial biomass with associated release of CO₂, CH₄, and water.

Several studies show that suitable bacteria strains aim to selective target micro plastics to degrade the MPs by 6% - 36% from 40 days to 16 weeks under the controlled environmental conditions, such as pH, temperature, salinity, etc., using isolated and cultured pure bacterial strains in the laboratory (Muhonja *et al.*, 2018; Auta *et al.*, 2017; Habib *et al.*, 2020). The advantage of using pure strains in MP degradation studies is that it is a convenient way to investigate metabolic pathways or evaluate the effect of different environmental conditions for MP degradation (Yuan *et al.*, 2020). Park and Kim 2019 isolated mesophilic mixed bacterial from an abandoned landfill and showed efficient degradation of PE. Habib *et al.* (Habib *et al.*, 2020) used the strains from the Antarctic region to degrade PP. These bacteria represent the cells living under the cold weather and poor nutrient levels. Interestingly Liu *et al.* (Liu *et al.*, 2021) proposed a proof of concept with ‘trap and release’ of MNPs. In this study, instead of degrading the MNPs into smaller and simpler products, genetically modified strains *P. aeruginosa* bio aggregated MNPs by a forming biofilm. Followed by a dispersal mechanism, these trapped aggregated MNPs were released for a further collection and recovery.

Table 2 highlights some of the recent research on the removal of MNPs by bacteria. Bacteria are ubiquitous in the ecosystem and can be most widely applied for the biodegradation of MNPs pollution in environment.

In further studies, species of bacteria such as *Pseudomonas aeruginosa*, have been shown

to colonize microplastics in the environment (Ayush et al., 2022). Two bacillus bacterial strains; *Bacillus cereus* and *Bacillus gottheilii*, isolated from mangrove sediments, have been shown to have the capacity to remove different microplastics composed of polyethylene, polystyrene, polyethylene terephthalate and polypropylene (Auta et al., 2017). In the study, the rate of biodegradation was assessed via measuring the microplastics weight loss using electron microscopy and FTIR analyses. Comparatively, *B. gottheilii* was found to be a better potential microplastic degrader. Other microbial species that are associated with degradation of polyethylene and polypropylene have been identified as Streptococcus, Klebsiella, Micrococcus Staphylococcus, Pseudomonas (Zeenat et al., 2021). Unfortunately, there is no research work conducted at the nano level of plastic biodegradation, hence this will be a future research topic.

The biodegradation begins by the formation of a biofilm where bacteria adhere on the surfaces and cracks of microplastics due to microplastics contact with water (Jacquin et al., 2019; Auta et al., 2018). Hydrophobicity microplastic polymers hinders the attachment of bacteria thereby preventing the formation of a biofilm and decelerating the onset of biodegradation (Pinto et al., 2019; Hossain et al., 2019). Bacterial adhesion is important in microplastic biodegradation, and the ability of bacterial adhesion has been investigated among four types of plastics; polyethylene, polypropylene, polyethylene terephthalate, and polyvinyl chloride (Cai et al., 2019). In this investigation, surface hardness of the plastics was identified as a major factor dominating the adhesion of bacteria onto plastic surfaces in contrast to the other factors (Elbourne et al., 2019). Intrinsic surface properties such as surface roughness,

topography, surface free energy, surface charge, electrostatic interactions, and surface hydrophobicity play an important role in the biofilm attachment (Persat *et al.*, 2015; Pinto *et al.*, 2019). The biofilms on microplastics are then depolymerized, catabolised and eventually bio-mineralized into organic matter (Artham and Doble, 2008; Sen and Raut, 2015; Mercier *et al.*, 2017). Indeed, some members of the bacterial species colonize around and trap microplastics creating biofilms (Yang *et al.*, 2019). In some cases, especially on the water bodies, colonization and formations of biofilms increase the density of microplastics. This makes microplastics aggregate and sink into the depths and thus decreasing prior photolytic degradation caused by the sun's UV radiation (Robyn *et al.*, 2020). Plastic related bacterial biofilms are more efficient in degrading plastics when compared to planktonic biofilms (Wilkes *et al.*, 2017). Several genera of hydrocarbon-degrading bacteria have been shown to play a vital role in plastic degradation (Delacuvellerie *et al.*, 2019).

Biofilm formation is a multistage process mediated by several factors *inter alia* temperature, light, surface properties, nutrient solution, and pH (Renner and Weibel, 2011). For instance, exposure of MPs to UV light, enable microbial enzymes to easily attach on the carbonyl group of plastic polymers (Kotova *et al.*, 2021; Taghavi *et al.*, 2021; Vedrtnam *et al.*, 2019; Montazer *et al.*, 2018). Exposure of micro-plastics to conditions such as UV radiation, thermal treatment, and pro-oxidants, generate more polar groups thereby decreasing hydrophobicity and accelerating biodegradation process (Auta *et al.*, 2017; Arkatkar *et al.*, 2009; Auta *et al.*, 2018; Arutchelvi *et al.*, 2008). By secreting various enzymes such as proteinases, bacteria can catalyse and hydrolyse plastic polymers into oligomers, monomers,

and other metabolic intermediates that can be easily mineralised into water and carbon dioxide (Siracusa, 2019).

Although more plastic-degrading bacteria have been found in the environment (Syranidou *et al.*, 2019; Mercier *et al.*, 2017; Auta *et al.*, 2017; Yoshida *et al.*, 2016; Yang *et al.*, 2019), no single strain was found suitable for commercial application to date, but a few studies have focused on the degradation of microplastics by microbial consortia (Lin, 2022). A recent study has shown that, degradation of micro-plastics using more than two bacteria living symbiotically, promotes more efficient plastic biodegradation as compared to pure strains (Oliveira *et al.*, 2020). This is due to creation of stable microbial community and elimination of the effects of toxic metabolites produced by some strains present in the community (Hibbing *et al.*, 2010). The toxic metabolites produced by one strain can be used as a substrate by another strain within the bacterial community (Singh and Wahid, 2015).

Biodegradation is typically an enzyme driven mechanism involving physico-chemical transformation of polymers into smaller units mediated by microorganisms that colonize on the surface of microplastics to form a plastisphere (Shah *et al.*, 2008; Dudek *et al.*, 2020). Several microorganisms that include bacteria, algae, fungi, and bryozoa have been observed within the plastisphere (Alshehrei, 2017; Amaral-Zettler *et al.*, 2020). The colonizing microbiota release extracellular enzymes which bio-fragment and depolymerize microplastics into oligomers, dimers, and monomers (Arkatkar *et al.*, 2009; Siracusa *et al.*, 2008). Once the microplastics have been disintegrated into smaller molecules, they pass through the microbe's cell wall, get assimilated and utilized as carbon and energy source (Da Luz *et al.*, 2015; Corcoran, 2021).

Microbial enzymes that breakdown microplastics, typically bio-fragment them into low molecular weight substrate biomass (Sengupta and Pike, 2015). The resultant bio-fragmented microplastic substrates, are transported into microbial cells via cell membranes where they are mineralized, oxidized, and used for energy production (Gu, 2003; Da Luz *et al.*, 2015; Adele Folino *et al.*, 2020). Within the microorganisms' cells, mineralized microplastics are broken down further aerobically using oxygen as an electron acceptor while producing carbon dioxide, water, biomass, and energy as by-products (Lucas *et al.*, 2008; Ayodeji Amobonye *et al.*, 2021). Biodegradation can also take place anaerobically whereby iron, nitrate, manganese, sulphate, and CO₂ serve as electron acceptor instead of oxygen while producing products such as CH₄ and H₂S (Shen *et al.*, 2020). The energy produced from biodegradation process is eventually utilised for biomass production (Lucas *et al.*, 2008; Osman *et al.*, 2021). Mineralisation yield atoms that are assimilated into microbial cells for complete degradation. Secondary metabolites are transported outside the cells or transferred to other microbes that utilize them (Mohapatra and Balaram, 2021). The secreted extracellular enzymes bio-deteriorate and bio-fragment microplastics into assimilable low molecular weight monomers and oligomers (Rhodes, 2019). Extracellular enzymes such as laccase from *Staphylococcus epidermis* and PETase from *Ideonella sakaiensis* have been shown to have the capacity to disintegrate microplastics (Yoshida *et al.*, 2016; Hiraga *et al.*, 2019; Hou and Majumder, 2021). Other oxidative enzymes such as monooxygenase, peroxidase, manganese, dehydrogenase, and oxidase, can degrade non-hydrolysable polymers e.g., polyethylene and polypropylene (Pathak *et al.*, 2017; Danso *et al.*, 2018). Moreover, bacterial enzymes such as oxygenase have the capacity to break down

carbon chains into environmentally harmless products such as alcohol and peroxy (Mohanani *et al.*, 2020; Pathak *et al.*, 2017). Likewise, enzymes lipases, proteases, ureases, esterases and endopeptidases, bio-fragment microplastics by catalysing carboxylic groups into amide groups (Amelia *et al.*, 2021; Zeenat *et al.*, 2021; Temporiti *et al.*, 2022). The reaction of such enzymes is normally optimized on those microplastic polymers that have been exposed to the action of both biotic and abiotic factors (Oliveira *et al.*, 2020). Indeed, some microbial enzymes such as laccase, lignin degrading enzymes, lipase, protease, and urease can attack the plastic polymers after such polymers have been exposed to the action of both biotic and abiotic factors (Maity *et al.*, 2021). Beside use of enzymes, micro-organisms use other compounds such as acids and peroxides which will change the surrounding pH and facilitate biodegradation process (Karigar and Rao, 2011). Microorganisms can also chemically weaken plastics by changing the pH of the surrounding microenvironment (Karigar and Rao, 2011).

Fungal-enzymatic processes

Terrestrial and marine fungi biodegrade plastic polymers and utilise them as source of nutrients (Russel *et al.* 2011; Zengal *et al.*, 2021). Fungi can promote the formation of different chemical bonds in micro plastics, such as carbonyl, carboxyl, and ester functional groups, decreasing their hydrophobicity (Yuan *et al.*, 2020). Fungi exhibit extraordinary strategies including adsorption ability, natural biosurfactant production, and extremely unspecific oxidative enzymes which allow them to oxidize numerous substrates that could attack polymers by the co-metabolic process and use plastic particles as carbon, energy, and electron sources (Bacha *et al.*, 2021).

Paço *et al.*, 2017 used a naturally occurring marine fungus *Zalerion maritimum* to degrade PE micro particles of the size range between 250um – 1000um over 28 days. The results showed that starting at the 14th day, the biomass weight increased 82% and PE weight loss 57% which corresponds to the removal rate of 43%. Until the 28th day, when the PE micro plastic weight loss was 73%. The FTIR-ATR and NMR results of *Zalerion maritimum* indicated the obvious reduction of this fungus lipidic and protein content when exposed to microplastics. Meanwhile, the FTIR spectra of PE showed the presence of oxidation functional groups which implied the degradation of microplastics.

Zhang *et al.*, 2020 isolated a PE-degrading fungus *Aspergillus flavus* named PEDX3 from the gut contents of wax moth *Galleria mellonella*. Their results indicated that HDPE of the size less than 200µm degraded into the microplastic particles with a lower molecular weight by PEDX3 after 28 days of incubation. The HDPE mass loss was 3.9% and the molecular weight decreased from 220,003 Da to 89,801 Da which corresponds to a 59% loss. This proved that HDPE produced microplastic particles were converted to smaller molecular weight and were more concentrated after exposure to strain PEDX3, which suggested that the depolymerization of HDPE long chain structure occurred and that lower molecular weight fragments were formed.

Some plastic degrading fungi from the Ascomycete phylum in which *Fusarium*, *Penicillium* and *Aspergillus* belong, have been identified (Tachibana *et al.*, 2010; Raghavendra *et al.*, 2016). Fungal strains belonging to *Penicillium sp* such as *P. chrysogenum*, *P. oxalicum* and *P. simplicissimum* are potential plastic degraders (Sowmya *et al.*, 2015; Ojha *et al.*, 2017

and Alshehrei, 2017). The genus *Aspergillus* possess several species that include *A. flavus*, *A. niger* and *A. terreus* that have been found to possess the abilities of degrading plastics (Zhang *et al.*, 2020; Yamada-Onodera *et al.* 2001). Other fungi such as *Myceliophthora* sp., *Phanerochaete chrysosporium*, and *Trametes versicolor*, exhibit the ability to degrade plastics especially those of polyethylene origin (Khalil *et al.*, 2013; Ojha *et al.*, 2017). Plastic wastes can also be degraded by fungal mushrooms which convert microplastics into fungal biomass (Da Luz *et al.*, 2012). Chemical and physical properties such as high molecular weight, hydrophobicity and insolubility of microplastics, make them difficult to biodegrade (Wei and Zimmermann, 2017; Kumar *et al.*, 2020; Amobonye *et al.*, 2021). However, use of filamentous fungi as means of removing microplastics, can circumvent this problem. This is because, filamentous fungal hyphae have penetrative apical growth which allows them to extend their mycelial networks into different kinds of materials. Besides, fungal hyphae secrete biochemical such as hydrophobics which promote adhesion to hydrophobic substrates (Daccò, *et al.*, 2020; Sánchez, 2020). Fungi production of fungal enzymes that can biodegrade microplastics polymers (Temporiti *et al.*, 2022). Fungal exoenzymes such as hydrolases (lipases, carboxylesterases, cutinases and proteases) modify the plastic surface, increasing its hydrophilicity and facilitate the biodegradation PET (Vertommen *et al.*, 2005; Krueger *et al.*, 2015; Webb *et al.*, 2013). Moreover, oxidoreductases (laccases and peroxidases) are involved in plastic degradation into micromeres such as oligomers, dimers and monomers (Álvarez-Barragán *et al.*, 2016; Gómez-Méndez *et al.*, 2018). These enzymes can depolymerize, biodegrade and thereby bioremediate different plastic polymers with higher

stable carbon–carbon (C–C) bonds but after such polymers have undergone oxidation (Da Luz *et al.*, 2019; Restrepo-Florez *et al.*, 2014). The fungus *Pestalotiopsis microspore* (an endophytic fungi), use its hydrolase enzyme to decompose microplastic polymers and utilise them as source of carbon (Russell *et al.* 2011). Furthermore, the enzymes serine hydrolases from fungi, have been shown to degrade micro-plastics in the presence of optimally controlled culture conditions (Ahmaditabatabaei *et al.*, 2021). Enzymes depolymerase, esterase, Manganese peroxidase and lignolytic enzymes produced by white rot fungi; *Phanerochaete chrysosporium*, split and degrade plastic polymers into small chain compounds especially those of nylon and polyethylene origins (Shimao, 2001; Da Luz *et al.*, 2012; Nunes *et al.*, 2014; Sato *et al.*, 2017; Oliveira *et al.*, 2018). Low-density polyethylene-based plastics can be easily deteriorated by fungal enzymes; laccase, manganese peroxidase and lignin peroxidase from *P. ostreatus* (Gómez-Méndez *et al.*, 2018). Moreover, Luccase enzyme produced by the fungus *Cochliobolus* sp has the capacity to degrade polyvinyl chloride-based plastics with *Myceliophthora* sp also being able to degrade polyethylene and polyurethane-based plastics (Loredo-Treviño *et al.*, 2011; Sumathi *et al.*, 2016; Moreno-Bayona *et al.*, 2019).

Penicillium sp produce the enzymes laccase and manganese peroxidase that have been shown to degrade polyethylene and natural rubber-based plastics (Santo *et al.*, 2013; Nayanashree and Tyhippeswam, 2015). However, degradation of microplastics by the fungi community is usually a slow process over many years, it would become unavoidable to subject microplastics to pre-treatments such as ozonolysis, photo-oxidation and solvolysis to initiate polymer degradation prior to fungal biodegradation (Dey *et al.*, 2021). Besides, efficient fungal

biodegradation sometimes requires specific external conditions to be optimal. For instance, the efficiency of plastic biodegradation by marine fungi *Zelerion maritimum* is increased under dark environment and at 25°C (Paço *et al.* 2017).

There are many research gaps of MP and NP removal by fungi. For example, most research work has been based on the visible polymer plastics and not on the micro plastic size. Only a few papers published mentioned research based on the micro-plastics. None of them studied nano plastics. On the other hand, MP and NP type is limited to PE, as no other types of micro plastic have been studied.

Green algae bioremediation

Edible marine microalgae, seaweed; *Fucus vesicu-losus* has been demonstrated to have the high capacity of approximately 94.5% to adsorb polystyrene microplastics (Sundbaek *et al.* 2018). The microalgae can sorb tiny plastic particles due to the surface charge of plastics (Bhattacharya *et al.* 2010; Nolte *et al.* 2017). However, the sorption of microplastics on algae surface largely relies on surface charge of particles (Lionetto *et al.*, 2021). Positively charged microplastics have higher tendency to be sorb more efficiently, due to the presence of an anionic polysaccharide in the algal chemical structure (Mohsen *et al.*, 2020). For instance, unicellular green algae, *Pseudokirchneriella subcapitata* adsorb positively charged polystyrene microplastics more efficiently as opposed to those that are negatively charged (Nolte *et al.*, 2017).

Planktonic crustacean bioremediation

Antarctic Krill can ingest polyethylene microplastics fragments and alter their size (Dawson *et al.* 2018). However, the degradation of microplastics by zooplankton, is reliant abiotic and biotic factors that must first fragment microplastics into smaller sizes (Ter Halle *et al.*, 2016). Marine communities of *Agios consortium* and *Souda consortium* have the capacity to remove high-density polyethylene (Cocca *et al.*, 2017). In the process of degrading Microplastics, these marine organisms, first adhere to microplastics surfaces, which is the first step in microbial polymer degradation, before breaking them down and utilize them as the source of carbon (Sivan 2011; Cocca *et al.*, 2017). Biodegradation of microplastics by marine organisms is unlikely to be efficient. This is due to microplastics' small size and weight that make them carried to and from by the movement of ocean winds thus reducing physical contact with possible degraders (Ivleva *et al.* 2017).

Concluding remarks and perspectives

There is limited information on drinking water contaminated with high concentration of MPs, also the available evidence suggests that they do accumulate in the human body with limited health risks. Hence human intake of MP from drinking water and the public health risk from micro and nano plastics cannot yet be fully confirmed due to the limited research and variation in sampling and analysis methods and lack of research in this area. However, based on the available evidence and the reported low MP concentrations in treated drinking water, microbial and chemical risks to drinking water quality appear to be greater than those presented by MPs.

There are several physical, chemical, and biological methods to remove and destroy micro and nano plastics in the ecosystem, however, there are not widely accepted and there are no cost-effective methods for complete removal of micro and nano plastics from the ecosystem. Also, there is a need to consider microplastics like other contaminants, cycle through ecosystems – natural and engineered, they do not operate in siloes and waste from treatment processes could be a conduit for recontamination of microplastics. Hence reducing plastic use would be the best option.

Within the context of drinking water, some key knowledge gaps and needs are:

- Standardized methods to enable reliable MP assessment and comparison between studies.
- Simulated environmental or field studies to consider transport, fate and removal of MPs (bench top studies do not replicate the multitude of interactions in operational systems or at the appropriate scale)
- Improved detection, characterization and quantification of microplastics in drinking water systems from source to human. intake to ascertain sources and sinks throughout the system (freshwater and drinking water)
- Epidemiological studies to determine the impact of microplastic characteristics (e.g. size, composition) on uptake into tissues following ingestion to inform which particles (if any) in water supplies are most likely to be toxic.

The research on removal of MPs is still limited. However, it is imperative to be cognizant of the following major considerations:

- Identification of transformation products, elucidation of degradation mechanisms, and toxicity assays, as well as computational tools, are needed to improve the assumption of these processes as feasible treatment options.
- Most current studies demonstrating the MP degradation have been performed in bench-scale investigations. It is indeed important to conduct pilot-scale experiments to scale-up for industrial level applications.
- From a microbial perspective, increased understanding of the environmental variables that influence:
 - Formation of biofilm on microplastics (and other plastic surfaces)
 - Composition of micro-plastic associated biofilms
 - Interactions between the microbiome of microplastics and water quality/safety
 - Transporting capacity/degradation of microplastics (in comparison to other particles in water sources)

In conclusion, the presence of microplastics in drinking water systems is a growing concern, and there are significant gaps in our knowledge of their transport, fate, and potential impacts on human health. Addressing these gaps will require a concerted effort from scientists, regulators, and water system operators, and will likely involve the development of standardized methods for assessing and comparing microplastic contamination, as well as the conduct both simulated environmental and field studies to better understand how MPs behave in real-world settings. Moreover, there is a need for improved detection and characterization methods, as well as epidemiological studies to determine risk assessments and identify potential toxicity.

Finally, the role of microplastics in shaping microbial communities and influencing water quality and safety requires further study to better understand their impacts on both human health and environmental sustainability.

Acknowledgements

Authors would like to acknowledge the contributions of the following individuals: David Nyakundi, Emmanuel Mogusu, Gileard Minja, Cornelius Mshubushi, and Didas Kimaro, Catholic University, Moshi, Kilimanjaro, Tanzania; Kazi Parvez Fattah, Department of Civil Engineering, American University of Sharjah, PO Box 26666, Sharjah, United Arab Emirates; Massoud Pirbazari, Department of Civil Engineering, University of Southern California, Los Angeles, CA, USA; Hong Guan and Catherine N. Mulligan, Concordia University, Montreal, Canada, Richard W. Marsh and Siddhartha Chittineni, of New Jersey Institute of Technology, NJ, USA, Leon Zhou of Pingry School, NJ, USA and Ben Ramster, Institute of Civil Engineers, London, UK.

References

- Ahmaditabatabaei S., Kyazze G., Iqbal H.M.N., Keshavarz T. 2021. Fungal Enzymes as Catalytic Tools for Polyethylene Terephthalate (PET) Degradation. *Journal of Fungi*. 7: 931.
- Alimba, C.G., Faggio, C. 2019. Microplastics in the marine environment: Current trends in environmental pollution and mechanisms of toxicological profile. *Environ. Toxicol. Pharmacol.* 68: 61–74.
- Allouzi, M.M.A., Tang, D.Y.Y., Chew, K.W., Rinklebe, J., Bolan, N., Allouzi, S.M.A., Show, P.L. . 2021. Micro (nano) plastic pollution: The ecological influence on soil-plant system and human health. *Sci. Total Environ.* 788: 147815.
- Alshehrei, F. 2017. Biodegradation of synthetic and natural plastic by microorganisms. *J. Appl. Environ. Microbiol.* 5: 8–19.
- Álvarez-Barragán J., Domínguez-Malfavón L., Vargas-Suárez M., González-Hernández R., Aguilar-Osorio G., Loza-Tavera H. 2016. Biodegradative activities of selected environmental fungi on a polyester polyurethane varnish and polyether polyurethane foams. *Appl. Environ. Microbiol.* 82: 5225–5235.
- Amaral-Zettler, L. A., Erik R Zettler, Beth Slikas, Gregory D Boyd, Donald W Melvin, Clare E Morrall, Giora Proskurowski, Tracy J Mincer, The biogeography of the Plastisphere: implications for policy, *Frontiers in Ecology and the Environment Research Communication*, 01 December 2015 <https://doi.org/10.1890/150017>
- Amaral-Zettler L.A., Zettler E.R., Mincer, T.J. 2020. Ecology of the plastisphere. *Nat Rev*

Microbiol 18, 139–151.

Amelia T.S.M., Khalik W.M.A.W.M., Ong M.C., *et al.* 2021. Marine microplastics as vectors of major ocean pollutants and its hazards to the marine ecosystem and humans. *Prog. Earth. Planet. Sci.* 8; 12.

Amobonye A., Bhagwat P., Singh S., Pillai S. 2021. Plastic biodegradation: Frontline microbes and their enzymes. *Sci. Total. Environ.* 759: 143536. doi: 10.1016/j.scitotenv.2020.143536.

Arkatkar A., Arutchelvi J., Bhaduri S., Uppara P.V., Doble M. 2009. Degradation of unpretreated and thermally pretreated polypropylene by soil consortia. *Int. Biodeterior. Biodegrad.* 63: 106–111.

Artham T., Doble M. 2008. Biodegradation of aliphatic and aromatic polycarbonates. *Macromol. Biosci.* 8:14–24.

Arutchelvi J., Sudhakar M., Arkatkar A. *et al.* 2008. Biodegradation of polyethylene and polypropylene. *Indian J. Biotechnol.* 7: 9–2.

Ateia M., Kanan A., Karanfil T. 2020. Microplastics release precursors of chlorinated and brominated disinfection byproducts in water. *Chemosphere.* 251: 126452. doi:10.1016/j.chemosphere.2020.126452

Auta, H.S., Emenike C.U., Fauziah S.H. 2017. Screening of *Bacillus* strains isolated from mangrove ecosystems in Peninsular Malasia for microplastic degradation. *Environ. Pollut.* 231: 1552-59.

Auta, H.S., Emenike C.U., Jayanthi B., Fauziah S.H. 2018. Growth kinetics and

- biodeterioration of polypropylene microplastics by *Bacillus* sp. and *Rhodococcus* sp. isolated from mangrove sediment. *Mar. Pollut. Bull.* 127: 15–21.
- Ayush P.T., Ko J.-H., Oh H.-S. 2022. Characteristics of Initial Attachment and Biofilm Formation of *Pseudomonas aeruginosa* on Microplastic Surfaces. *Appl. Sci.* 12: 5245. <https://doi.org/10.3390/app12105245>
- Ashfaq M.Y., Al-Ghouti M.A., Qiblawey H., Zouari N., Rodrigues D.F., Hu Y. 2019. Use of DPSIR Framework to Analyze Water Resources in Qatar and Overview of Reverse Osmosis as an Environment Friendly Technology. *Environ. Progr. Sustain. Ener.* 38: 1–13.
- Bacha A-U-R., Nabi I., Zhang L. 2021. Mechanisms and the engineering approaches for the degradation of microplastics. *ACS EST Eng.* 1: 1481–1501.
- Badola N., Bahuguna A., Sasson Y., Chauhan J.S. 2022. Microplastics removal strategies: A step toward finding the solution. *Front. Environ. Sci. Eng.* 16:1–18
- Bandow N., Will V., Wachtendorf V., Simon F.-G. 2017. Contaminant release from aged microplastic, *Environ. Chem.* 14: 394. <https://doi.org/10.1071/EN17064>
- Bayo J., López-Castellanos J., Olmos S. 2020. Membrane bioreactor and rapid sand filtration for the removal of microplastics in an urban wastewater treatment plant. *Marine Pollution Bulletin.* 156: 111211. doi:10.1016/j.marpolbul.2020.111211
- Bhattacharya P., Lin S., Turner J.P., Ke P.C. 2010. Physical adsorption of charged plastic nanoparticles affects algal photosynthesis. *J. Phys. Chem. C* 114:16556–16561. <https://doi.org/10.1021/jp1054759>

- Bildik Dal A. E., Hubbe M. A. 2021. Hydrophobic copolymers added with starch at the size press of a paper machine: A review of findings and likely mechanisms. *BioResources* 16: 2138-2180.
- Boyle K., Örmeci B. 2020. Microplastics and Nanoplastics in the Freshwater and Terrestrial Environment: A Review. *Water*. 12: 2633. <https://doi.org/10.3390/w12092633>.
- Bryant J.A., Clemente T.M., Viviani D.A. *et al.* 2016. Diversity and activity of communities inhabiting plastic debris in the North Pacific Gyre. *mSystems* 1:e00024–e00016
- Burgess R.M., Ho K.T. 2017. The Challenge: Microplastics in the aquatic environment —Perspectives on the scope of the problem. *Environ. Toxicol. Chem.* 36: 2259–2259.
- Cai L., Wu D., Xia J., Shi H., Kim H. 2019. Influence of physicochemical surface properties on the adhesion of bacteria onto four types of plastics. *Sci. Total. Environ.* 671:1101-1107. DOI: 10.1016/j.scitotenv.2019.03.434
- Calabrò P.S., Grosso M. 2018. Bioplastics and waste management. *Waste Manag.* 78: 800–801.
- Chen X., Wang Y., Chen S., Sun Y., Tan Q., Ding Z., *et al.* 2021. Microplastics as carbon-nutrient sources and shaper for microbial communities in stagnant water. *J Hazard Mater.* 420:126662. doi: 10.1016/j.jhazmat.2021.126662.
- Chen, G., Patel, M.K., 2012. Plastics Derived from Biological Sources: Present and Future: A Technical and Environmental Review. *Chem. Rev.* 112: 2082–2099.
- Cheng H., Luo H., Hu Y., Tao S. 2020. Release kinetics as a key linkage between the occurrence of flame retardants in microplastics and their risk to the environment and ecosystem: A critical review. *Water Res.* 185: 116253. doi:10.1016/j.watres.2020.116253

- Cocca M., Di Pace E., Errico M.E., Gentile G., Montarsolo A., Mossotti R. 2017. Proceedings of the international conference on microplastic pollution in the mediterranean sea. Springer, Berlin
- Corcoran P.L. 2021. Degradation of Microplastics in the Environment. In: Rocha-Santos T., Costa M., Mouneyrac C. (eds) Handbook of Microplastics in the Environment. Springer, Cham. https://doi.org/10.1007/978-3-030-10618-8_10-1
- Da L., Nunes J.M.R., Paes M.D., Torres S.A, Silva D.P. *et al.* 2012. Lignocellulolytic enzyme production of *Pleurotus ostreatus* growth in agroindustrial wastes. *Braz. J. Microbiol.* 43:1508-1515.
- Da L., J.M., Paes S.A., Ribeiro K.V., Mendes I.R., Kasuya M.C. 2015. Degradation of Green Polyethylene by *Pleurotus ostreatus*. *PLoS ONE.* 10: e0126047.
- Da L., J.M.R., da Silva M.D.C.S., dos Santos L.F., Kasuya, M.C.M. 2019. Plastics polymers degradation by fungi. In *Microorganisms*; Blumenberg, M., Ed.; IntechOpen: London, UK. pp. 261–270.
- Daccò C., Girometta C., Asemoloye M.D., Carpani G., Picco A.M., Tosi S. 2020. Key fungal degradation patterns, enzymes and their applications for the removal of aliphatic hydrocarbons in polluted soils: A review. *Int. Biodeterior. Biodegrad.* 147: 104866.
- Dalmau-Soler J., Ballesteros-Cano R., Boleda M.R., Paraira M., Ferrer N., Lacorte S. 2021. Microplastics from headwaters to tap water: occurrence and removal in a drinking water treatment plant in Barcelona Metropolitan area (Catalonia, NE Spain). *Environ. Sci. Pollut. Res.* 28: 59462–59472. doi:10.1007/s11356-021-13220-1

- Danso D., Chow J., Streit W. R. 2019. Plastics: environmental and biotechnological perspectives on microbial degradation. *Appl. Environ. Microbiol.* 85: e01095. doi: 10.1128/AEM.01095-19
- Dawson A.L., Kawaguchi S., King C.K., Townsend K.A, King R., Huston W.M., Nash S.M.B. 2018. Turning microplastics into nanoplastics through digestive fragmentation by Antarctic krill. *Nat. Commun.* 9:1001. <https://doi.org/10.1038/s41467-018-03465-9>
- De Tender C.A., Devriese L.I., Haegeman A. *et al.* 2017. The temporal dynamics of bacterial and fungal colonization on plastic debris in the North Sea. *Environ. Sci. Technol.* 51: 7350–7360.
- Delacuvellerie, A., Cyriaque, V., Gobert, S., Benali, S. and Wattiez, R., The plastisphere in marine ecosystem hosts potential specific microbial degraders including *Alcanivorax borkumensis* as a key player for the low-density polyethylene degradation, *Journal of Hazardous Materials*, Volume 380, 15 December 2019, 120899
- Dey T. K., Uddin M.E., Jamal M. 2021. Detection and removal of microplastics in wastewater: evolution and impact. *Environ. Sci. Pollut. Res.* 28: 16925–16947. <https://doi.org/10.1007/s11356-021-12943-5>
- Ding H., Zhang J., He H., Zhu Y., Dionysiou D.D., Liu Z., *et al.* 2021. Do membrane filtration systems in drinking water treatment plants release nano/microplastics? *Sci. Total. Environ.* 755: 142658. doi:10.1016/j.scitotenv.2020.142658
- Ding S., Sin A. , Nam H., Park Y., Lee H., Han C. 2022. Advanced oxidation processes for microplastic degradation: recent trend, *Chem. Eng. J. Adv.* 9: 100213.

- Dudek K., Cruz B., Polidoro B., Neuer S. 2020. Microbial colonization of microplastics in the Caribbean Sea, Dryad, Dataset, <https://doi.org/10.5061/dryad.z8w9ghx7m>
- Elbourne A., Chapman J., Gelmi A., Cozzolino D., Crawford R.J., Truong V.K. 2019. Bacterial-nanostructure interactions: The role of cell elasticity and adhesion forces. *J. Colloid Interface Sci.* 546: 192-210. DOI: 10.1016/j.jcis.2019.03.050
- Folino A., Karageorgiou A., Calabrò P.S., Komilis D. 2020. Biodegradation of Wasted Bioplastics in Natural and Industrial Environments: A Review. *Sustainability.* 2020; 12: 6030. <https://doi.org/10.3390/su12156030>
- Garrido Gamarro E., Costanzo V. 2022. Dietary Exposure to Additives and Sorbed Contaminants from Ingested Microplastic Particles Through the Consumption of Fisheries and Aquaculture Products. In: Bank, M.S. (eds) *Microplastic in the Environment: Pattern and Process. Environmental Contamination Remediation and Management.* Springer, Cham. https://doi.org/10.1007/978-3-030-78627-4_8
- Gómez-Méndez L.D., Moreno-Bayona D.A., Poutou-Piñales R.A., Salcedo-Reyes J.C., Pedroza-Rodríguez A.M., Vargas A., *et al.* 2018. Biodeterioration of plasma pretreated LDPE sheets by *Pleurotus ostreatus*. *PLoS One.* 13:e0203786. DOI: 10.1371/journal.pone.0203786
- Gu J.D. 2003. Microbiological deterioration and degradation of synthetic polymeric materials: recent research advances. *Int. Biodeterior. Biodegradation* 52:69–91.
- Habib S., Iruthayam A., Abd Shukor M.Y., S. Alias, J. Smykla, N. A. Yasid. 2020. Biodeterioration of untreated polypropylene microplastic particles by antarctic bacteria.

- Polymers. 12: 2616.
- Hakkarainen M., Albertsson A.C. 2004. Environmental degradation of polyethylene. In: Albertsson AC (ed) Long term properties of polyolefins. Advances in polymer science, 169. Springer, Heidelberg. 177–200.
- Harmaen A. S., Khalina A., Azowa I., Hassan M.A., Tarmian, A., Jawaid, M. 2015. Thermal and biodegradation properties of poly(lactic acid)/fertilizer/oil palm fibers blends biocomposites. Polym. Compos. 36: 576–583.
- Hettiarachchi, H. and Meegoda, J.N. Microplastic Pollution Prevention: The Need for Robust Policy Interventions to Close the Loopholes in Current Waste Management Practices. Int. J. Environ. Res. Public Health 2023, 20, 6434. <https://doi.org/10.3390/ijerph20146434>
- Hibbing M.E., Fuqua C., Parsek M.R., Peterson S.B. 2010. Bacterial competition: surviving and thriving in the microbial jungle. Nat Rev Microbiol. 8:15-25. doi: 10.1038/nrmicro2259. PMID: 19946288; PMCID: PMC2879262.
- Hidayaturrehman H., Lee T.G. 2019. A study on characteristics of microplastic in wastewater of South Korea: identification, quantification, and fate of microplastics during treatment process, Mar. Pollut. Bull. 146: 696–702.
- Hiraga K., Taniguchi I., Yoshida S., Kimura Y., Oda K. 2019. Biodegradation of waste PET: A sustainable solution for dealing with plastic pollution. EMBO Rep. 20. e49365.
- Hossain M. R., Jiang M., Wei Q., Leff L.G. 2019. Microplastic surface properties affect bacterial colonization in freshwater. J. Basic Microbiol. 59: 54–61.
- Hou L., Majumder E.L. 2021. Potential for and Distribution of Enzymatic Biodegradation of

- Polystyrene by Environmental Microorganisms. *Materials*. 14: 503.
<https://doi.org/10.3390/ma14030503>
- Ivleva N. P., Wiesheu A.C., Niessner R. 2017. Microplastic in aquatic ecosystems. *Angew. Chem. Int. Ed.* 56:1720–173.
- Jacquín, J., Cheng J., Odobel C., Pandin C., Conan P., Pujo-Pay M., Ghiglione J.F. 2019. Microbial ecotoxicology of marine plastic debris: A review on colonization and biodegradation by the “Plastisphere”. *Front. Microbiol.* 10: 865.
- Jagannathan S.V., Manemann E.M., Rowe S.E., Callender M.C., Soto W. 2021. Marine Actinomycetes, New Sources of Biotechnological Products. *Mar Drugs*. 19:365. doi: 10.3390/md19070365. PMID: 34201951; PMCID: PMC8304352.
- Jambeck J.R., Geyer R., Wilcox C., Siegler T.R., Perryman M., Andrady A., *et al.* 2015. Plastic waste inputs from land into the ocean. *Science*. 347: 768–771. doi:10.1126/science.1260352
- Jiang Q., Li Z., Wei R., Xu H., Liu L. 2021. Quantum mechanical investigation of the oxidative cleavage of c-c backbone bonds in polyethylene model molecule. *Polymers*. 13: 2730.
- Johnson AC, Ball H, Cross R, Horton AA, Jürgens MD, Read DS, *et al.* Identification and Quantification of Microplastics in Potable Water and Their Sources within Water Treatment Works in England and Wales. *Environ Sci Technol.* 2020;54: 12326–12334. doi:10.1021/acs.est.0c03211
- Karigar C S, Rao SS. Role of microbial enzymes in the bioremediation of pollutants: a review. *Enzyme Res.* 2011;2011:805187. doi: 10.4061/2011/805187. Epub 2011 Sep 7. PMID:

21912739; PMCID: PMC3168789.

Khalil M I, Ramadan NA, Albarhawi RK. Biodegradation of polymers by fungi isolated from plastic garbage and the optimum condition assessment of growth. *Journal of Environmental Management*. 2013;1:33-43

Kida, M., Ziembowicz, S., Koszelnik, P., “Impact of modified Fenton process on the degradation of a component leached from microplastics in bottom sediments”, *Catalysis*, (2019), 9 (11), 932.

Kiendrebeogo, M. *et al.* (2021) ‘Treatment of microplastics in water by anodic oxidation: A case study for polystyrene’, *Environmental Pollution*, 269, p. 116168.

Kim S., Sin A., Nam H., Park Y., Lee H., Han C., Advanced oxidation processes for microplastics degradation: A recent trend, *Chemical Engineering Journal Advances*, Volume 9, 2022, 100213.

Kirstein I V, Gomiero A, Vollertsen J. Microplastic pollution in drinking water. *Current Opinion in Toxicology*. 2021;28: 70–75. doi:10.1016/j.cotox.2021.09.003

Koelmans A A, Mohamed Nor NH, Hermsen E, Kooi M, Mintenig SM, De France J. Microplastics in freshwaters and drinking water: Critical review and assessment of data quality. *Water Research*. 2019;155: 410–422. doi:10.1016/j.watres.2019.02.054

Kotova, I. B., Taktarova, Y.V., Tsavkelova, E.A. *et al.* Microbial Degradation of Plastics and Approaches to Make it More Efficient. *Microbiology* 90, 671–701 (2021).
<https://doi.org/10.1134/S0026261721060084>

Koutny M, Sancelme M, Dabin C, Pichon N, Delort AM, Lemaire J. Acquired biodegradability

- of polyethylenes containing pro-oxidant additives. *Polymer Degradation and Stability*. 2006;91:1495-1503. DOI: 10.1016/j.polymdegradstab.2005.10.007
- Kroon, R., Mengistie, D.A., Kiefer, D., Hynnen, J. , Ryan, J.D. , Yu, L. , Müller, C. , 2016. Thermoelectric plastics: from design to synthesis, processing and structure-property relationships. *Chem. Soc. Rev.* 45, 6147–6164.
- Krueger, M. C.; Hofmann, U.; Moeder, M.; Schlosser, D. Potential of wood-rotting fungi to attack polystyrene sulfonate and its depolymerisation by *Gloeophyllum trabeum* via hydroquinone-driven Fenton chemistry. *PLoS ONE* 2015, 10, e0131773.
- Kumar A, Chandra R. Ligninolytic enzymes and its mechanisms for degradation of lignocellulosic waste in environment. *Heliyon*. 2020 Feb 19;6(2):e03170. doi: 10.1016/j.heliyon.2020.e03170. PMID: 32095645; PMCID: PMC7033530.
- Lares, M. *et al.* (2018) ‘Occurrence, identification and removal of microplastic particles and fibers in conventional activated sludge process and advanced MBR technology’, *Water research*, 133, pp. 236–246.
- Law K L, Morét-Ferguson SE, Goodwin DS, Zettler ER, DeForce E, Kukulka T, Proskurowski G (2014) Distribution of surface plastic debris in the eastern Pacific Ocean from an 11-year data set. *Environ Sci Technol* 48(9):4732–4738. <https://doi.org/10.1021/es4053076>.
- Lee Y K, Murphy KR, Hur J. Fluorescence Signatures of Dissolved Organic Matter Leached from Microplastics: Polymers and Additives. *Environ Sci Technol*. 2020;54: 11905–11914. doi:10.1021/acs.est.0c00942

- Li J, Liu H, Paul Chen J. Microplastics in freshwater systems: A review on occurrence, environmental effects, and methods for microplastics detection. *Water Research*. 2018;137: 362–374. doi:10.1016/j.watres.2017.12.056
- Li Q, Hu Y, Kou D, Yang W, Tang W, Chen Q, *et al.* Factors Impacting Microplastic Biofilm Community and Biological Risks Posed by Microplastics in Drinking Water Sources. *Water, Air, and Soil Pollution*. 2022;233. doi:10.1007/s11270-022-05649-y
- Li Q, Lai Y, Yu S, Li P, Zhou X, Dong L, *et al.* Sequential Isolation of Microplastics and Nanoplastics in Environmental Waters by Membrane Filtration, Followed by Cloud-Point Extraction. *Anal Chem*. 2021;93: 4559–4566. doi:10.1021/acs.analchem.0c04996
- Li, J. , Liu, H. , Chen, J.P. , 2018. Microplastics in freshwater systems: A review on occurrence, environmental effects, and methods for microplastics detection. *Water Res.* 137, 362–374.
- Li, J., Song, Y., Cai, Y., 2020. Focus topics on microplastics in soil: Analytical methods, occurrence, transport, and ecological risks. *Environ. Pollut.* 257, 113570.
- Lin, L. Bottom-up synthetic ecology study of microbial consortia to enhance lignocellulose bioconversion. *Biotechnol Biofuels* 15, 14 (2022). <https://doi.org/10.1186/s13068-022-02113-1>
- Lionetto, F.; Esposito Corcione, C. An Overview of the Sorption Studies of Contaminants on Poly(Ethylene Terephthalate) Microplastics in the Marine Environment. *J. Mar. Sci. Eng.* 2021, 9, 445. <https://doi.org/10.3390/jmse9040445>
- Liu, B., Jiang, Q., Qui, z., Liu, L., Wei, R., Zhang, x., Process analysis of microplastic

- degradation using activated PmS and Fenton Reagents:, *Chemosphere*, (2022), 298
134220.
- Liu, X., P. Sun, G. Qu, J. Jing, T. Zhang, H. Shi, Y. Zhao, Insight into the characteristics and sorption behaviors of aged polystyrene microplastics through three type of accelerated oxidation processes, *J. Hazard. Mater.* 407 (2021), 124836.
- Loredo-Treviño A, García G, Velasco-Téllez A, Rodríguez-Herrera R, Aguilar CN. Polyurethane foam as substrate for fungal strains. *Advances in Bioscience and Biotechnology*. 2011;2:52-58
- Lucas N, Bienaime C, Belloy C, Queneudec M, Silvestre F, Nava-Saucedo JE. Polymer biodegradation: Mechanisms and estimation techniques—a review. *Chemosphere*. 2008;73(4):429-442. DOI: 10.1016/j.chemosphere.2008.06.064
- Fadli, M. H., M. Ibadurrohman, S. Slamet, Microplastic Pollutant degradation in water using modified TiO₂ photocatalyst under UV-irradiation, *IOP Conf. Ser. Mater. Sci. Eng.* (2021), 012055.
- Ma, J. *et al.* (2013) ‘Microbial communities in an anaerobic dynamic membrane bioreactor (AnDMBR) for municipal wastewater treatment: Comparison of bulk sludge and cake layer’, *Process Biochemistry*, 48(3), pp. 510–516.
- MacArthur D E, Waughray D, Stuchtey M (2016) The new plastics economy, rethinking the future of plastics. World Economic Forum.
- Mahesh S, Tang KC, Raj M. Amide Bond Activation of Biological Molecules. *Molecules*. 2018 Oct 12;23(10):2615. doi: 10.3390/molecules23102615. PMID: 30322008; PMCID:

PMC6222841.

Maity, S., Banerjee, S., Biswas, C. *et al.* Functional interplay between plastic polymers and microbes: a comprehensive review. *Biodegradation* 32, 487–510 (2021).
<https://doi.org/10.1007/s10532-021-09954-x>

Mantel, T., B. Büning, M. Ernst, 'Removal of micropollutants from the effluent of municipal wastewater treatment plants with electrosorptive membrane ultrafiltration', Conference Proceedings, 14. Aachener Tagung Wassertechnologie, 02 - 03 November 2021, Aachen

Meegoda, J.N. and Hettiarachchi, M.C., A Path to a Reduction in Micro and Nanoplastics Pollution. *Int. J. Environ. Res. Public Health* 2023, 20, 5555.
<https://doi.org/10.3390/ijerph20085555>

Mercier A, Gravouil K, Aucher W et al (2017) Fate of eight different polymers under uncontrolled composting conditions: relationships between deterioration, biofilm formation, and the material surface properties. *Environ Sci Technol* 51(4):1988–1997

Metzler, D. and Simbeck, S., , 2022, "Microplastics: Global buzz and concern spur increased regulation," Haley & Aldrich, 70 Blanchard Road, Suite 204, Burlington, MA 0180

Mohanan N, Montazer Z, Sharma PK, Levin DB. Microbial and Enzymatic Degradation of Synthetic Plastics. *Front Microbiol.* 2020 Nov 26;11:580709. doi: 10.3389/fmicb.2020.580709. PMID: 33324366; PMCID: PMC7726165.

Mohapatra, Balaram, Phale Prashant S. Microbial Degradation of Naphthalene and Substituted Naphthalenes: Metabolic Diversity and Genomic Insight for Bioremediation. *Frontiers in Bioengineering and Biotechnology* 9. 2021 <https://www.frontiersin.org/>

article/10.3389/fbioe.2021.602445

Mohsen P., Eric Lichtfouse, Didier Robert, Chuanyi Wang. Removal of microplastics from the environment. A review. *Environmental Chemistry Letters*, Springer Verlag, 2020, 18 (3), pp.807-828. 10.1007/s10311-020-00983-1

Montazer, Z., Habibi-Najafi, M.B., Mohebbi, M. *et al.* Microbial Degradation of UV-Pretreated Low-Density Polyethylene Films by Novel Polyethylene-Degrading Bacteria Isolated from Plastic-Dump Soil. *J Polym Environ* 26, 3613–3625 (2018).
<https://doi.org/10.1007/s10924-018-1245-0>

Moreno-Bayona D A, Gómez-Méndez LD, Blanco-Vargas A, Castillo-Toro A, Herrera Carlosama L, Poutou-Piñales RA, *et al.* Simultaneous bioconversion of lignocellulosic residues and oxodegradable polyethylene by *Pleurotus ostreatus* for biochar production, enriched with phosphate solubilizing bacteria for agricultural use. *PLoS One*. 2019;14(5):e0217100. DOI: 10.1371/journal.pone.0217100

Mortula, M. M., Atabay, S., Fattah, K. P., & Madbully, A. (2021). Leachability of microplastic from different plastic materials. *Journal of Environmental Management*, 294, 112995. Retrieved from <https://doi.org/10.1016/j.jenvman.2021.112995>.

Muhonja, C. N., Huxley Makonde, Gabriel Magoma, and Mabel Imbuga. 2018. 'Biodegradability of polyethylene by bacteria and fungi from Dandora dumpsite Nairobi-Kenya', *PloS one*, 13: e0198446.

Murphy F, Ewins C, Carbonnier F, Quinn B. Wastewater Treatment Works (WwTW) as a Source of Microplastics in the Aquatic Environment. *Environ Sci Technol*. 2016;50:

5800–5808. doi:10.1021/acs.est.5b05416

- Na, S. H., Min-Ji Kim, Jun-Tae Kim, Seongpil Jeong, Seunghak Lee, Jaeshik Chung, Eun-Ju Kim, Microplastic removal in conventional drinking water treatment processes: Performance, mechanism, and potential risk, *Water Research*, Volume 202, 2021, 117417, ISSN 0043-1354, <https://doi.org/10.1016/j.watres.2021.117417>.
- Nabi, I., Li, K., Cheng, H., Wang, T., Liu, H., Ajmal, S., Yang, Y., Feng, Y., Zhang, L., “ Complete photocatalytic mineralization of microplastic on TiO₂ nanoparticle film”, *Science*, (2020) 23, (7), 101326
- Nayanashree G, Tyhippeswam B. Natural rubber degradation by laccase and manganese peroxidase enzymes of *Penicillium chrysogenum*. *International Journal of Environmental Science and Technology*. 2015;12:2665-2672. DOI: 10.1007/s13762-014-0636-6
- Negrete Velasco A, Ramseier Gentile S, Zimmermann S, Stoll S. Contamination and Removal Efficiency of Microplastics and Synthetic Fibres in a Conventional Drinking Water Treatment Plant. *Frontiers in Water*. 2022;4. doi:10.3389/frwa.2022.835451
- Nolte TM, Hartmann NB, Kleijn JM, Garnæs J, van de Meent D, Hendriks AJ, Baun A (2017) The toxicity of plastic nanoparticles to green algae as influenced by surface modification, medium hardness and cellular adsorption. *Aquat Toxicol* 183:11–20. <https://doi.org/10.1016/j.aquatox.2016.12.005>
- Nunes M D, Da Luz JMR, Paes AS, Torres DP, Kasuya MCM. *Jatropha* seed cake supplementation for improved fungal growth and later use as animal feed. *African Journal of Microbiology Research*. 2014;8:3457

Oberbeckmann, S., Martin G.J. Loeder, Gunnar Gerds, A. Mark Osborn Author Notes,

Spatial and seasonal variation in diversity and structure of microbial biofilms on marine plastics in Northern European waters, *FEMS Microbiology Ecology*, Volume 90, Issue 2, November 2014, Pages 478–492

Ojha N, Pradhan N, Singh S, Barla A, Shrivastava A, Khatua P, *et al.* Evaluation of HDPE and LDPE degradation by fungus, implemented by statistical optimization. *Nature Scientific Reports*. 2017;7:39515

Oliveira J, Belchior A, da Silva VD, Rotter A, Petrovski Ž, Almeida PL, Lourenço ND and Gaudêncio SP (2020) Marine Environmental Plastic Pollution: Mitigation by Microorganism Degradation and Recycling Valorization. *Front. Mar. Sci.* 7:567126. doi: 10.3389/fmars.2020.567126

Oliveira S F, Da Luz JMR, Kasuya MCM, Ladeira, LO, Correa AJ. Enzymatic extract containing lignin peroxidase immobilized on carbon nanotubes: Potential biocatalyst in dye decolourization. *Saudi Journal of Biological Sciences*. 2018, Vol. 25, pp. 651-659

Oliveira, J., Belchior, Afonso, da Silva, Veronica, Rotter, Ana, Petrovski, Zeljko, De Almeida, Pedro, Lourenco, Nidia and Gaudencio, Susana. (2020). Marine Environmental Plastic Pollution: Mitigation by Microorganism Degradation and Recycling Valorization. *Frontiers in Marine Science*. 7. 10.3389/fmars.2020.567126.

Osman, A. I., Mehta, N., Elgarahy, A.M. *et al.* Conversion of biomass to biofuels and life cycle assessment: a review. *Environ Chem Lett* 19, 4075–4118 (2021).
<https://doi.org/10.1007/s10311-021-01273-0>

Oßmann B E. Microplastics in drinking water? Present state of knowledge and open questions.

Current Opinion in Food Science. 2021;41: 44–51. doi:10.1016/j.cofs.2021.02.011

Paço, A., Kátia Duarte, João P da Costa, Patrícia SM Santos, Rita Pereira, ME Pereira, Ana C

Freitas, Armando C Duarte, and Teresa AP Rocha-Santos. 2017. 'Biodegradation of polyethylene microplastics by the marine fungus *Zalerion maritimum*', Science of The Total Environment, 586: 10-15.

Park, S. Y, and Kim, C. G., 2019. 'Biodegradation of micro-polyethylene particles by bacterial colonization of a mixed microbial consortium isolated from a landfill site', Chemosphere, 222: 527-33.

Pathak, V.M., Navneet Review on the current status of polymer degradation: a microbial approach. Bioresour. Bioprocess. 4, 15 (2017). <https://doi.org/10.1186/s40643-017-0145-9>

Peng C, Wang J, Liu X, Wang L. Differences in the Plastispheres of Biodegradable and Non-biodegradable Plastics: A Mini Review. Front Microbiol. 2022 Apr 25;13:849147. doi: 10.3389/fmicb.2022.849147. PMID: 35547108; PMCID: PMC9082994.

Perren, W., Wojtasik, A. and Cai, Q. (2018) 'Removal of microbeads from wastewater using electrocoagulation', *ACS omega*, 3(3), pp. 3357–3364.

Persat A, Nadell C D, Kim MK, Ingremeau F, Siryaporn A, Drescher K, *et al.* The mechanical world of bacteria. Cell. 2015;161(5):988-997. DOI: 10.1016/j.cell.2015.05.005

Pinto, M.; Langer, T.M.; Hüffer, T.; Hofmann, T.; Herndl, G.J. The composition of bacterial communities associated with plastic biofilms differs between different polymers and

stages of biofilm succession. PLoS ONE 019, 14, e0217165.

Plastics Europe, 2020. Plastics - the Facts 2020. An analysis of European plastics production, Demand and Waste Data Available online at <https://www.plasticseurope.org/en/resources/publications/4312-plastics-facts-2020>.

Raghavendra, V. R., Uzma, M., Govindappa, M., Vasantha, R. A., and Lokesh, S., Screening and identification of polyurethane(PU) and low density polyethylene(LDPE) degrading soil fungi isolated from municipal solid waste, July 2016, International Journal of Current Research 8(07):34753-34761.

Rajala, K., Outi Grönfors, Mehrdad Hesampour, Anna Mikola, Removal of microplastics from secondary wastewater treatment plant effluent by coagulation/flocculation with iron, aluminum and polyamine-based chemicals, Water Research, Volume 183, 2020, 116045, ISSN 0043-1354, <https://doi.org/10.1016/j.watres.2020.116045>.

Ranade V. V. and V. M. Bhandari (2014), Industrial wastewater treatment, recycling and reuse, Elsevier Inc., 560p, ISBN#s 9780444634030, 978008099968, Jul 2014.

Renner L D, Weibel DB (2011) Physicochemical regulation of biofilm formation. MRS Bull 36

Restrepo-Florez, J.M.; Bassi, A.; Thompson, M.R. Microbial degradation and deterioration of polyethylene—A review. Int. Biodeterior. Biodegrad. 2014, 88, 83–90

Rhodes, C.J. Solving the plastic problem: From cradle to grave, to reincarnation. Sci. Prog. 2019, 102, 218–248.

Ricardo, I. A., Alberto, E. A., Silva Junor, A. H., Macuvele, D.L.P., Padoin, N., Soares, C., Riella, H. G., Starling, M. C., Troro, A. G., “ A critical review on microplastics ,

- interaction with organic and inorganic pollutants, impacts and effectiveness of advanced oxidation processes applied for their removal from aqueous matrices”, *Chemical Engineering Journal*, (2021) 424, 130282
- Rios, L. M., Moore, C. and Jones, P. R., 2007, Persistent organic pollutants carried by synthetic polymers in the ocean environment, *August 2007*, 54(8):1230-7.
- Robyn J. Wright, Gabriel Erni-Cassola, Vinko Zadjelovic, Mira Latva, and Joseph A. Christie-Oleza *Environmental Science & Technology* 2020 54 (19), 11657-11672 DOI: 10.1021/acs.est.0c02305
- Russell J R, Huang J, Anand P, Kucera K, Sandoval AG, Dantzler KW, Hickman D, Jee J, Kimovec FM, Koppstein D (2011) Biodegradation of polyester polyurethane by endophytic fungi. *Appl Environ Microbiol* 77(17):6076–6084
- Sánchez, C. Fungal potential for the degradation of petroleum-based polymers: An overview of macro-and microplastics biodegradation. *Biotechnol. Adv.* 2020, 40, 107501.
- Santo M, Weitsman R, Sivan A. The role of the copper-binding enzyme-laccase-in the biodegradation of polyethylene by the actinomycete *Rhodococcus ruber*. *International Biodeterioration and Biodegradation*. 2013;84:204-210
- Sato S, Saika A, Shinozaki Y, Watanabe T, Suzuki K, Sameshima-Yamashita Y, *et al.* Degradation profiles of biodegradable plastic films by biodegradable plastic-degrading enzymes from the yeast *Pseudozyma antarctica* and the fungus *Paraphoma* sp. B47-9. *Polymer Degradation and Stability*. 2017;141:26-32
- Sen S. K and Raut S (2015) Microbial degradation of low density polyethylene (LDPE): a

review. *J Environ Chem Eng* 3(1):462–473

Sengupta D., Pike R.W. (2015) Chemicals from Biomass. In: Chen WY., Suzuki T., Lackner M. (eds) *Handbook of Climate Change Mitigation and Adaptation*. Springer, New York, NY.
https://doi.org/10.1007/978-1-4614-6431-0_28-2

Shah AA, Hasan F, Hameed A, Ahmed S. Biological degradation of plastics: A comprehensive review. *Biotechnology Advances*. 2008;26:246-265. DOI: 10.1016/j.biotechadv.2007.12.005

Shah, A.A.; Hasan, F.; Hameed, A.; Ahmed, S. Biological degradation of plastics: A comprehensive review. *Biotechnol. Adv.* 2008, 26, 246–265.

Stefan, M. I., *Advanced Oxidation Processes for Water treatment: Fundamentals and Applications*, IWA Publishing, 2017.

Shahi, N. K., Minsoo Maeng, Donghyun Kim, Seok Dockko, Removal behavior of microplastics using alum coagulant and its enhancement using polyamine-coated sand, *Process Safety and Environmental Protection*, Volume 141, 2020, Pages 9-17, ISSN 0957-5820, <https://doi.org/10.1016/j.psep.2020.05.020>.

Shen, M., Song, B., Zhu, Y., Zeng, G., Zhang, Y., Yang, Y., . . . Yi, H. (2020). Removal of microplastics via drinking water treatment: Current knowledge and future directions. *Chemosphere*, 251, 126612. Retrieved from <https://doi.org/10.1016/j.chemosphere.2020.126612>

Shen, M. *et al.* (2022) ‘Efficient removal of microplastics from wastewater by an electrocoagulation process’, *Chemical Engineering Journal*, 428, p. 131161.

Shruti V C, Pérez-Guevara F, Kutralam-Muniasamy G. Metro station free drinking water fountain- A potential “microplastics hotspot” for human consumption. *Environmental Pollution*. 2020;261: 114227. doi:10.1016/j.envpol.2020.114227

Siracusa V. Microbial Degradation of Synthetic Biopolymers Waste. *Polymers (Basel)*. 2019 Jun 20;11(6):1066. doi: 10.3390/polym11061066. PMID: 31226767; PMCID: PMC6630276.

Sivan A (2011) New perspectives in plastic biodegradation. *Curr Opin Biotechnol* 22(3):422–426. <https://doi.org/10.1016/j.copbio.2011.01.013>

Sowmya, H.V., Ramalingappa, B., Krishnappa, M., and Basaiah, T, Degradation of polyethylene by *Penicillium simplicissimum* isolated from local dumpsite of Shivamogga district, August 2015 *Environment Development and Sustainability* 17(4):731-745

Suhrhoff, T.J and Scholz-Böttcher, B. M., Qualitative impact of salinity, UV radiation and turbulence on leaching of organic plastic additives from four common plastics — A lab experiment, *Marine Pollution Bulletin*, Volume 102, Issue 1, 15 January 2016, Pages 84-94

Sumathi T, Viswanath B, Lakshmi AS, DVR SG. Production of laccase by *Cochliobolus* sp. isolated from plastic dumped soils and their ability to degrade low molecular weight PVC. Hindawi Publishing Corporation, *Biochemistry Research International*. 2016;9519527:1-10

Sundbæk, K. B., Due Würtzner Koch, I., Greve Villaro, C., Rasmussen, N. S., Løvstad Holdt, S., & Hartmann, N. B. (2018). Sorption of fluorescent polystyrene microplastic particles

to edible seaweed *Fucus vesiculosus*. *Journal of Applied Phycology*, 30(5), 2923–2927.

<https://doi.org/10.1007/s10811-018-1472-8>

Sussarellu R, Suquet M, Thomas Y, Lambert C, Fabioux C, Pernet MEJ, Le Goïc N, Quillien V,

Mingant C, Epelboin Y (2016) Oyster reproduction is affected by exposure to polystyrene

microplastics. *Proc Natl Acad Sci* 113(9):2430–2435. [https://](https://doi.org/10.1073/pnas.1519019113)

doi.org/10.1073/pnas.1519019113.

Suzuki, M.; Tachibana, Y.; Oba, K.; Takizawa, R.; Kasuya, K. ichi Microbial degradation of

poly(ϵ -caprolactone) in a coastal environment. *Polym. Degrad. Stab.* 2018, 149, 1–8.

Syranidou E, Karkanorachaki K, Amorotti F et al (2019) Biodegradation of mixture of plastic

films by tailored marine consortia. *J Hazard Mater* 375:33–42

Suhrhoff, T. J., B.M. Scholz-Bottcher, Qualitative impact of salinity, UV radiation and

turbulence on leaching of organic plastic additives from four common plastics—a lab

experiment, *Mar. Pollut. Bull.* 102 (1) (2016) 84–94.

Tachibana, K.; Urano, Y.; Numata, K. Biodegradability of nylon 4 film in a marine

environment.

Taghavi, N.; Zhuang, W.Q.; Baroutian, S. Enhanced biodegradation of non-biodegradable

plastics by UV radiation: Part 1. *J. Environ. Chem. Eng.* 2021, 9, 106464.

Talvitie J, Heinonen M, Pääkkönen JP, Vahtera E, Mikola A, Setälä O, Vahala R. Do

wastewater treatment plants act as a potential point source of microplastics? Preliminary

study in the coastal Gulf of Finland, Baltic Sea. *Water Sci Technol.* 2015;72(9):1495-504.

doi: 10.2166/wst.2015.360. PMID: 26524440.

Talvitie, J., Anna Mikola, Arto Koistinen, Outi Setälä, Solutions to microplastic pollution –

Removal of microplastics from wastewater effluent with advanced wastewater treatment technologies, *Water Research*, Volume 123, 2017, Pages 401-407, ISSN 0043-1354, <https://doi.org/10.1016/j.watres.2017.07.005>.

Tamoor M, Samak NA, Jia Y, Mushtaq MU, Sher H, Bibi M, Xing J. Potential Use of Microbial Enzymes for the Conversion of Plastic Waste Into Value-Added Products: A Viable Solution. *Front Microbiol.* 2021 Nov 30;12:777727. doi: 10.3389/fmicb.2021.777727. PMID: 34917057; PMCID: PMC8670383.

Teixeira, S.; Eblagon, K.M.; Miranda, F.; R. Pereira, M.F.; Figueiredo, J.L. Towards Controlled Degradation of Poly(lactic) Acid in Technical Applications. *C* 2021, 7, 42. <https://doi.org/10.3390/c7020042>

Temporiti, M. E. E.; Nicola, L.; Nielsen, E.; Tosi, S. Fungal Enzymes Involved in Plastics Biodegradation. *Microorganisms* 2022, 10, 1180. <https://doi.org/10.3390/microorganisms10061180>

Ter Halle A, Ladirat L, Gendre X, Goudounèche D, Pusineri C, Routaboul C, Tenailleau C, Duployer B, Perez E (2016) Understanding the fragmentation pattern of marine plastic debris. *Environ Sci Technol* 50(11):5668–5675. <https://doi.org/10.1021/acs.est.6b00594>

Tiwari, Neha, Deenan Santhiya, and Jai Gopal Sharma. 2020. 'Microbial remediation of micro-nano plastics: Current knowledge and future trends', *Environmental Pollution*, 265: 115044.

Tofa, T. S., F. Ye, K.L. Kunjali, J. Dutta, Enhanced visible light photodegradation of

- microplastic fragments with plasmonic platinum/zinc oxide nanorod photocatalysts, *Catalysts* 9 (10) (2019) 819.
- Urbanek, A. K.; Rymowicz, W.; Strzelecki, M.C.; Kociuba, W.; Franczak, Ł.; Mirończuk, A.M. Isolation and characterization of Arctic microorganisms decomposing bioplastics. *AMB Express* 2017, 7, 148.
- Vedrtnam, A.; Kumar, S.; Chaturvedi, S. Experimental study on mechanical behavior, biodegradability, and resistance to natural weathering and ultraviolet radiation of wood-plastic composites. *Compos. B. Eng.* 2019, 176, 107282.
- Vertommen, M.A.M.E.; Nierstrasz, V.A.; van der Veer, M.; Warmoeskerken, M.M.C.G. Enzymatic surface modification of poly (ethylene terephthalate). *J. Biotechnol.* 2005, 120, 376–386.
- Wahyuningtyas, N.; Suryanto, H. Analysis of Biodegradation of Bioplastics Made of Cassava Starch. *J. Mech.Eng. Sci. Technol.* 2017, 1, 24–31.
- Wang J, Qin X, Guo J, Jia W, Wang Q, Zhang M, *et al.* Evidence of selective enrichment of bacterial assemblages and antibiotic resistant genes by microplastics in urban rivers. *Water Research.* 2020;183: 116113. doi:10.1016/j.watres.2020.116113
- Wang S, Xue N, Li W, Zhang D, Pan X, Luo Y. Selectively enrichment of antibiotics and ARGs by microplastics in river, estuary and marine waters. *Science of The Total Environment.* 2020;708: 134594. doi:10.1016/j.scitotenv.2019.134594
- Wang W, Gao H, Jin S, Li R, Na G. The ecotoxicological effects of microplastics on aquatic food web, from primary producer to human: A review. *Ecotoxicology and Environmental*

Safety. 2019;173: 110–117. doi:10.1016/j.ecoenv.2019.01.113

Wang, J. C., Wang, H., Huang, L. I., Wang, C. Q., “ Surface treatment with Fenton for separation of acrylonitrile-butadiene-styrene and polyvinylchloride waste plastic by flotation”, *Waste Management*, (2017), 67, 20-26

Webb, H.; Arnott, J.; Crawford, R.; Ivanova, E. Plastic degradation and its environmental implications with special reference to poly(ethylene terephthalate). *Polymers* 2013, 5, 1.

Wei R, Zimmermann W. Microbial enzymes for the recycling of recalcitrant petroleum-based plastics: how far are we? *Microb Biotechnol.* 2017 Nov;10(6):1308-1322. doi: 10.1111/1751-7915.12710. Epub 2017 Mar 28. PMID: 28371373; PMCID: PMC5658625.

WHO, Microplastics in drinking-water. Geneva: World Health Organization; 2019. Available: https://scholar.google.com/scholar_lookup?title=Microplastics%20in%20drinking-water&author=WHO&publication_year=2019

Wu X, Pan J, Li M et al (2019) Selective enrichment of bacterial pathogens by microplastic biofilm. *Water Res* 165:114979

Xiong, Y. *et al.* (2020) ‘Interfacial interaction between micro/nanoplastics and typical PPCPs and nanoplastics removal via electrosorption from an aqueous solution’, *Water Research*, 184, p. 116100.

Xiong X, Siddique MS, Graham NJD, Yu W. Towards microplastics contribution for membrane biofouling and disinfection by-products precursors: The effect on microbes. *Journal of Hazardous Materials.* 2022;426. doi:10.1016/j.jhazmat.2021.127797

- Xu, R. *et al.* (2022) 'Removal of microplastics and attached heavy metals from secondary effluent of wastewater treatment plant using interpenetrating bipolar plate electrocoagulation', *Separation and Purification Technology*, 290, p. 120905.
- Xue, J., Peldszus, S., van Dyke, M. I., & Huck, P. M. Removal of polystyrene microplastic spheres by alum-based coagulation-flocculation-sedimentation (CFS) treatment of surface waters. *Chemical Engineering Journal*, 2021, 422. <https://doi.org/10.1016/j.cej.2021.130023>
- Yang Y, Liu G, Song W, Ye C, Lin H, Li Z, *et al.* Plastics in the marine environment are reservoirs for antibiotic and metal resistance genes. *Environment International*. 2019;123: 79–86. doi:10.1016/j.envint.2018.11.061
- Yoon M G, Jeon HJ, Kim MN (2012) Biodegradation of Polyethylene by a Soil Bacterium and AlkB Cloned Recombinant Cell. *J Bioremed Biodegrad* 3:145. doi: 10.4172/2155-6199.1000145
- Yoshida, S., Kazumi Hiraga, Toshihiko Takehana, Ikuo Taniguchi, Hironao Yamaji, Yasuhito Maeda, Kiyotsuna Toyohara, Kenji Miyamoto, Yoshiharu Kimura, Kohei Oda, A bacterium that degrades and assimilates poly(ethylene terephthalate), *Science*, 2016 Mar, 11;351(6278):1196-9. doi: 10.1126/science.aad6359.
- Yuan, J., Jie Ma, Yiran Sun, Tao Zhou, Youcai Zhao, and Fei Yu. 2020. 'Microbial degradation and other environmental aspects of microplastics/plastics', *Science of The Total Environment*, 715: 136968.
- Yusuf, A., Sodiq, A., Giwa, A., Eke, J., Pikuda, O., Eniola, J. O., . . . Bilad, M. R. (2022).

- Updated review on microplastics in water, their occurrence, detection, measurement, environmental pollution, and the need for regulatory standards. *Environmental Pollution*, 292, 118421. Retrieved from <https://doi.org/10.1016/j.envpol.2021.118421>
- Zafar, R., S.Y. Park, C.G. Kim, Surface modification of polyethylene microplastic particles during the aqueous phase ozonation process, *Environ. Eng. Res.* 26 (5) (2021).
- Zambrano, M. C., Pawlak, J. J., and Venditti, R. A. (2020). "Effects of chemical and morphological structure on biodegradability of fibers, fabrics, and other polymeric materials," *BioRes.* 15(4), 9786-9833.
- Zeenat, A.E., Dilara Abbas Bukhari, Saba Shamim, Abdul Rehman. Plastics degradation by microbes: A sustainable approach, *Journal of King Saud University - Science*, Volume 33, Issue 6, 2021, 101538, ISSN 1018-3647, <https://doi.org/10.1016/j.jksus.2021.101538>
- Zeghal E, Vaksmaa A, Vielfaure H, Boekhout T and Niemann H (2021) The Potential Role of Marine Fungi in Plastic Degradation – A Review. *Front. Mar. Sci.* 8:738877. doi: 10.3389/fmars.2021.738877
- Zhang J, Gao D, Li Q, Zhao Y, Li L, Lin H, Bi Q, Zhao Y (2020) Biodegradation of polyethylene microplastic particles by the fungus *Aspergillus flavus* from the guts of wax moth *Galleria mellonella*. *Sci Total Environ* 704:135931
- Zhang X, Chen J, Li J. The removal of microplastics in the wastewater treatment process and their potential impact on anaerobic digestion due to pollutants association. *Chemosphere.* 2020a;251: 126360. doi:10.1016/j.chemosphere.2020.126360
- Zhang, Junqing, Danling Gao, Quanhao Li, Yixuan Zhao, Li Li, Hanfeng Lin, Qirui Bi, and

Yucheng Zhao. 2020. 'Biodegradation of polyethylene microplastic particles by the fungus *Aspergillus flavus* from the guts of wax moth *Galleria mellonella*', *Science of The Total Environment*, 704: 135931.

Zhang, Y., Jiang, H., Bian, K., Wang, H., & Wang, C. (2021). A critical review of control and removal strategies for microplastics from aquatic environments. *Journal of Environmental Chemical Engineering*, 9, 105463. Retrieved from <https://doi.org/10.1016/j.jece.2021.105463>.

Zhou, L., T. Wang, G. Qu, H. Jia, L. Zhu, Probing the aging processes and mechanisms of microplastic under simulated multiple actions generated by discharge plasma, *J. Hazard. Mater.* 398 (2020), 122956.

Zuccarello P, Ferrante M, Cristaldi A, Copat C, Grasso A, Sangregorio D, *et al.* Exposure to microplastics (<10 µm) associated to plastic bottles mineral water consumption: The first quantitative study. *Water Research*. 2019;157: 365–371. doi:10.1016/j.watres.2019.03.091

Table 1. Review of key aspects (MP description, treatment process) of studies evaluating efficiency of MPs removal via coagulation method

Reference	Size of MP	Coagulant(s)	Optimal conditions	Removal efficiency
Zhang <i>et al.</i> (2021)	< 270 micrometers	Magnetic magnesium hydroxide	200 mg/L of Mg(OH) ₂ , 120 mg/L of Fe ₃ O ₄ (to synthesize magnetic magnesium hydroxide), 5 mg/L of PAM	93.8%
Zhang <i>et al.</i> (2022)	50-1000 nm	PAC and PAM	400 mg/L of PAC, 20 mg/L of PAM, and pH of 8	98.5%
Na <i>et al.</i> (2021)	10-90 micrometers	Aluminum chloride and iron chloride	Aluminum chloride as coagulant	100% for MP > 20 micrometers
Rajala <i>et al.</i> (2020)		Ferric chloride, PAC and PAM	Ferric chloride and PAC ideal coagulants	99.4%
Xue <i>et al.</i> (2021)	3-90 micrometers	Alum		> 80% for MPs < 25 micrometers
Shahi <i>et al.</i> (2020)	10-100 micrometers	Alum with PC sand	20 mg/L of alum and 500 mg/L of PC sand	92.7%

Table 2. Overview of Micro and Nano Plastics (MNPs) reported as being biodegraded by bacteria

MNPs	Shape & size	Bacteria strain	Sample type	Analysis method	Test duration	Weight loss %	Reference
Low density polyethylene (LDPE)	Sheets	<i>Bacillus cereus</i> strain A5,a, <i>Brevibacillus borstelensis</i> strain B2,2,	Soil	Weight loss%, FTIR, GC-MS	16 weeks	<i>Bacillus cereus</i> : 35.7% <i>Brevibacillus borstelensis</i> : 20.3%	(Muhonja <i>et al.</i> 2018)
Polyethylene (PE), Polyethylene terephthalate (PET), Polypropylene (PP), Polystyrene (PS)	Grating and cutting of commercial plastics, <250um	<i>Bacillus cereus</i> , <i>Bacillus gottheilii</i>	Sediment	Weight loss%, FTIR, SEM	40 days	<i>Bacillus cereus</i> : PE 1.6%, PET 6.6%, PS 7.4% <i>Bacillus gottheilii</i> : PE 6.2%, PET 3.0%, PP 3.6%, PS 5.8%	(Auta, Emenike, and Fauziah 2017)
Polyethylene (PE)	Granules, 40 – 600um	Mesophilic mixed bacterial: <i>Bacillus sp.</i> and <i>Paenibacillus sp.</i>	Landfill	Weight loss%, FTIR, FE-SEM, GC-MS, TGA	60 days	Weight loss 14.7%, Mean particle size decrease 22.8%	(Park and Kim 2019)
Polypropylene (PP)	Grating and cutting of commercial plastics, 1mm	<i>Pseudomonas sp.</i> ADL15, <i>Rhodococcus sp.</i> ADL36	Antarctic soil	Weight loss%, FTIR	40 days	ADL15 17.3%, ADL36 7.3%	(Habib <i>et al.</i> 2020)
Polyvinyl chloride (PVC)	By cooling grinding obtained 106–300 µm or < 106 µm particles	Engineered <i>P. aeruginosa</i>	Artificial seawater freshwater	Weight loss%, SEM, Raman micro-spectroscopy	24hrs	80% trapped PVC by biofilm	(Liu <i>et al.</i> 2021)

Figure 1. Schematic of processes and key stages in the cycling of (micro)plastics within aquatic environments, including key state-of-the-art removal or destruction methods reviewed herein

