



UNIVERSITY OF LEEDS

This is a repository copy of *Computational investigation of the structures and energies of microporous materials*.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/217677/>

Version: Supplemental Material

Article:

Stacey, E., Quesne, M.G. orcid.org/0000-0001-5130-1266 and Catlow, C.R.A. (2023) Computational investigation of the structures and energies of microporous materials. *Microporous and Mesoporous Materials*, 358. 112382. ISSN 1387-1811

<https://doi.org/10.1016/j.micromeso.2022.112382>

© 2022 Published by Elsevier Inc. This is an author produced version of an article published in *Microporous and Mesoporous Materials*. Uploaded in accordance with the publisher's self-archiving policy. This manuscript version is made available under the CC-BY-NC-ND 4.0 license <http://creativecommons.org/licenses/by-nc-nd/4.0/>

Reuse

This article is distributed under the terms of the Creative Commons Attribution-NonCommercial-NoDerivs (CC BY-NC-ND) licence. This licence only allows you to download this work and share it with others as long as you credit the authors, but you can't change the article in any way or use it commercially. More information and the full terms of the licence here: <https://creativecommons.org/licenses/>

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.



eprints@whiterose.ac.uk
<https://eprints.whiterose.ac.uk/>

Supporting Information

Computational Investigation of The Structures and Energies of Microporous Materials

Edward Stacey ^{a,b*}, Matthew G. Quesne ^{a,b}, C. Richard A. Catlow ^{a,b,c}

^a School of Chemistry, Cardiff University, Main Building, Park Place, Cardiff CF10 3AT, UK

^b UK Catalysis Hub, Research Complex at Harwell, STFC Rutherford Appleton Laboratory, Didcot, Oxfordshire OX11 0FA, UK

^c Department of Chemistry, University College London, 20 Gordon St., London WC1 HOAJ, UK.

	2Å	3Å	4Å	5Å	6Å	7Å	8Å	9Å	
Quartz Energy for Reference	-17453.42	-16498.63	-16620.56	-16756.95	-16818.48	-16848.92	-16871.17	-16882.45	
Energy Difference from Quartz for Different Cut-offs / kJ									
Structure	2Å	3Å	4Å	5Å	6Å	7Å	8Å	9Å	EXP /kJ
AST-FW	1.58	1.38	19.07	37.99	42.59	46.77	50.15	51.55	10.9
BEA-FW	3.74	5.48	13.73	30.03	37.44	41.56	46.12	47.93	9.3
CIT-5	-1.43	-3.37	16.85	25.47	30.32	32.69	36.90	38.58	8.8
CHA	5.66	8.48	19.53	37.98	49.04	53.33	57.61	59.52	11.4
ITQ-4	4.95	8.32	15.51	31.49	37.48	41.64	45.35	46.96	10
ITQ-7	4.80	8.14	17.59	34.46	41.37	45.76	50.31	52.20	14.4
ITQ-3	3.09	3.89	14.98	32.53	40.61	44.21	48.46	50.25	10.1
ZSM-11	-0.09	-1.51	13.56	22.51	29.87	32.70	36.68	37.92	8.2
ZSM-5	-0.96	-3.02	12.79	22.20	28.50	31.38	35.26	36.46	6.8
ITQ-1	3.49	4.88	17.52	27.65	36.65	39.78	43.74	45.27	10.4
SSZ-23	2.66	3.91	16.28	30.59	38.91	42.63	46.68	48.29	9.2
AFI-FW	-0.61	-1.93	23.85	28.97	29.38	32.02	36.78	38.05	7.2
EMT-FW	8.34	13.34	18.32	43.40	53.06	57.17	61.38	63.63	10.5
FER-FW	0.19	-0.79	15.38	21.56	30.08	32.59	36.46	37.20	6.6
ZSM-18	8.40	13.57	22.19	40.46	49.27	54.24	58.74	60.82	13.9
ZSM-12	-2.06	-4.89	11.96	21.99	26.00	28.58	32.24	33.45	8.7

Table S1. Van Beest Cut-Off Parameter Benchmarks

Structure	Normalised Lattice Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Lattice Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Lattice Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Lattice Energy /kJ	Normalised ΔE Quartz /kJ
Quartz	-12418.0	0	JSW-FW	-12401.5	16.5	GME-FW	-12401.5	16.5	LTJ-FW	-12403.3	14.8
ITQ-33	-12398.2	19.8	ABW-FW	-12405.5	11.9	LOS-FW	-12404.1	13.9	LTL-FW	-12399.9	18.1
CIT-5	-12405.4	12.7	ANA-FW	-12404.3	13.7	FRA-FW	-12404.4	13.6	MAR-FW	-12404.2	13.1
CIT-7	-12401.3	15.2	DON-FW	-12407.8	10.2	LTF-FW	-12401.1	19.3	MEP-FW	-12405.8	12.2
EDI-FW	-12395.2	22.8	BIK-FW	-12406.7	7.2	MAPO-39-FW	-12405.3	12.7	MER-FW	-12401.8	16.3
ITQ-12	-12403.1	14.9	LOV-FW	-12393.1	24.9	STA-6-FW	-12402.1	15.9	MON-FW	-12403.2	14.9
AEN-FW	-12405.8	12.2	MOZ-FW	-12400.3	17.7	STA-15-FW	-12407.6	10.4	MOR-FW	-12405.7	12.3
SAPO-40-FW	-12401.2	16.8	MWW-FW	-12403.6	14.4	SIZ-7-FW	-12402.6	15.4	MSO-FW	-12406.0	12.0
ACO-FW	-12399.5	18.5	SAPO-31-FW	-12407.9	10.1	DAC-FW	-12405.7	12.3	BEA-FW	-12403.6	14.4
ITQ-13-FW	-12405.5	12.5	SAPO-56-FW	-12401.6	16.4	EPI-FW	-12404.5	13.5	BRE-FW	-12404.3	13.3
ITQ-22	-12404.1	13.9	VFI-FW	-12398.4	19.5	DOH-FW	-12407.4	10.6	CAN-FW	-12404.1	13.9
ITQ-24-FW	-12402.4	15.6	ZSM-12	-12409.8	8.2	EAB-FW	-12401.6	16.4	CAS-FW	-12407.1	11.0
ITQ-3	-12403.9	14.1	AEL-FW	-12407.9	11.0	EMT-FW	-12397.9	20.1	NAT-FW	-12395.6	22.4
ITQ-34-FW	-12405.5	12.5	AHT-FW	-12397.2	20.8	EON-FW	-12403.0	13.0	NES-FW	-12402.2	15.9
ITQ-38-FW	-12403.8	14.2	ITQ-33-FW	-12398.2	19.8	ERI-FW	-12401.6	16.4	OFF	-12401.2	16.8
ITQ-4	-12403.0	15.0	ITQ-39-FW	-12383.1	36.2	ERS-7	-12404.5	13.5	PHI-FW	-12402.3	15.7

ITQ-49-FW	-12400.5	17.6	ITQ-44-FW	-12393.2	24.8	ETR-FW	-12396.9	21.1	PST-21	-12402.0	16.0
ITQ-50	-12398.7	19.3	GOO-FW	-12398.9	19.1	FAR-FW	-12404.3	13.7	PST-22	-12403.0	15.0
ITQ-52	-12404.2	13.8	GUS-1	-12406.2	9.1	HEU-FW	-12405.5	12.5	RHO-FW	-12399.7	18.3
ITQ-7	-12401.6	16.4	FER-FW	-12404.1	11.8	JBW-FW	-12407.0	11.0	ITQ-26-FW	-12400.5	15.2
ZSM-5	-12408.3	9.7	AFG-FW	-12399.0	13.9	JOZ-FW	-12384.4	33.6	AFY-FW	-12390.7	27.3
ZON-FW	-12401.5	16.6	AFS-FW	-12404.0	19.0	KFI-FW	-12400.8	17.3	ZSM-18	-12399.2	18.9
MAPO-36	-12405.1	12.9	BOG-FW	-12398.8	14.0	LAU-FW	-12403.8	14.2	ZSM-11	-12407.3	10.8
WEI-FW	-12383.4	34.6	BPH-FW	-12403.0	19.2	LEV-FW	-12402.0	16.0	EWS-FW	-12401.4	16.6
JNT-FW	-12399.2	18.8	GIS-FW	-12404.2	15.0	LIO-FW	-12404.1	13.9	NAB-FW	-12385.2	32.8
DFT-FW	-12403.2	14.8	GIU-FW	-12398.9	13.8	LTA-FW	-12398.7	19.3	LTJ-FW	-12403.3	14.8
AST-FW	-12399.9	18.1	CHA	-12401.9	16.1	SSZ-23	-12403.3	14.7	AFI-FW	-12406.1	11.9

Table S2. Zeolite Lattice Energies: Shell Model Potentials

Framework	Normalised Energy /kJmol ⁻¹	ΔE Berlinite /kJ
Berlinite	-12938.8	0
ITQ-51	-12929.1	9.8
ALPO-C	-12929.8	9.0
ALPO-12	-12929.1	9.8
ALPO-5	-12932.1	6.8
ALPO-11	-12929.7	9.1
ALPO-18	-12928.0	10.8
VPI-5	-12926.2	12.6
ALPO-41	-12933.1	5.7
ALPO-8	-12928.1	10.8
ALPO-D	-12931.0	7.8
SAPO-56	-12928.2	10.6
STA-20	-12927.9	11.0
UiO-6	-12933.4	5.4
STA-1	-12924.9	13.9
PST-14	-12925.5	13.3
ALPO-16	-12926.5	12.4
SAPO-42	-12925.9	12.9

Table S3. Interatomic Potential ALPO Lattice Energies

Structure	Normalised Cohesive Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Cohesive Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Cohesive Energy /kJ	Normalised ΔE Quartz /kJ	Structure	Normalised Cohesive Energy /kJ	Normalised ΔE Quartz /kJ
Quartz	-2314.9	0	JSW-FW	-2303.7	11.2	GME-FW	-2302.7	10.9	LTJ-FW	-2303.5	11.4
ITQ-33	-2300.3	14.5	ABW-FW	-2304.6	10.3	LOS-FW	-2303.8	10.9	LTL-FW	-2304.0	10.8
CIT-5	-2303.0	11.9	ANA-FW	-2305.0	9.9	FRA-FW	-2304.0	9.6	MAR-FW	-2304.0	10.9
CIT-7	-2303.2	11.7	DON-FW	-2305.8	9.1	LTF-FW	-2303.9	11.0	MEP-FW	-2305.2	9.6
EDI-FW	-2298.7	16.1	BIK-FW	-2305.2	9.6	MAPO-39-FW	-2305.3	9.5	MER-FW	-2303.2	11.6
ITQ-12	-2304.1	10.7	LOV-FW	-2299.7	15.1	STA-6-FW	-2303.6	11.2	MON-FW	-2305.1	9.7
AEN-FW	-2304.1	10.8	MOZ-FW	-2303.9	11.0	STA-15-FW	-2307.1	7.8	MOR-FW	-2305.1	8.2
SAPO-40-FW	-2302.7	12.1	MWW-FW	-2303.7	11.1	SIZ-7-FW	-2303.3	11.5	MSO-FW	-2306.7	11.0
ACO-FW	-2301.8	13.1	SAPO-31-FW	-2306.7	8.2	DAC-FW	-2304.9	10.0	BEA-FW	-2303.9	10.8
ITQ-13-FW	-2305.2	9.7	SAPO-56-FW	-2302.7	12.2	EPI-FW	-2304.5	10.4	BRE-FW	-2304.7	10.2
ITQ-22	-2304.0	10.8	VFI-FW	-2297.9	16.9	DOH-FW	-2303.9	11.1	CAN-FW	-2303.8	11.0
ITQ-24-FW	-2303.5	11.4	ZSM-12	-12409.8	8.2	EAB-FW	-2303.4	11.0	CAS-FW	-2305.5	9.4
ITQ-3	-2304.2	10.7	AEL-FW	-2306.5	8.4	EMT-FW	-2301.9	11.5	NAT-FW	-2298.7	16.2
ITQ-34-FW	-2305.2	9.7	AHT-FW	-2298.6	16.3	EON-FW	-2304.4	12.9	NES-FW	-2301.0	13.9
ITQ-38-FW	-2303.6	11.2	ITQ-33-FW	-2303.6	14.5	ERI-FW	-2303.4	10.5	OFF	-2303.4	11.5
ITQ-4	-2304.6	10.3	ITQ-39-FW	-2304.6	8.8	ERS-7	-2304.6	10.3	PHI-FW	-2303.3	11.6
ITQ-49-FW	-2302.7	12.2	ITQ-44-FW	-2302.7	16.6	ETR-FW	-2301.5	13.3	PST-21	-2303.0	11.8
ITQ-50	-2301.3	13.6	GOO-FW	-2300.2	14.6	FAR-FW	-2304.9	10.0	PST-22	-2303.9	11.0
ITQ-52	-2304.1	10.8	GUS-1	-2307.5	7.4	HEU-FW	-2305.1	9.8	RHO-FW	-2302.3	12.6

ITQ-7	-2301.5	11.7	FER-FW	-2305.3	9.6	JBW-FW	-2305.8	9.1	ITQ-26-FW	-2301.6	13.3
ZSM-5	-2306.7	8.2	AFG-FW	-2303.9	11.0	JOZ-FW	-2296.2	18.6	AFY-FW	-2295.8	19.0
ZON-FW	-2303.2	11.6	AFS-FW	-2302.1	12.9	KFI-FW	-2302.7	12.2	ZSM-18	-2301.9	13.0
MAPO-36	-2305.0	9.8	BOG-FW	-2304.5	10.40	LAU-FW	-2304.9	10.0	ZSM-11	-2305.7	9.1
WEI-FW	-2295.9	18.9	BPH-FW	-2301.9	13.0	LEV-FW	-2303.4	11.5	EWS-FW	-2302.3	12.5
JNT-FW	-2301.9	12.9	GIS-FW	-2303.4	11.5	LIO-FW	-2303.5	11.3	NAB-FW	-2296.6	18.2
DFT-FW	-2303.7	11.2	GIU-FW	-2304.1	10.8	LTA-FW	-2301.6	13.3	LTJ-FW	-2303.5	11.4
AST-FW	-2302.2	12.7	CHA	-2302.7	12.2	SSZ-23	-2303.5	11.4	AFI-FW	-2305.0	10.0

Table S4. DFT Zeolite Cohesive Energies

Framework	Normalised Energy /kJmol ⁻¹	ΔE Berlinite /kJ
Berlinite	-2192.5	0
ITQ-51	-2182.2	10.3
ALPO-C	-2181.2	11.3
ALPO-12	-2180.1	12.4
ALPO-5	-2181.6	10.8
ALPO-11	-2181.6	10.9
ALPO-18	-2179.1	13.3
VPI-5	-2178.0	14.5
ALPO-41	-2183.0	9.5
ALPO-8	-2182.1	10.4
ALPO-D	-2183.0	9.5
SAPO-56	-2179.3	13.1
STA-20	-2180.1	12.4
UiO-6	-2184.1	8.3
STA-1	-2177.9	14.6
PST-14	-2178.5	14.0
ALPO-16	-2178.3	14.2
SAPO-42	-2178.6	13.9

Table S5. DFT ALPO Cohesive Energies