



UNIVERSITY OF LEEDS

This is a repository copy of *Editorial*.

White Rose Research Online URL for this paper:
<http://eprints.whiterose.ac.uk/135500/>

Version: Accepted Version

Article:

Bernal, SA orcid.org/0000-0002-9647-3106 (2018) Editorial. Proceedings of the Institution of Civil Engineers - Construction Materials, 171 (4). p. 133. ISSN 1747-650X

<https://doi.org/10.1680/jcoma.2018.171.4.133>

© ICE Publishing, all rights reserved. This is an author produced version of a paper published in Proceedings of the Institution of Civil Engineers - Construction Materials. Uploaded in accordance with the publisher's self-archiving policy.

Reuse

Items deposited in White Rose Research Online are protected by copyright, with all rights reserved unless indicated otherwise. They may be downloaded and/or printed for private study, or other acts as permitted by national copyright laws. The publisher or other rights holders may allow further reproduction and re-use of the full text version. This is indicated by the licence information on the White Rose Research Online record for the item.

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.



eprints@whiterose.ac.uk
<https://eprints.whiterose.ac.uk/>

Editorial – Construction Materials, 171/4 issue

Susan A. Bernal

Department of Materials Science & Engineering, University of Sheffield, Sheffield S1 3JD, UK

It is a pleasure to introduce this issue of *Construction Materials*, which features articles spanning a wide range of important topics for Civil Engineering, including the use of new screening techniques to determine performance of different timber species, innovative corrosion protection approaches to concrete structures, and performance of glass fibre reinforced ultra-high strength concretes.

The first article in this issue by Williams et al (Williams & Sawyer et al. 2018) describes advances in the utilisation of novel fast-track screening methods to assess key characteristic of less used timber species, from South America and West Africa, for potential application in structures exposed to marine environments. It provides a compelling case featuring the challenges of utilising timber in these applications, and highlights that understanding service requirements and hazards provides a pathway for development of fast-screening methods to determine performance of less used timbers. It is also noted, the need for further research to develop strategies for predicting long-term mechanical performance evolution of less used timber, under marine service conditions.

Doods et al (Dodds & Christodoulou et al. 2018) report unique results of surveying six bridging structures with novel hybrid anode corrosion protection systems, installed between 2006 and 2013. This study determined the effectiveness of these systems in providing sufficient protection against the initiation of corrosion in steel reinforced concretes. The authors identified that corrosion rates were generally low, over a period of up to 8 years, since the installation of the hybrid systems, validating their functionality as an alternative corrosion risk management technique in reinforced concrete structures. The authors also provide valuable insight for the designing of new hybrid anodes improve the redundancy, functionality and robustness of the system.

Hossain et al (Hossain & Ametrano et al. 2018) describes the bond characteristics of sand-coated, glass-fibre-reinforced polymer bars in ultra-high-strength concrete (UHSC). An extensive experimental campaign was follow by the authors, evaluating the influence of different types of glass fibre reinforced polymers (GFRP), and the diameter and/or length of the bars used, embedded in UHSC of different strength classes. The authors identified that bond strengths are influenced by the properties of the GFRP used, although the differences are reduced at lower embedment lengths. Independently of the GFRP type and/or diameter and embedment length or cover, the bond strength increased when reinforcing concretes with higher compressive strengths. These findings provide evidence that existing codes for design and construction of structures with fibre-reinforced polymers are applicable to predict the bond strength of GFRP bars embedded in UHSC.

On behalf of the Advisory Editorial Panel, I hope that this issue of *Construction Materials* will be of interest and value to the readers.

References

William JR, Sawyer GS, Cragg SM, Icely JD, Simm J, Meaden M, Borges LMS, Maylon GP. 2018). Evaluating less-used timber species for marine construction. *Construction Materials* **171(4)**:XX-XX

Dodds W, Christodoulou C, Goodier C. (2018). Hybrid anode concrete corrosion protection – independent study. *Construction Materials* **171(4)**:XX-XX

Hossain KMA, Ametrano D, Lachemi M. (2018). The bond between glass-fibre-reinforced polymer bars and ultra-high-strength concrete. *Construction Materials* **171(4)**:XX-XX