



This is a repository copy of *Influences of non-fullerene acceptor fluorination on three-dimensional morphology and photovoltaic properties of organic solar cells.*

White Rose Research Online URL for this paper:

<http://eprints.whiterose.ac.uk/156041/>

Version: Supplemental Material

---

**Article:**

Chen, M., Liu, D., Li, W. et al. (11 more authors) (2019) Influences of non-fullerene acceptor fluorination on three-dimensional morphology and photovoltaic properties of organic solar cells. *ACS Applied Materials & Interfaces*, 11 (29). pp. 26194-26203. ISSN 1944-8244

<https://doi.org/10.1021/acsmami.9b07317>

---

This document is the Accepted Manuscript version of a Published Work that appeared in final form in ACS Applied Materials and Interfaces, copyright © American Chemical Society after peer review and technical editing by the publisher. To access the final edited and published work see <https://doi.org/10.1021/acsmami.9b07317>

**Reuse**

Items deposited in White Rose Research Online are protected by copyright, with all rights reserved unless indicated otherwise. They may be downloaded and/or printed for private study, or other acts as permitted by national copyright laws. The publisher or other rights holders may allow further reproduction and re-use of the full text version. This is indicated by the licence information on the White Rose Research Online record for the item.

**Takedown**

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing [eprints@whiterose.ac.uk](mailto:eprints@whiterose.ac.uk) including the URL of the record and the reason for the withdrawal request.

# **Supporting Information**

## **Influences of non-fullerene acceptor fluorination on three-dimensional morphology and photovoltaic properties of organic solar cells**

Mengxue Chen<sup>1,2</sup>, Dan Liu<sup>1,2</sup>, Wei Li<sup>1,2</sup>, Robert S. Gurney<sup>1,2</sup>, Donghui Li<sup>1,2</sup>, Jinlong Cai<sup>1,2</sup>, Emma L. K. Spooner<sup>3</sup>, Rachel C. Kilbride<sup>3</sup>, James D. McGettrick<sup>4</sup>, Trystan M. Watson<sup>4</sup>, Zhe Li<sup>5</sup>, Richard A. L. Jones<sup>3</sup>, David G. Lidzey<sup>3</sup>, Tao Wang<sup>1,2\*</sup>


<sup>1</sup>School of Materials Science and Engineering, Wuhan University of Technology, Wuhan 430070, China E-mail: [twang@whut.edu.cn](mailto:twang@whut.edu.cn)

<sup>2</sup>State Key Laboratory of Silicate Materials for Architectures, Wuhan University of Technology, Wuhan, 430070, China

<sup>3</sup>Department of Physics and Astronomy, University of Sheffield, Sheffield, S3 7RH, UK

<sup>4</sup>SPECIFIC, College of Engineering, Bay Campus, Swansea University, Swansea, SA1 8EN, UK


<sup>5</sup>School of Engineering, Cardiff University, Cardiff, Wales UK, CF24 3AA




**Figure S1** (a) Chemical structure of PBDB-T-2F. (b) Energy level diagram of donors (PBDB-T, PBDB-T-2F) and IT-4F. (c) Absorbance of donors (PBDB-T, PTB7-Th, PBDB-T-2F). (d) J-V characteristics of our best performing PBDB-T:IT-4F and PBDB-T-2F:IT-4F OSCs.


**Table S1** Photovoltaic parameters of OSCs measured at an illumination of AM 1.5 G, 100 mW cm<sup>-2</sup>. The statistical data were obtained from over 15 individual devices.

Donor:Acceptor	FF [%]	$J_{sc}$ [mA cm <sup>-2</sup> ]	Calculated $J_{sc}$ [mA cm <sup>-2</sup> ]	$V_{oc}$ [V]	PCE <sub>max</sub> (PCE <sub>avg</sub> ) [%]
PBDB-T:IT-4F	73.1	19.4	18.3	0.67	9.6 (9.2±0.5)
PBDB-T-2F:IT-4F	75.1	20.3	20.9	0.85	13.1 (12.8±0.4)




**Figure S2**  $\Psi$  of (a) ITIC, (b) IT-4F, (c) IEICO, (d) IEICO-4F films as a function of temperature. The thickness of acceptor's films is fitted by the Cauchy model.







**Figure S3** AFM height images ( $5 \text{ } \mu\text{m} \times 5 \text{ } \mu\text{m}$ ) of (a) PBDB-T:ITIC, (b) PBDB-T:IT-4F, (c) PTB7-Th:IEICO and (d) PTB7-Th:IEICO-4F films.



**Figure S4** Water contact angles ( $\theta$ ) and surface energies ( $\gamma$ ) of (a) ITIC, (b) IT-4F, (c) PBDB-T, (d) IEICO, (e) IEICO-4F and (f) PTB7-Th pure films.



**Figure S5** Root square plots of (a) electron densities versus voltage of the ITO/ZnO/Active layer/Ca/Ag electron-only devices and (b) hole densities versus voltage of the ITO/PEDOT:PSS/Active layer/MoO<sub>3</sub>/Ag hole-only devices. A linear fit was applied in the voltage range from 0 to 6 V.



**Figure S6** Nyquist plots of impedance spectra of various devices under 1 sun irradiation with an applied bias at  $V_{oc}$ .