

This is a repository copy of *Simple, quick and green isolation of cannabinoids from complex natural product extracts using sustainable mesoporous materials (Starbon®)*.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/186228/>

Version: Accepted Version

---

**Article:**

Attard, Thomas Michael, Goodwin, Christopher, Nalivaika, Povilas et al. (6 more authors) (2022) Simple, quick and green isolation of cannabinoids from complex natural product extracts using sustainable mesoporous materials (Starbon®). *Materials Chemistry Frontiers*. pp. 1324-1330. ISSN 2052-1537

<https://doi.org/10.1039/D2QM00028H>

---

**Reuse**

This article is distributed under the terms of the Creative Commons Attribution-NonCommercial (CC BY-NC) licence. This licence allows you to remix, tweak, and build upon this work non-commercially, and any new works must also acknowledge the authors and be non-commercial. You don't have to license any derivative works on the same terms. More information and the full terms of the licence here: <https://creativecommons.org/licenses/>

**Takedown**

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing [eprints@whiterose.ac.uk](mailto:eprints@whiterose.ac.uk) including the URL of the record and the reason for the withdrawal request.


# MATERIALS CHEMISTRY

## FRONTIERS

Accepted Manuscript



This article can be cited before page numbers have been issued, to do this please use: T. M. Attard, C. Goodwin, P. Nalivaika, J. Attard, V. Budarin, A. Lanot, D. Bove, J. Clark and C. R. McElroy, *Mater. Chem. Front.*, 2022, DOI: 10.1039/D2QM00028H.



This is an Accepted Manuscript, which has been through the Royal Society of Chemistry peer review process and has been accepted for publication.

Accepted Manuscripts are published online shortly after acceptance, before technical editing, formatting and proof reading. Using this free service, authors can make their results available to the community, in citable form, before we publish the edited article. We will replace this Accepted Manuscript with the edited and formatted Advance Article as soon as it is available.

You can find more information about Accepted Manuscripts in the [Information for Authors](#).

Please note that technical editing may introduce minor changes to the text and/or graphics, which may alter content. The journal's standard [Terms & Conditions](#) and the [Ethical guidelines](#) still apply. In no event shall the Royal Society of Chemistry be held responsible for any errors or omissions in this Accepted Manuscript or any consequences arising from the use of any information it contains.

## ARTICLE

**Simple, quick and green isolation of cannabinoids from complex natural product extracts using sustainable mesoporous materials (Starbon®)**Thomas M. Attard,<sup>a,b</sup> Christopher Goodwin,<sup>a</sup> Povilas Nalivaika,<sup>a</sup> Jennifer Attard,<sup>a,c</sup> Vitaliy L. Budarin,<sup>a</sup> Alexandra Lanot,<sup>d</sup> Damien Bove,<sup>b</sup> James H. Clark<sup>a</sup> and Con Robert McElroy<sup>a\*</sup>Received 00th January 20xx,  
Accepted 00th January 20xx

DOI: 10.1039/x0xx00000x

The current process to purify cannabidiol (CBD) from *C. sativa* extract is long and intensive, requiring several steps such as winterification for 48 hours at -45 °C and high-temperature, high vacuum distillation. These processes are capital intensive and generate large amounts of toxic solvent waste. In contrast, the solid phase extraction (SPE) methodology proposed herein will change the way CBD is obtained, doing so in a single step that is fast and reusable. Furthermore, the new process is simple and easily implemented and does not require any intensive operator training. Starbon® A300 was successfully employed as the stationary phase in SPE taking Cannabis sativa extract in hexane to selectively physisorb the cannabinoids onto the surface, followed by ethanol to bring about desorption at up to 93% (by GC-FID). A similar one pot system was also proven, using Fedora hemp stem dust as feedstock, with extraction and adsorption in supercritical CO<sub>2</sub> followed by desorption in ethanol.

**Introduction**

There has been a substantial increase in the global demand for cannabinoids from Cannabis sativa L., especially with the ever-increasing legalisation of medicinal Cannabis; Cannabis for medical use has now been legalised in a host of countries.<sup>1</sup> Cannabidiol (CBD) has been the main cannabinoid investigated for medical use due to its non-psychoactive properties and plethora of pharmacological properties in the treatment of neurological and central nervous system (CNS) disorders, consequently possessing significant therapeutic importance.<sup>2</sup> The medicinal advances for use of CBD have seen investigations in seizures,<sup>3</sup> spasms,<sup>4</sup> migraines,<sup>5</sup> pain relief,<sup>6</sup> anxiety,<sup>7</sup> glaucoma,<sup>8</sup> anti-nausea,<sup>9</sup> anti-bacterial<sup>10</sup> and anti-inflammatory purposes.<sup>11</sup> It should be noted that the two dominant cannabinoids in the plant are the acidic forms of CBD and tetrahydrocannabinol (THC), i.e. CBDA and THCA, these are normally converted into CBD and THC via a decarboxylation step.<sup>12</sup>

One of the major hurdles in CBD product utilisation has always been separation and purification. While the extraction of cannabinoids is a relatively straightforward process, the conventional purification of cannabinoids is a long and intensive process. The desired cannabinoids, having the specific pharmaceutical/nutraceutical activity, are co-extracted with a plethora of other unwanted hydrophobic compounds, which leads to a number of potential major problems, from unwanted texture and appearance to the lowering of activity/performance of the target molecule.<sup>13</sup> This results in the need for separation and purification technology that is highly energy and time-consuming as well as costly. The conventional extraction and purification is a step-wise process, each step increasing the purity of the cannabinoid content and comprises extraction, winterisation (a time-consuming step, taking between 1 – 3 days to ensure that all waxes and lipids are removed), chlorophyll removal, short path distillation (decarboxylation occurs here if the sample has not already undergone heating) and finally chromatography (flash, high-performance liquid chromatography (HPLC), centrifugal partition chromatography (CPC) etc).<sup>14</sup> These technologies have high capital costs associated with them, are time-consuming processes and often use large volumes of solvent. In recent commercial applications selective cannabinoid purification was achieved using a series of fractionating solvent systems and/or chromatography.<sup>15, 16</sup> However, both column and liquid chromatographic methods involve long run times, small sample loadings and poor yields. Furthermore, techniques using large volumes of solvents or column effluents have high process mass intensities (PMI)<sup>17</sup> using solvents such as dichloromethane or chloroform.

<sup>a</sup> Department of Chemistry, University of York, York, YO105DD, UK, email [rob.mcelroy@york.ac.uk](mailto:rob.mcelroy@york.ac.uk).

<sup>b</sup> RX Extraction Ltd, Unit 10, Rowan Trade Park, Bradford, BD4 8TQ, UK

<sup>c</sup> Circular Bioeconomy Research Group, Munster Technological University Kerry, Ireland V92 CX88

<sup>d</sup> Department of Biology, University of York, York, YO105DD, UK

\*corresponding author



Starbon® materials ("Starbons"), first developed in 2006, are a bio-based mesoporous material obtained in 3 steps; 1) gelling 2) drying 3) pyrolysis.<sup>18</sup> The materials take their name from starch and carbonisation to give Starbon, although they can be produced from any polysaccharide that can be gelled, most notably alginic acid<sup>19</sup> from seaweed and pectin<sup>20</sup> from fruit waste. Starbons are traditionally classified by a letter and 3 numbers e.g. S300, where the letter defines the starting polysaccharide; S starch, A alginic acid, P pectin, while the number denotes the pyrolysis temperature. The potential to vary the polysaccharide used and the pyrolysis temperature, has allowed for the materials' properties to be highly tunable to the required application. To date, there have been over 50 Starbon related publications since their discovery, in a variety of fields including catalysis,<sup>21</sup> gas capture,<sup>22</sup> batteries,<sup>23</sup> metal recovery,<sup>24</sup> and water treatment.<sup>25</sup> Additionally there are two live patents relating to Starbons<sup>26,27</sup> with an associated start-up company.<sup>28</sup>

A significant amount of published work on Starbons exists in the field of separation. Early work demonstrated the uptake of two model dyes from aqueous systems as compared to Norit® activated carbon.<sup>29</sup> Both mesoporosity and surface chemistry were found to be far more significant in dye uptake as opposed to surface area, with the highest loading observed being 186 mg g<sup>-1</sup>. Similar work showed uptake and recovery of phenolic compounds from an aqueous environment.<sup>30</sup> In each case the adsorption was carried out in an ideal system of the target phenol in water, with an uptake of between 87 to 139 mg g<sup>-1</sup>. Desorption was carried out over a 24 hour period in an aqueous system at a pH above 11, with a recovery range of 7-40%. Starbons performed well in the adsorption and controlled desorption of 4 plant growth promoters in aqueous systems.<sup>31</sup> Adsorption capacity varied between 76 and 370 mg g<sup>-1</sup> while desorption varied between 2 to 47%, depending on the plant growth promoter. A more complex system was investigated, focusing on uptake of a series of phenolic compounds in methanol.<sup>32</sup> Each compound was investigated individually for uptake and then tested using a model system of all 10 compounds again in methanol. Results showed some materials had irreversible uptake, while in others, all compounds could be recovered. However, the solid phase extraction (SPE) systems were not tested on real, complex extracts so selective adsorption of the target molecules was not investigated (i.e. whether there would be competition from non-target molecules).

In this work we apply reusable mesoporous Starbons in simple, rapid SPE of cannabinoids from a crude complex extract in a single step giving a product of high purity, with the scope of replacing the number of time-consuming and energy-consuming purification steps highlighted above.

## Results

The initial step in this work required the generation of cannabinoid rich complex materials. Flowers from a high cannabinoid Cannabis sativa plants grown in US and dust obtained from the processing of Fedora hemp stems for fibre

application were extracted using supercritical carbon dioxide (scCO<sub>2</sub>) to give a complex mixture in yields of 10.4% and 1.1% respectively. Gas chromatography flame ionisation detector (GC-FID) analysis of the crude extracts indicates multiple classes of compounds including terpenes, long-chain saturated and unsaturated fatty acids, fatty alcohols, aldehydes, n-alkanes, cannabinoids, sterols and wax esters.

All Starbons used in this work have been produced at scale on a commercial pilot plant, it is their application as opposed to their synthesis which is being investigated. Alginic acid based Starbons were selected as they are produced at scale more readily than other Starbon materials. Starbons Ltd routinely pyrolysis their material to either 300, 450 or 800 °C as this gives a range of surface properties from hydrophilic to hydrophobic while also ensuring stability as compared to the hydroscopic feedstock (ESI S1). As such alginic acid derived A300, A450 and A800 Starbon were commercially packed into Instrument Top Sample Preparation (ITSP™) cartridges for use on a Gerstel Multi Purpose Sampler (MPS, ESI S2). Crude *C. sativa* extract was taken up in 3 different organic solvents, non-polar hexane, moderately polar ethyl acetate and polar ethanol. These were passed through A450 as a representative Starbon sample and the eluted solution analysed via GC to ascertain adsorption of the cannabinoid target compounds from solution. Good adsorption was observed in hexane, moderate adsorption in ethyl acetate and limited uptake from ethanol. Hexane was therefore selected as the adsorption solvent and ethanol selected as desorption solvent. GC chromatography of these early results shows the selective adsorption and desorption of cannabinoids using Starbon A300.

The full program used by the MPS is given in the ESI (Table 1) but the SPE methodology is as follows. The Starbon is first washed with the adsorption solvent to prep the solid phase in the desired solvent system. The hemp extract is then passed through the Starbon and the solvent collected – this is the adsorption sample. In order to ensure only material that is strongly bound to the Starbon is retained, more adsorption solvent is passed through the material to wash any residual content. The desorption solvent is then passed through the Starbon to remove any physisorbed material and collected – this is the desorption sample (Figure 1). The Starbon is washed with more desorption solvent to ensure all bound material has been removed from the pore network. The Starbon is then re-conditioned with the desorption solvent for the next run.




Figure 1 - GC chromatograph of HTs: A) Crude *C. sativa* extract, B) Desorption phase (ethanol) after passing through A300. Higher definition figures are available in the ESI.



The choice of desorption solvents was also investigated. The rationale being that a polar solvent was required so that the CBD has greater affinity for the mobile phase than the stationary phase (Starbon). Methanol, ethanol and propanol were trailed as desorption solvents, with hexane as adsorption solvent. Methanol gave 53% CBD recovery, ethanol 84% and propanol 79%. Presumably this result is due to ethanol having enough non-polar content to rapidly exchange with hexane, while still being sufficiently polar to disrupt binding of CBD to the surface (ESI S3).

A series of repeat adsorption/desorption runs were conducted reusing the same Starbon material and cyclohexanone as an external standard. Interestingly, the first cycle always gave reduced desorption, suggesting a degree of irreversible adsorption and conditioning of the Starbon. This is probably due to the blocking of some smaller pores. Activity was benchmarked against Norit® Activated Carbon (AC). AC exhibited poor CBD uptake, with minimal reduction of the cannabinoid peaks in the adsorption solvent compared to the control. Figure 2 indicates the superiority of A300 in terms of cannabinoid recovery, with a total extraction of  $71.68 \pm 4.1\%$ . A800 performed well, while A450 results indicated more cannabinoids travelled directly through the cartridge than preferentially adsorbed onto the Starbon. As the materials increase in carbonisation temperature, they increase in surface area, pore volume and micropore volume. These properties alone do not explain the observed trend as the performance is  $A300 > A800 > A450$ . This suggests that the surface chemistry of Starbon is the dominating property.




Figure 2 A-series % CBD recovery quantified by external standard, *C. sativa* extract loaded at  $19 \text{ mg g}^{-1}$  adsorbent.

The lower temperature A300 material is more hydrophilic, containing aldehyde, carboxylic acid, ketone and OH functionality. The 450 contains fewer hetero atoms as well as significant unsaturation, while the 800 material is too conductive for an IR to be obtained as it is principally a conjugated aromatic system. This structure temperature relationship has been extensively discussed in the literature,<sup>18,19</sup> with a key figure illustrating this reproduced in the ESI (ESI S1). In all cases the cannabinoids here are in their acidic form, decarboxylation only occurs upon heating. There appear to be stronger polar interactions between the cannabinoids and A300 than with  $\pi$ - $\pi$  stacking between the aromatic ring of the

cannabinoids and the poly-aromatic A800 surface. Also of significance is the speed of uptake, the *C. sativa* extract had a contact time of just 30 seconds to the material (as determined by the slowest possible add speed on the MPS). If contact time is reduced to just under 2 seconds, adsorption and recovery of cannabinoids is reduced by almost 50% but this still indicates that initial uptake is rapid, followed by a longer period to reach equilibrium (ESI S4). Desorption speed was also investigated but the contact time of ethanol on the Starbon did not influence the %CBD recovery. This suggests that breaking the cannabinoid-Starbon interaction occurs rapidly in a polar solute.

The adsorption capacity of A300 was investigated to see how much CBD could be loaded from the HT extract, thus determining the optimal loading of CBD. This was done by preparing a series of HT extract solutions of varying concentrations ( $\text{mg ml}^{-1}$ ), thus varying the loading of extract to Starbon and determining the percentage recovery of CBD for each concentration. The results are summarised in Figure 3.




Figure 3 Recovery of CBD from HT extract at different concentrations using hexane/ethanol on A300.

Low concentrations showed high levels of CBD recovery. All runs were repeated five times for reliability, although with the initial run results discarded as they are always significantly poorer. This demonstrates the ease of repeatability of this method and the relative consistency of the A300 for multiple extraction runs. The level of CBD recovery seems to decrease above loadings of  $14 \text{ mg g}^{-1}$  at which point more significant levels of cannabinoids are found in both the adsorb and the washing steps. This indicates that the loading of CBD is too high to be completely physisorbed onto the Starbon and so some remains in solution. As such the amount of CBD detected in the adsorption sample increases. The excess of CBD also means more cannabinoids are retained in the wetted Starbon without being bound to the surface. This is removed in the first washing step using the adsorption solvent. Results at  $19 \text{ mg g}^{-1}$  are almost within error and at this higher loading, reasonable to take forward as an optimised loading.

The crude hemp top extract has been characterised used GC-FID and GC-MS. Key components have been identified and the relevant chromatograms annotated in the ESI.

The A300 Starbon was scaled up from a  $16 \text{ mg}$  scale to a  $10 \text{ g}$  scale to assess potential industrial viability (ESI S5). This would represent a potential step forward for green extraction



processes. The same method and washing steps were carried out manually in line with the MPS sequence. The extraction was run twice to negate the effect of the first extraction being inconsistent, as explained previously. As with the small-scale work, conditioning of the Starbon was vital as the first extraction run gave a poor CBD recovery in the desorption phase. A CBD recovery of 97% was extracted on the second run and quantified via the external standard. This is compared with a value of 71% obtained on the ITSP cartridge. The flow rate of the large-scale experiment was slower than the  $10 \mu\text{Ls}^{-1}$  (30 second contact time) of the small-scale work as only a slight vacuum was applied. This is a potential reason for the higher extraction yield of CBD observed. This suggests that contact time between the extract and the Starbon is greater here than in the small-scale automated work suggesting the system requires time to fully equilibrate. Large scale SPE also allowed sufficient sample for proton and carbon NMR (ESI S6 and S7) as well as Liquid Injection Field Desorption Ionisation mass spectrometry (LIFDI-MS, S8 and S9).

The NMR data confirmed that both the desorbed product is of relatively high purity and that the cannabinoid has principally been isolated in its acidic form, CBDA. All GC data showed CBD due to decarboxylation at the temperatures employed. LIFDI-MS indicates that there are a number of higher molecular weight compounds still present within the desorb sample, but significantly there are no signals related to triglyceride species 869-943 m/z.

The large scale SPE trials also meant sufficient Starbon material was available for analysis by nitrogen porosimetry (table 1). Upon uptake of cannabinoids and other material that physisorbs onto the surface of A300, all micropores have become blocked and the mesopore volume has also dropped by over 25%, with an overall pore volume decrease of 31%. This is reflected in the drop in surface area and the increase in pore diameter. On desorption the surface area is only 5% lower than the original material. Overall pore volume is now only 11% lower, with a loss of 9% of microporosity and 13% of mesoporosity. The 20% recovered pore volume being attributed to that involved in binding of material that undergoes selective adsorption and desorption. As a greater relative number of larger pores have been lost, the average pore diameter is now smaller than the original material. This data shows that mesopores and micropores are both important in the selective uptake of cannabinoids and also demonstrates a degree of irreversible conditioning in keeping with other experimental data.

Table 1. Total pore volume and pore size distribution of A300 used in large scale SPE before, during and after purification of *C. sativa* extract.

	A300	A300 post adsorption	A300 post desorption
$S^{\text{BET}}$ surface $\text{m}^2 \text{g}^{-1}$	95.1338	40.1390	90.0233
$V_p^{\text{BJH}}$ $\text{cm}^3 \text{g}^{-1}$	0.2350	0.1620	0.2092
Micropore vol <sup>BJH</sup> $\text{cm}^3 \text{g}^{-1}$	0.0182	0	0.0165
Mesopore vol <sup>BJH</sup> $\text{cm}^3 \text{g}^{-1}$	0.2321	0.1726	0.2026
Diameter <sup>BJH</sup> nm	11.4797	11.8821	11.2838

Finding a replacement for hexane as the adsorption solvent was investigated due to its classification as "Suspected to be Toxic to Reproduction".<sup>33</sup> As there are not many non-polar, green solvents with sufficient volatility to allow recovery of extracts, scCO<sub>2</sub> was investigated as a replacement for hexane as the adsorption solvent.<sup>34</sup> For these trials, A300 was used to pack a column for adsorption/desorption of CBD using scCO<sub>2</sub> as the adsorption solvent and ethanol as the desorption solvent. A 25 ml column packed with 7 g of A300 was placed between the extractor and the back pressure regulator to allow flow of extractives through the Starbon.

The extractor was loaded with *C. sativa* dust (HD) (60 grams) and extraction carried out at optimised conditions of 65 °C and 400 bar. HD is an interesting feedstock as the number and complexity of compounds in the extract is significantly higher than that found in HT, including long-chain hydrocarbons, saturated and unsaturated fatty acids, fatty alcohols, fatty aldehydes, wax esters and sterols.<sup>35</sup> Also of note, the cannabinoid content in this biomass is significantly lower. As with earlier SPE work, the first extraction, adsorption and desorption results were not used as this conditioned the solid phase. Results from the second run displayed in Figure 4 clearly show that the majority of volatile components in the extract are not retained by the A300 column and were removed with the scCO<sub>2</sub>; i.e. little adsorption occurred. It is also evident that under such conditions and with a loading of roughly  $94 \text{ mg g}^{-1}$  (extract to A300), the cannabinoids are either overloading the Starbon and/or capacity has been reduced. The desorbed phase showed that the cannabinoids were preferentially adsorbed onto the A300, along with short chain fatty acids.




Figure 4 – GC-FID chromatograms representing 3 extracts. From top to bottom; Original hemp dust extract, adsorption, desorption phases. Fa – fatty acids, Ak – alkanes, Ac – Alcohols. Higher definition figures are available in the ESI, full characterisation of hemp dust extract is available in the literature.<sup>35</sup>

GC-EI-MS analysis conducted on the one pot hemp dust desorbed phase showed the following cannabinoids; Cannabidiol (CBD), Cannabigerol (CBG), Cannabichromene (CBC) and Tetrahydrocannabinol (THC). Interestingly CBG, CBC and THC were not previously observed in scCO<sub>2</sub> hemp dust extracts carried out without solid phase extraction (SPE). This confirms that Starbon SPE enriches the cannabinoid content as compared to the crude extract. All cannabinoids appear to have affinity to the Starbon material, although some may do so more preferentially. This also needs to be studied more thoroughly in future work.

The innovation and green credentials of Starbon SPE setup is the application of a renewable, bio-derived mesoporous material that replaces the need for a number of hazardous steps. The industrial process to purify cannabinoids from hemp extract is



long and intensive, requiring several steps such as winterification for two days at  $-45\text{ }^{\circ}\text{C}$  and high-temperature, high vacuum distillation. These processes generate large amounts of toxic solvent waste and are energy intensive. In contrast, the work shown herein uses a single step to obtain cannabinoids that is fast and reusable. It makes use of a lower amount of ethanol which is a food-grade solvent and has the potential to apply  $\text{scCO}_2$  as the adsorption solvent.

The work herein shows promise for developing a one-pot system, wherein extraction and purification of cannabinoids from *C. sativa* occurs simultaneously, reducing significantly the need for extensive post-purification processes.

## Experimental

**Chemicals** Hexane, deuterated chloroform and cyclohexanone were purchased from Sigma Aldrich. Ethanol and 2-propanol were purchased from Fisher Chemical.

**Cannabis sativa samples** Cannabis sativa tops (HTs) were provided by RX Extraction. The Cannabis sativa sample was obtained from the US due to the high levels of CBDA (ca. 20% w/w). Hemp dust (HD) was obtained from Harrison Spinks hemp processing facility in North Yorkshire, UK.

**Starbons** Solid-phase extraction cartridges, obtained from ITSP Solutions Inc., were packed with 16 mg of Starbon. Alginic acid-based Starbons (A-series) were synthesised through Starbons Ltd at the biorenewables development centre (BDC) in Dunnington, York and are derived from kelp. Different Starbons were obtained by varying preparation temperatures: 300, 450 and  $800\text{ }^{\circ}\text{C}$ .

**Purification and isolation of cannabinoid** Analysis of *C. sativa* extracts Auto sampled adsorption and desorption of crude *C. sativa* extracts; *C. sativa* extracts (20 mg) were dissolved in hexane (20 mL) and placed on a Gerstel multipurpose sampler (MPS) purchased from Anatune. Details of the adsorption, desorption system are given in ESI Table 1. Each repetition on the autosampler consisted of three key steps: adsorption, washing and desorption. The Starbon cartridge was flushed with hexane immediately prior to the run to condition the adsorbent. *C. sativa* extract (300  $\mu\text{L}$ ) was passed through the ITSP cartridge, and the adsorption phase collected. The cartridge was then flushed with hexane (500  $\mu\text{L}$ ). The needle was sequentially washed with ethanol, ethyl acetate and hexane (500  $\mu\text{L}$ ). Subsequently, ethanol (300  $\mu\text{L}$ ) was then passed through the cartridge and collected to give the desorption phase. The cartridge was then flushed with ethanol (500  $\mu\text{L}$ ) followed by hexane (500  $\mu\text{L}$ ) ready for the next SPE run.

**A300 scale-up** 190 mg of HT extract was dissolved in 166 mL of hexane and passed through a plug of A300 Starbon (10 g) in vacuo and the adsorption phase collected. The cartridge was then washed with 166 mL of hexane. The ethanol desorption solvent (166 mL) was subsequently passed through the Starbon and collected. This was then washed sequentially with ethanol

and hexane (166 mL) to prepare for additional runs. The adsorption/desorption run was done twice. The desorption solvent was removed in vacuo to afford products to undergo further analysis. Aliquots of each phase were collected and external standard was added to quantify the results.

**scCO<sub>2</sub> extraction/Starbon isolation** Supercritical CO<sub>2</sub> has already been established as a viable methodology for extraction of hydrophobic constituents containing cannabinoids from various *C. sativa* sources. Herein the direct isolation of cannabinoids from hemp dust in one pot is discussed.

**Lab-scale supercritical fluid extraction of *C. sativa* biomass** All  $\text{scCO}_2$  extractions were carried out using a SFE-500 extractor provided by Thar technologies. 80 g of milled *C. sativa* biomass was placed into the 500  $\text{cm}^3$  extraction vessel and connected to the extraction system. Liquid CO<sub>2</sub> was then pumped to the required pressure (maintained by an automated back pressure regulator - ABPR) and passed through an inline pre-heater maintained at the desired extraction temperature. The system was run for 2 hours at a flow rate of 30  $\text{g min}^{-1}$  CO<sub>2</sub> with continual collection of extract.

**One pot system** In the one pot system, a stainless steel 10  $\text{cm}^3$  column was filled with 7 g of Starbon A300 and connected between the extractor and the ABPR. The system was set to the desired temperature and pressure and run for 2 hours at 30  $\text{g min}^{-1}$  and the extract collected and analysed. Post extraction, ethanol was passed through the column for 10 minutes using the co-solvent modifier pump at a 10  $\text{ml min}^{-1}$  flowrate to give the desorption fraction. The column was reconditioned with  $\text{scCO}_2$  at 120 bar,  $50\text{ }^{\circ}\text{C}$  for 30 minutes at 30  $\text{g min}^{-1}$ .

**Gas chromatography flame ionisation detection (GC-FID)** Samples were quantified by using an Agilent Technologies 7890B GC system and a Hewlett Packard HP 6890 Series GC system. Both GCs were run using flame ionisation detection methods and on identical methods. A Rxi-5HT capillary column (30 m x 250  $\mu\text{m}$  x 0.25  $\mu\text{m}$  nominal) was fitted at constant pressure of 20.16 psi. Helium was the carrier gas used. Both the injector temperature and FID detector temperature were set at  $320\text{ }^{\circ}\text{C}$ . 1  $\mu\text{L}$  samples were injected by automated injection, with a split ratio of 5:1. The oven temperature profile was as follows: Initial temperature of  $50\text{ }^{\circ}\text{C}$ , increased to  $300\text{ }^{\circ}\text{C}$  at a rate of 30  $^{\circ}\text{C min}^{-1}$ , held at this temperature for 5 mins. Quantification was carried out by means of an external standard (cyclohexanone).

**Gas chromatography mass spectrometry (GC-EIMS)** Gas chromatography electronic ionisation mass spectrometry (GC-MS) was run on a Perkin Elmer Clarus 500 GC coupled with a Clarus 560 S mass spectrometer. This was run using an Rxi<sup>®</sup>-5HT 30 m x 250  $\mu\text{m}$  x 0.25  $\mu\text{m}$  at a pressure of 21.4 psi. The carrier gas was helium. The injector temperature is set to 300  $^{\circ}\text{C}$  and the flow rate of 1.0  $\text{mL min}^{-1}$ . The method was run at  $50\text{ }^{\circ}\text{C}$  starting temperature. The Clarus 500 quadrupole mass spectra were operated in the electron ionisation mode (EI+) at 70 eV, a source temperature of 300  $^{\circ}\text{C}$ , quadrupole in the scan range of 30-1200 amu per second.



**Porosimetry** Nitrogen-adsorption analysis was carried out using an ASAP 2020 volumetric adsorption analyser from Micrometrics. Measurements were performed at 77 K. Samples were degased at 150 °C, 50 µm Hg for 4 h prior to analysis. The Brunauer-Emmett-Teller (BET) theory was used to determine the surface area, and the Barret-Joyner-Halenda (BJH) equation was applied to determine the mesoporous volume and the pore size.

## Conclusions

A rapid SPE system using Starbon mesoporous materials has been found to enable rapid and high purity isolation of cannabinoids from complex crude mixtures. Starbons derived from alginic acid pyrolysed to 300 °C gave the best performance, presumably due to surface interactions. The solvent adsorb and desorb system of hexane and ethanol can be potentially replaced with a one pot extraction and separation using scCO<sub>2</sub>. This shows promise for the development of a one-pot extraction and purification process whereby the cannabinoids are separated from impurities while being extracted from the biomass.

## Author Contributions

Thomas Attard, conceptualisation, supervision, formal analysis, writing –original draft; Christopher Goodwin, investigation, formal analysis, writing - original draft; Povilas Nalivaika, investigation, formal analysis; Jennifer Attard, investigation, formal analysis, writing – review & editing; Vitaliy L. Budarin, methodology; Alexandra Lanot, resources; Damien Bove, resources, funding acquisition; James H. Clark, supervision, writing – review & editing; Con Robert McElroy conceptualisation, supervision, formal analysis, writing –original draft.

## Conflicts of interest

Dr Rob McElroy is CTO of Starbons Ltd, a start-up from the University of York.

## Acknowledgements

We would like to thank Mr Karl Heaton, University of York MS centre for running of LIFDI-MS, Mr John Horsefield from Harrison Spinks Beds Ltd for supply of hemp dust, Leeds City Region Enterprise Partnership for part-funding the research.

## Notes and references

- 1 Bridgeman MB, Abazia DT. Medicinal cannabis: history, pharmacology, and implications for the acute care setting. *Pharmacy and therapeutics* 42, 180 (2017).
- 2 Sholler DJ, Schoene L, Spindle TR. Therapeutic Efficacy of Cannabidiol (CBD): a Review of the Evidence From Clinical Trials and Human Laboratory Studies. *Current Addiction Reports* 7, 405-412 (2020).

- 3 Patra PH, et al. Cannabidiol reduces seizures and associated behavioral comorbidities in a range of animal seizure and epilepsy models. *Epilepsia* 60, 303-314 (2019).
- 4 Hussain SA, Dlugos DJ, Cilio MR, Parikh N, Oh A, Sankar R. Synthetic pharmaceutical grade cannabidiol for treatment of refractory infantile spasms: A multicenter phase-2 study. *Epilepsy & Behavior* 102, 106826 (2020).
- 5 Mechtler LL, Gengo FM, Bargnes VH. Cannabis and Migraine: It's Complicated. *Current Pain and Headache Reports* 25, (2021).
- 6 Boyaji S, Merkow J, Elman RNM, Kaye AD, Yong RJ, Urman RD. The Role of Cannabidiol (CBD) in Chronic Pain Management: An Assessment of Current Evidence. *Current Pain and Headache Reports* 24, (2020).
- 7 Skelley JW, Deas CM, Curren Z, Ennis J. Use of cannabidiol in anxiety and anxiety-related disorders. *Journal of the American Pharmacists Association* 60, 253-261 (2020).
- 8 Vallée A, Lecarpentier Y, Vallée J-N. Cannabidiol and the Canonical WNT/ $\beta$ -Catenin Pathway in Glaucoma. *International Journal of Molecular Sciences* 22, 3798 (2021).
- 9 Rock EM, et al. Evaluation of repeated or acute treatment with cannabidiol (CBD), cannabidiolic acid (CBDA) or CBDA methyl ester (HU-580) on nausea and/or vomiting in rats and shrews. *Psychopharmacology* 237, 2621-2631 (2020).
- 10 Aqawi M, Sionov RV, Gallily R, Friedman M, Steinberg D. Anti-Bacterial Properties of Cannabigerol Toward *Streptococcus mutans*. *Frontiers in Microbiology* 12, (2021).
- 11 Sunda F, Arowolo A. A molecular basis for the anti-inflammatory and anti-fibrosis properties of cannabidiol. *The FASEB Journal* 34, 14083-14092 (2020).
- 12 Moreno T, Dyer P, Tallon S. Cannabinoid Decarboxylation: A Comparative Kinetic Study. *Industrial & Engineering Chemistry Research* 59, 20307-20315 (2020).
- 13 Brenneisen R. Chemistry and Analysis of Phytocannabinoids and Other Cannabis Constituents. In: *Marijuana and the Cannabinoids* (ed ElSohly MA). Humana Press (2007).
- 14 Valizadehderakhshan M, Shahbazi A, Kazem-Rostami M, Todd MS, Bhowmik A, Wang L. Extraction of Cannabinoids from Cannabis sativa L. (Hemp)—Review. *Agriculture* 11, 384 (2021).
- 15 Roura XN. Methods of purifying cannabinoids, compositions and kits thereof Patent US20180000879A1 (2017).
- 16 Roura XN. Methods of purifying cannabinoids using liquid: liquid chromatography Patent US11034639B2 (2019).
- 17 Jimenez-Gonzalez C, Ponder CS, Broxterman QB, Manley JB. Using the Right Green Yardstick: Why Process Mass Intensity Is Used in the Pharmaceutical Industry To Drive More Sustainable Processes. *Organic Process Research & Development* 15, 912-917 (2011).
- 18 Budarin V, et al. Starbons: New Starch-Derived Mesoporous Carbonaceous Materials with Tunable Properties. *Angewandte Chemie International Edition* 45, 3782-3786 (2006).
- 19 White RJ, Budarin V, Luque R, Clark JH, Macquarrie DJ. Tuneable porous carbonaceous materials from renewable resources. *Chemical Society Reviews* 38, 3401 (2009).
- 20 White RJ, Budarin VL, Clark JH. Pectin-Derived Porous Materials. *Chemistry - A European Journal* 16, 1326-1335 (2010).
- 21 Matharu AS, Ahmed S, Almonthery B, Macquarrie DJ, Lee Y-S, Kim Y. Starbon/High-Amylose Corn Starch-Supported N-Heterocyclic Carbene-Iron(III) Catalyst for Conversion of Fructose into 5-Hydroxymethylfurfural. *ChemSusChem* 11, 716-725 (2018).
- 22 Milesu RA, et al. The role of surface functionality of sustainable mesoporous materials Starbon® on the adsorption of toxic ammonia and sulphur gasses. *Sustainable Chemistry and Pharmacy* 15, 100230 (2020).



- 23 Kim S, et al. Green electrode processing using a seaweed-derived mesoporous carbon additive and binder for LiMn<sub>2</sub>O<sub>4</sub> and LiNi<sub>1/3</sub>Mn<sub>1/3</sub>Co<sub>1/3</sub>O<sub>2</sub> lithium ion battery electrodes. *Sustainable Energy & Fuels* 3, 450-456 (2019).
- 24 Muñoz García A, et al. Starch-derived carbonaceous mesoporous materials (Starbon®) for the selective adsorption and recovery of critical metals. *Green Chemistry* 17, 2146-2149 (2015).
- 25 Tony MA, Parker HL, Clark JH. Treatment of laundrette wastewater using Starbon and Fenton's reagent. *Journal of Environmental Science and Health, Part A* 51, 974-979 (2016).
- 26 Budarin V, Clark JH, Luque R, Macquarrie DJ, Milkowski K, White RJ. Carbonaceous materials Patent US8790548B2 (2014).
- 27 White RJ, Clark JH, Budarin VLV, Macquarrie DJ. Polysaccharide derived materials Patent US9457338B2 (2016).
- 28 [https://www.starbons.com/.](https://www.starbons.com/) (accessed 28/11/21).
- 29 Parker HL, Hunt AJ, Budarin VL, Shuttleworth PS, Miller KL, Clark JH. The importance of being porous: polysaccharide-derived mesoporous materials for use in dye adsorption. *RSC Advances* 2, 8992 (2012).
- 30 Parker HL, Budarin VL, Clark JH, Hunt AJ. Use of Starbon for the Adsorption and Desorption of Phenols. *ACS Sustainable Chemistry & Engineering* 1, 1311-1318 (2013).
- 31 Shannon JM, Clark JH, Ingrid De Heer M, Ekblad T, Matharu AS. Kinetic and Desorption Study of Selected Bioactive Compounds on Mesoporous Starbons: A Comparison with Microporous-Activated Carbon. *ACS Omega* 3, 18361-18369 (2018).
- 32 Zuin VG, et al. Polysaccharide-derived mesoporous materials (Starbon®) for sustainable separation of complex mixtures. *Faraday Discussions* 202, 451-464 (2017).
- 33 <https://echa.europa.eu/substance-information/-/substanceinfo/100.003.435.> (accessed 28/11/21).
- 34 D. Prat, A. Wells, J. Hayler, H. Sneddon, C. R. McElroy, S. Abou-Shehade and P. J. Dunn, CHEM21 selection guide of classical- and less classical-solvents. *Green Chemistry*, 18, 288-296 (2016).
- 35 Attard TM, Bainier C, Reinaud M, Lanot A, McQueen-Mason SJ, Hunt AJ. Utilisation of supercritical fluids for the effective extraction of waxes and Cannabidiol (CBD) from hemp wastes. *Industrial Crops and Products* 112, 38-46 (2018).
- 36 Qamar S, Torres YJM, Parekh HS, Robert Falconer J. Extraction of medicinal cannabinoids through supercritical carbon dioxide technologies: A review. *Journal of Chromatography B* 1167, 122581 (2021).

View Article Online  
DOI: 10.1039/D2QM00028H

Open Access Article. Published on 25 April 2022. Downloaded on 4/26/2022 2:45:04 PM.  
This article is licensed under a Creative Commons Attribution-NonCommercial 3.0 Unported Licence.

