

This is a repository copy of *Prediction of phonon-mediated superconductivity in new Ti-based M2AX phases*.

White Rose Research Online URL for this paper:

<https://eprints.whiterose.ac.uk/189660/>

Version: Published Version

Article:

Karaca, Ertugrul, Byrne, Peter John Phares, Hasnip, Philip James orcid.org/0000-0002-4314-4093 et al. (1 more author) (2022) Prediction of phonon-mediated superconductivity in new Ti-based M2AX phases. *Scientific Reports*. 13198. ISSN 2045-2322

<https://doi.org/10.1038/s41598-022-17539-8>

Reuse

This article is distributed under the terms of the Creative Commons Attribution (CC BY) licence. This licence allows you to distribute, remix, tweak, and build upon the work, even commercially, as long as you credit the authors for the original work. More information and the full terms of the licence here:

<https://creativecommons.org/licenses/>

Takedown

If you consider content in White Rose Research Online to be in breach of UK law, please notify us by emailing eprints@whiterose.ac.uk including the URL of the record and the reason for the withdrawal request.



OPEN

Prediction of phonon-mediated superconductivity in new Ti-based M_2AX phases

E. Karaca^{1,2}, P. J. P. Byrne¹, P. J. Hasnip¹ & M. I. J. Probert¹✉

A high-throughput computational method is used to predict 39 new superconductors in the Ti-based M_2AX phases, and the best candidates are then studied in more detail using density functional theory electron–phonon coupling calculations. The detailed calculations agree with the simple predictions, and Ti_2AlX (X: B, C and N) materials are predicted to have higher values of T_c than any currently known hexagonal M_2AX phases. The electronic states at the Fermi level are dominated by the Ti 3d states. The choice of X (X: B, C and N) has a significant impact on the electronic density of states but not on the phonon characteristics. The electron–phonon coupling parameter for Ti_2AlX (X: B, C and N) was determined to be 0.685, 0.743 and 0.775 with a predicted T_c of 7.8 K, 10.8 K and 13.0 K, respectively.

M_2AX phases are hexagonal carbides or nitrides with the chemical formula $M_{n+1}AX_n$ where $n = 1, 2, 3$, etc. Here, M is an early transition metal, A is mainly group 13–16 and X is either C or N. M_2AX phases exhibit high damage tolerance, excellent thermal shock resistance, resistance to corrosion and oxidation, high creep lifetime, exceptionally damage-tolerant good machinability, and are electrically and thermally conductive^{2–12}. The physical properties of hexagonal carbides and nitrides in the ternary M_2AX family phase have been extensively studied due to their unusual combination of properties typically associated with metals and ceramics. Additionally, in the last 2 years, some M_2AX phase ceramics, including B as the X element have been synthesized for the first time^{13–16}. Boron and its compounds have important technological uses due to their interesting physical and chemical properties^{17,18}. As such, M_2AX phase borides are also expected to become promising research and application candidates, particularly in the nuclear industry due to their enhanced stability¹⁹. Hadi et al. investigated the impact of substituting B for C and N in Nb_2SX (X: B, C and N) on the structural, electronic, mechanical, thermal and optical properties. They discovered that compared to Nb_2SC and Nb_2SN , Nb_2SB was mechanically stronger, more covalent, more resistant to shear deformation and more elastically and optically isotropic¹⁹. Some M_2AX phases are superconductors, with the highest known T_c in Nb_2GeC which has $T_c = 10$ K²⁰.

The purpose of this study is to predict new superconducting materials within the Ti-based M_2AX family and increase the maximum T_c . In addition, we present the first study of superconductivity in the recently synthesized boride-based M_2AX phases. This is a proof of principle of our high-throughput method to quickly screen M_2AX superconductors to provide useful guidance for experiments.

Three materials (Ti_2GeC , Ti_2InC and Ti_2InN) were initially studied and compared to known experimental T_c data to create a high-throughput screening model for Ti-based materials, based on the Fröhlich model we developed to predict T_c in Nb-C based M_2AX phases²¹. We then used this model to screen 42 different Ti_2AX materials (where A: Al, Si, P, S, Cu, Zn, Ga, Ge, As, Cd, In, Sn, Tl and Pb; X: B, C and N). For each X it was found that A = Al gave the highest predicted T_c .

In 1963, Jeitschko et al. reported on the manufacture and characterisation of Ti_2AlN ²², from which the hexagonal M_2AX phase family developed. So far, about 60 M_2AX phases have been synthesized¹, but only 10 of them have been shown to be superconductors in experiment: Mo_2GaC (4.0 K)²³, Nb_2SC (5.0 K)²⁴, Nb_2AsC (2.0 K)²⁵, Nb_2SnC (7.8 K)²⁶, Ti_2InC (3.1 K)²⁷, Nb_2InC (7.5 K)²⁸, Ti_2InN (7.3 K)²⁹, Ti_2GeC (9.5 K)³⁰, Lu_2SnC (5.2 K)³¹ and Nb_2GeC (10.0 K)²⁰. Of these, Nb_2GeC has the highest known $T_c = 10$ K. Attempts to synthesize V_2AlN have only succeeded in growing the related cubic non- M_2AX phase, which has recently been shown to be superconducting with $T_c = 15.9$ K³². The M_2AX phases have very useful mechanical properties, including high damage tolerance, excellent thermal shock resistance, resistance to corrosion and oxidation, high creep lifetime, and good machinability, which are properties that are not often found in superconductors, and so could have novel applications.

¹Department of Physics, University of York, York YO10 5DD, UK. ²Biomedical, Magnetic and Semiconductor Materials Research Center (BIMAS-RC), Sakarya University, 54187 Sakarya, Turkey. ✉email: matt.probert@york.ac.uk

As our high-throughput model predicted the highest T_c for Ti_2AlX (X: B, C and N), we therefore performed a more detailed study of superconductivity in these materials. Whilst the structural, electronic, elastic, thermodynamic, and vibrational properties of Ti_2AlX (X: B, C and N) have been studied theoretically^{33–37} and experimentally^{35,38}, we are unaware of any study of superconductivity in these materials. Thus, this work presents an ab initio study of the superconducting T_c , including electron-phonon coupling, as well as structural, electronic and phonon properties of Ti_2AlX (X: B, C, and N), using the plane-wave pseudopotential approach to density functional theory (DFT). The Eliashberg spectral function is calculated by combining linear response theory^{39,40} with Migdal–Eliashberg theory^{41,42}. These quantities are then used to investigate the origin of superconductivity in these materials, and the effect of changing X (X: B, C, and N). In our previous study of superconductivity in Nb–C based M_2AX phases²¹ we found that the Migdal–Eliashberg predictions agreed with experimental T_c values within ± 1 K.

Methods

The calculations used the Quantum Espresso ab initio simulation package^{39,40,43} with the Perdew–Burke–Ernzerhof (PBE)⁴⁴ exchange–correlation approximation and ultrasoft pseudopotentials⁴⁵. The plane-wave basis cut-off is 60 Ry (~ 812 eV) and the Brillouin zone integration used the Monkhorst–Pack⁴⁶ scheme with $(36 \times 36 \times 8)$ \mathbf{k} -mesh (maximum spacing of $0.01 \times 2\pi \text{ \AA}^{-1}$) whilst electronic and Fermi surface calculations are performed with a denser $(40 \times 40 \times 10)$ \mathbf{k} -mesh.

Phonon calculations used the linear response approach^{39,40,43} and the Brillouin zone integration for the phonons used a $(4 \times 4 \times 4)$ \mathbf{q} -mesh and twelve dynamical matrices by symmetry. The electron and phonon results are combined to compute the electron-phonon interaction using the Migdal–Eliashberg theory^{41,42} and hence T_c .

This calculation of T_c is very computationally demanding, and is therefore impractical for high-throughput screening for novel superconductors. A change in the A element in Ti_2AX (X: B, C, and N) appears to have a comparable impact to the superconducting isotope effect, and in our previous work²¹ on Nb–C based M_2AX phases, we showed that a simple model based upon the Fröhlich⁴⁷ theory of the isotope effect was an effective foundation for a high-throughput screening approach of these materials, with

$$T_c = \alpha \frac{N(E_F)}{\sqrt{M}} - T_0, \quad (1)$$

where M is the mass of a formula unit, $N(E_F)$ is the electronic density at the Fermi energy E_F and T_0 and α are linear fit parameters. This model has a critical value of $N(E_F)/\sqrt{M} > T_0/\alpha$ for superconductivity to occur. This functional form is an approximation to the simplified BCS equation⁴⁸.

In its most basic form, BCS theory gives the superconducting transition temperature T_c in terms of the electron–phonon interaction (V) and the Debye temperature (Θ_D), and can be simplified as

$$T_c = 1.134\Theta_D \exp\left(\frac{-1}{N(E_F)V}\right), \quad (2)$$

where $\Theta_D \sim 1/\sqrt{M}$. This exponential form is approximately linear when $0.2 < NV < 0.7$ and saturates at large values of NV . Within each Ti_2AX family (borides, carbides and nitrides) we might expect a similar V and hence observe behaviour similar to Eq. (1).

The advantage of Eq. (1) is that $N(E_F)$ can be calculated in much less time (typically less than 1 core hour) than the electron–phonon matrix elements (typically 300 core hours per material), and when combined with the observed trend in T_c vs. $N(E_F)/\sqrt{M}$ for known superconducting materials (Ti_2GeC , Ti_2InC and Ti_2InN), it can be used in a high-throughput search to predict the superconducting transition temperatures of candidate materials for which there have been no previous superconductivity studies. The most promising of these is Ti_2AlX (X: B, C and N) which is then investigated in more detail using full electron–phonon coupling and Migdal–Eliashberg theory.

Results

Superconducting T_c results. The high-throughput screening is based on our Fröhlich model, which predicts a linear relationship between the critical temperature (T_c) and the value of $N(E_F)/\sqrt{M}$ (as shown in Fig. 1). As shown in the Supplementary Information, the T_c values of three known superconductors (Ti_2GeC , Ti_2InC and Ti_2InN) were calculated using the Eliashberg theory^{41,42} and the best fit to experimental T_c values is found when $\mu^* = 0.13$ for all 3 materials. These theoretical values are shown in Fig. 1 using blue and magenta squares, whilst the corresponding experimental T_c values are given in black circles.

In our previous work²¹ we found that Nb–C based M_2AX phases containing Al had high T_c values. Hence we used the Eliashberg theory with $\mu^* = 0.13$ to determine the superconductivity temperatures of Ti_2AlX (X: C and N) and Ti_2GeN materials, none of which have a known T_c . These results are also plotted in Fig. 1 as blue and magenta squares, and it appears that the M_2AX carbides and nitrides fall into 2 distinct classes, which we have shown by 2 straight lines.

Recently, a new family of boride M_2AX phases⁴⁹ has been synthesized but has yet to be tested for superconductivity. We therefore used Eliashberg theory to calculate the superconductivity temperatures of Ti_2AB (A: Al, Ge, In) using $\mu^* = 0.13$ as before, for a direct comparison with the carbides and nitrides. These results are also plotted in Fig. 1 as red squares, and it appears that the borides fall into a third distinct class.

With electron–phonon coupling calculation results of T_c for 3 materials in each of the Ti-based boride/carbide/nitride families, we can perform a simple linear fit and use this as the basis for our Fröhlich model. The




Figure 1. For Ti_2AX (A: Al, Ge and In; X: B, C and N), the results for T_c computed using $\mu^* = 0.13$ using Migdal–Eliashberg theory are presented as red (X = B), blue (X = C) and magenta (X = N) squares, and the corresponding experimental data are displayed as black circles, with linear best fit to the theoretical values in red, blue and magenta dashed lines. Red, blue and magenta dashed lines represent a simple Fröhlich model for estimating superconducting transition temperature T_c . Full data in Tables 1 and 2.

Phase	T_c (Exp)	T_c (Fröhlich)	T_c (Full ME theory)
Ti_2AlB		7.8	7.8
Ti_2GeB		4.9	5.0
Ti_2InB		3.4	3.2
Ti_2AlC		11.2	10.8
Ti_2GeC	9.5 ³⁰	9.3	9.4
Ti_2InC	3.1 ²⁷	3.6	3.7
Ti_2AlN		12.9	13.0
Ti_2GeN		11.6	11.6
Ti_2InN	7.3 ²⁹	6.9	7.0

Table 1. Superconducting temperature values (T_c in K) of experimental, predicted through simple Fröhlich model and calculated by Migdal–Eliashberg (ME) theory for Ti_2AX (A: Al, Ge and In, X: B, C and N).

results are summarized in Table 1, and validate the usefulness of our screening method to predict T_c in novel materials.

We can now use this model in a high-throughput screening approach to quickly evaluate similar materials for which T_c is unknown. This only requires an electronic DOS calculation (~ 1 core hour/material) which is much quicker than calculating the full electron–phonon coupling (~ 300 core hours/material).

The full set of Fröhlich model results, for Ti_2AX (where A: Al, Si, P, S, Cu, Zn, Ga, Ge, As, Cd, In, Sn, Tl and Pb; X: B, C and N) are shown in Table 2. This shows that the compounds containing Al have the highest superconducting transition temperature for each family, and that Ti_2AlN is predicted to have the highest superconductivity temperature of *any* known M_2AX material. Similarly, Ti_2AlC is predicted to have the highest T_c of the carbides, and Ti_2AlB is predicted to have the highest T_c of the borides.

As a validation of Eq. (1), we calculated values for Θ_D using Quantum Espresso’s QHA package, and these are shown in Table 3 along with the values for T_c and $N(E_F)$. This allows the electron phonon interaction strength (V) to be inferred from Eq. (2). This shows that the borides/carbides/nitrides all follow the same universal form as shown in Fig. 2.

Having presented the T_c results, we now consider the detailed electronic and phonon properties that underly this behaviour.

Structural, electronic and Fermi surface properties. Ti_2AlX (X: B, C and N) crystallizes in the hexagonal structure with space group $P6_3/mmc$. The primitive unit cell has two formula units (eight atoms), each of which has occupied Wyckoff coordinates $4f$ ($1/3, 2/3, z$) for Ti, $2d$ ($1/3, 2/3, 3/4$) for Al, and $2a$ ($0, 0, 0$) for B (C and N) atoms. Thus, two lattice parameters, a and c , and one internal structural parameter, z , determine the structure. The hexagonal unit cell is shown in Fig. 3a in which blocks of edge-sharing Ti_6X octahedra are sandwiched between planes of Al. The hexagonal Brillouin zone is shown in Fig. 3b.

Phase	$N(E_F)$ (States/eV)	\sqrt{M} (amu ^{0.5})	T_c (K)
Ti ₂ AlB	2.241	16.3	7.8
Ti ₂ SiB	1.758	16.4	2.9
Ti ₂ PB	1.902	16.5	3.9
Ti ₂ SB	1.703	16.6	2.1
Ti ₂ CuB	2.354	18.4	6.4
Ti ₂ ZnB	2.446	18.5	7.1
Ti ₂ GaB	1.718	18.8	0.3
Ti ₂ GeB	2.227	18.9	4.9
Ti ₂ AsB	1.799	19.1	0.6
Ti ₂ CdB	2.631	20.9	6.1
Ti ₂ InB	2.324	21.0	3.4
Ti ₂ SnB	2.617	21.2	5.7
Ti ₂ TlB	2.066	24.9	0.0
Ti ₂ PbB	2.440	25.0	1.2
Ti ₂ AlC	3.048	16.4	11.2
Ti ₂ SiC	2.788	16.5	8.4
Ti ₂ PC	2.727	16.6	7.6
Ti ₂ SC	2.314	16.7	3.0
Ti ₂ CuC	3.335	18.5	10.5
Ti ₂ ZnC	3.328	18.6	10.1
Ti ₂ GaC	2.226	18.8	0.3
Ti ₂ GeC	3.319	19.0	9.3
Ti ₂ AsC	2.506	19.1	2.4
Ti ₂ CdC	3.599	21.0	9.1
Ti ₂ InC	2.938	21.1	3.6
Ti ₂ SnC	3.427	21.3	7.1
Ti ₂ TlC	2.730	25.0	0.0
Ti ₂ PbC	3.791	25.1	5.7
Ti ₂ AlN	4.568	16.5	12.9
Ti ₂ SiN	3.864	16.6	4.3
Ti ₂ PN	3.796	16.7	3.6
Ti ₂ SN	3.688	16.8	2.0
Ti ₂ CuN	4.890	18.6	10.3
Ti ₂ ZnN	4.841	18.7	9.7
Ti ₂ GaN	3.991	18.9	0.4
Ti ₂ GeN	5.144	19.1	11.6
Ti ₂ AsN	4.110	19.2	1.4
Ti ₂ CdN	5.321	21.1	8.4
Ti ₂ InN	5.182	21.2	6.9
Ti ₂ SnN	5.672	21.4	11.0
Ti ₂ TlN	5.084	25.1	0.0
Ti ₂ PbN	6.043	25.2	6.0

Table 2. Superconducting temperature values of all the different M₂AX phases screened by the high-throughput Fröhlich model.

The Murnaghan equation of state was used to compute the lattice constants (a, c), the optimum internal parameter (z) and the bulk modulus (B) for each compound. These are shown in Table 4 and are in excellent agreement with previous theoretical results^{33,34,36,37}.

Figure 4 shows the electronic properties of hexagonal Ti₂AIX including the band structure in the Brillouin zone, the total and partial density of states (DOS and PDOS), and the Fermi surface. The electronic density of states at the Fermi level ($N(E_F)$) is important for metallic phases and superconductivity calculations. The PDOS of each component, broken into site and angular momentum contributions, is shown in Fig. 4, and as bands (mostly Ti 3d states) cross the Fermi level, this is the origin of the metallic behaviour. The electrical band structure is similar to that observed in previous studies^{35,37}. Notably, each material has six valence bands that cross the Fermi level.

An analysis of the PDOS of Ti₂AlN reveals that the lowest energy region, $-16.8 < E < -15.6$ eV, is dominated by the N 2s states with minor contributions from Ti 4s and 3d states. In Ti₂AlC this low-energy region is

Phase	$N(E_F)V$	Θ_D (K)
Ti ₂ AlB	0.224	594.3
Ti ₂ GeB	0.207	555.6
Ti ₂ InB	0.199	429.3
Ti ₂ AlC	0.231	722.2
Ti ₂ GeC	0.236	572.9
Ti ₂ InC	0.196	527.7
Ti ₂ AlN	0.240	728.9
Ti ₂ GeN	0.248	576.9
Ti ₂ InN	0.229	484.8

Table 3. The effective electron–phonon coupling potential $N(E_F)V$ and calculated values for the Debye temperature, Θ_D , for the MAX phases studied.




Figure 2. Simple BCS theory analysis of the observed trends in T_c for Ti₂AX (A: Al, Ge, In, and X: B, C, or N).




Figure 3. (a) The hexagonal crystal structure of Ti₂AlX (X: B, C and N), where blocks of Ti–X (X: B, C and N) (formed by edge-shared Ti₆X (X: B, C and N) octahedra) are sandwiched with Al atomic sheets. (b) The hexagonal Brillouin zone for Ti₂AlX (X: B, C and N).

Source	<i>a</i> (Å)	<i>c</i> (Å)	<i>z</i>	B(GPa)
Ti₂AlB	3.153	14.359	0.086	110.7
GGA ³⁶	3.148	14.077		111.9
GGA ³⁷	3.148	14.064	0.087	134.0
Ti₂AlC	3.069	13.643	0.083	137.6
Theory ³³	3.071	13.726		138.0
Theory ³⁴	3.040	13.600		
Theory ³⁵	3.040	13.600	0.084	
GGA ³⁶	3.069	13.737		140.3
Ti₂AlN	2.995	13.722	0.085	155.7
Theory ³³	2.998	13.634		155.0
Theory ³⁴	2.989	13.614		
GGA ³⁶	2.996	13.643		160.2

Table 4. Structural properties of Ti₂AlX (X: B, C and N) for this work in bold, and their comparison with previous theoretical results.




Figure 4. The electronic band structure, the total and partial electronic local density of states and Fermi surface for the hexagonal phase of (a) Ti₂AlB, (b) Ti₂AlC and (c) Ti₂AlN.

dominated by the C 2s orbital and is about 5 eV higher than in Ti₂AlN. This low-energy region is absent in Ti₂AlB material.

The main valence band region, $-8.0 < E < -4.0$ eV, is made of hybridised Ti 3d and X 2p states, indicating covalent Ti-X bonding, with increasing covalent character in the order of $B > C > N$. Hence it is expected that Ti₂AlN should have higher electrical conductivity than Ti₂AlB and Ti₂AlC. The region $-4.0 < E < E_F$ eV is dominated by Ti 3d states with some weak Ti 3d and Al 3p hybridization. In the region $E > E_F$ the band structure is almost entirely dominated by Ti 3d states.

Qualitatively, it appears that the band structures around the Fermi level for Ti_2AlX ($X = \text{B}, \text{C}$ or N) are similar, with the principal difference being a shift of E_F by 0.5 eV from $X = \text{B}$ to $X = \text{C}$, and by 0.2 eV from $X = \text{C}$ to $X = \text{N}$. This shift results in a significant increase in $N(E_F)$. The electronic states at the Fermi level are crucial for superconductivity and we find that the DOS of Ti_2AlN at the Fermi level is $N(E_F) = 4.568$ states/eV, with about 89.3%, 5.9% and 4.8% contributions from Ti, Al, and N atoms, respectively. As a consequence, the conduction properties are dominated by the Ti 3d electrons. Similarly, $N(E_F) = 3.048$ states/eV for Ti_2AlC and 2.241 states/eV for Ti_2AlB . This suggests that the most important contribution to the formation of the superconducting properties of Ti_2AlX phases come from the Ti 3d states which increase $N(E_F)$ and enhance λ according to the McMillan–Hopfield expression⁵⁰:

$$\lambda = \frac{N(E_F)\langle I^2 \rangle}{M\langle \omega^2 \rangle}, \quad (3)$$

where $\langle \omega^2 \rangle$ denotes the average squared phonon frequency, $\langle I^2 \rangle$ describe the average squared electron–phonon matrix element and M is the average atomic mass. As Ti_2AlN has higher $N(E_F)$ than the other materials, it should result in a higher T_c value if all other effects are similar.

Figure 4 also shows the Fermi surface of Ti_2AlX ($X: \text{B}, \text{C}$ and N) which again illustrates the dominance of Ti 3d-like bands. The calculated Fermi surface of Ti_2AlC agrees well with the previous theoretical result³⁵. The Fermi surface of Ti_2AlB has four sheets, while the Fermi surface of the other two materials contains five sheets. The Fermi surface is completely prismatic and cylindrical in the Γ - A direction and exhibits electron-like behaviour, while hole-like sheets appear at the corners of the Brillouin zone along the H - K and L - M directions. The non-spherical Fermi sheets may also cause a high metallic conductivity⁵¹.

Phonons and electron–phonon interaction. Phonons have a crucial role in superconductivity, so the calculated phonon dispersion, total and partial vibrational density of states and electron–phonon spectral function for Ti_2AlX ($X: \text{B}, \text{C}$ and N) are shown in Fig. 5a–c, respectively. All 3 materials have 8 atoms per primitive unit cell, so there are 3 acoustic and 21 optical phonon modes. A detailed study of the zone centre optical phonon modes is given in our previous paper²¹. As there are no negative frequencies, each structure is dynamically stable. The phonon spectra splits into two distinct frequency regions: a low-frequency region up to 12 THz that contains three acoustic and fifteen optical phonon modes, and a high-frequency region from 15 to 21 THz that contains six optical modes. The E_{2g} branch of all three materials exhibits a phonon anomaly along the Γ - K direction.

There is weak overlap and hybridization of Ti–Al modes in the low-frequency region, and the modes in the high frequency region are dominated by the light X atoms. The DOS in this region has two peaks separated by a small gap for the atoms of Ti_2AlC and Ti_2AlN compounds but this gap vanishes for Ti_2AlB . Overall, the phonon properties of Ti_2AlX ($X: \text{B}, \text{C}$ and N) materials are very similar.

The electron–phonon interaction may be studied using the linear response theory^{39,40} approach to the Migdal–Eliashberg theory^{41,42}. The average electron–phonon coupling constant λ may be calculated from the Eliashberg spectral function ($\alpha^2F(\omega)$). A detailed study of the Eliashberg spectral function is given in our previous paper²¹. λ values of Ti_2AlX ($X: \text{B}, \text{C}$ and N) have been calculated as 0.685, 0.743 and 0.775, respectively. Figure 5 confirms that $\lambda(\omega)$ is dominated by the lowest frequency region, in which $\lambda \propto \omega$. The low frequency contribution to the total λ is 93%, 97% and 94%, respectively, and is dominated by the coupled motion of Ti and Al atoms. The high-frequency region makes a minor contribution to λ as this region is dominated by light X atom modes. Using the value of $\lambda(\omega)$, the logarithmic average phonon frequency (ω_{ln}) is calculated as 219.540 K, 342.218 K and 369.818 K for Ti_2AlX ($X: \text{B}, \text{C}$ and N), respectively. The values of λ and ω_{ln} are used to calculate the superconducting transition temperature T_c using the Allen–Dynes modification of the McMillan formula as discussed in our previous paper²¹. In most studies, the value of μ^* ranges from 0.10 to 0.16^{50,52}. Here, we use $\mu^* = 0.13$, as this gave the best fit to the experimental T_c for Ti_2GeC , Ti_2InC , and Ti_2InN (see Supplementary Information). There is currently no known experimental T_c for Ti_2AlX and so we use $\mu^* = 0.13$ and predict $T_c = 7.8, 10.8$, and 13.0 K for Ti_2AlX (B, C , and N).

Conclusion

We have used a high-throughput approach to study the superconducting properties of 42 different Ti-based $M_2\text{AX}$ phases where A: Al, Si, P, S, Cu, Zn, Ga, Ge, As, Cd, In, Sn, Tl and Pb; X: B, C and N; as shown in Fig. 1 and detailed in Table 2. Currently, 3 are known to be superconducting in experiment (black circles in Fig. 1). Our screening identified that A = Al has the best potential for a high T_c , and we then studied the properties of Ti_2AlX ($X: \text{B}, \text{C}$ and N) in more detail. The $M_2\text{AX}$ phase with the highest known experimental T_c is Nb_2GeC which has $T_c = 9.5$ K. Our study predicts that Ti_2AlC will have $T_c = 10.8$ K, the highest T_c for a carbide-based $M_2\text{AX}$ phase. Our high-throughput model also predicts the potential for even higher T_c in the nitride-based materials, and our detailed calculations predict Ti_2AlN to have $T_c = 13.0$ K. We also demonstrate superconductivity in the boride-based $M_2\text{AX}$ phases for the first time.

Our analysis shows that the electron–phonon coupling is dominated by low-frequency Ti-based phonon modes, and Ti 3d-based electronic states near the Fermi energy. This work should encourage further studies of superconductivity in $M_2\text{AX}$ phases, and the use of Al rather than the more usual Ge or In should have higher T_c and cost savings.

The high-throughput model developed here, with its detailed justification, should also have application in other systematic studies of superconductivity.




Figure 5. Phonon dispersion curves, total, partial vibrational density of states and the calculated electron-phonon spectral function $\alpha^2F(\omega)$ (red line) and the variation of the electron-phonon coupling parameter (λ) with rising frequency $\lambda(\omega)$ of (a) Ti_2AlB , (b) Ti_2AlC and (c) Ti_2AlN .

Data availability

The data created and analysed during the current study are available from the corresponding author on reasonable request.

Received: 9 June 2022; Accepted: 27 July 2022

Published online: 01 August 2022

References

- Hadi, M. Superconducting phases in a remarkable class of metallic ceramics. *J. Phys. Chem. Solids* **138**, 109275 (2020).
- Barsoum, M. W. The $\text{M}_{N+1}\text{AX}_N$ phases: A new class of solids: Thermodynamically stable nanolaminates. *Prog. Solid State Chem.* **28**, 201 (2000).
- Barsoum, M., Golczewski, J., Seifert, H. & Aldinger, F. Fabrication and electrical and thermal properties of Ti_2InC , Hf_2InC and $(\text{Ti}, \text{Hf})_2\text{InC}$. *J. Alloy. Compd.* **340**, 173 (2002).
- Hettinger, J. *et al.* Electrical transport, thermal transport, and elastic properties of M_2AlC ($\text{M} = \text{Ti}, \text{Cr}, \text{Nb}$, and V). *Phys. Rev. B* **72**, 115120 (2005).
- Manoun, B. *et al.* Compression behavior of M_2AlC ($\text{M} = \text{Ti}, \text{V}, \text{Cr}, \text{Nb}$, and Ta) phases to above 50 GPa. *Phys. Rev. B* **73**, 024110 (2006).
- Eklund, P. *et al.* Discovery of the ternary nanolaminated compound Nb_2GeC by a systematic theoretical-experimental approach. *Phys. Rev. Lett.* **109**, 035502 (2012).
- Kumar, R. S., Rekihi, S., Cornelius, A. & Barsoum, M. W. Compressibility of Nb_2AsC to 41 GPa. *Appl. Phys. Lett.* **86**, 111904 (2005).

8. Schneider, J. M. *et al.* Elastic properties of Cr₂AlC thin films probed by nanoindentation and ab initio molecular dynamics. *Scr. Mater.* **57**, 1137 (2007).
9. Emmerlich, J., Music, D., Houben, A., Dronskowski, R. & Schneider, J. Systematic study on the pressure dependence of M₂AlC phases (M = Ti, V, Cr, Zr, Nb, Mo, Hf, Ta, W). *Phys. Rev. B* **76**, 224111 (2007).
10. Wang, Q. *et al.* Fabrication and oxidation behavior of Cr₂AlC coating on Ti6242 alloy. *Surf. Coat. Technol.* **204**, 2343 (2010).
11. Hu, C. *et al.* On the rapid synthesis of the ternary Mo₂GaC. *J. Am. Ceram. Soc.* **98**, 2713 (2015).
12. Bortolozzo, A. D., Cremasco, A., Floriano, R. & Contieri, R. J. Effects of microwave heating in nanolaminated Nb₂GeC synthesis. *Ceram. Int.* **42**, 16343 (2016).
13. Rackl, T., Eisenburger, L., Niklaus, R. & Johrendt, D. Syntheses and physical properties of the max phase boride Nb₂Sb and the solid solutions nb₂Sb_xC_{1-x} (x = 0–1). *Phys. Rev. Mater.* **3**, 054001 (2019).
14. Rackl, T. & Johrendt, D. The max phase borides Zr₂Sb and Hf₂Sb. *Solid State Sci.* **106**, 106316 (2020).
15. Qin, Y. *et al.* Synthesis and characterization of ternary layered Nb₂Sb ceramics fabricated by spark plasma sintering. *J. Alloy. Compd.* **878**, 160344 (2021).
16. Zhang, Q. *et al.* Synthesis and property characterization of ternary laminar Zr₂Sb ceramic. *J. Adv. Ceram.* **11**, 825 (2022).
17. Kurakevych, O. Superhard phases of simple substances and binary compounds of the bcno system: From diamond to the latest results (a review). *J. Superhard Mater.* **31**, 139 (2009).
18. Ali, M. *et al.* Physical properties of new MAX phase borides M₂SB (M = Zr, Hf and Nb) in comparison with conventional MAX phase carbides M₂SC (M = Zr, Hf and Nb): Comprehensive insights. *J. Market. Res.* **11**, 1000 (2021).
19. Hadi, M. *et al.* A density functional theory approach to the effects of C and N substitution at the B-site of the first boride MAX phase Nb₂Sb. *Mater. Today Commun.* **29**, 102910 (2021).
20. Bortolozzo, A. D., Osorio, W. R., de Lima, B. S., Dos Santos, C. A. M. & Machado, A. J. S. Superconducting evidence of a processed Nb₂GeC compound under a microwave heating. *Mater. Chem. Phys.* **194**, 219 (2017).
21. Karaca, E., Byrne, P. J. P., Hasnip, P. J., Tütüncü, H. & Probert, M. Electron–phonon interaction and superconductivity in hexagonal ternary carbides Nb₂AC (A: Al, S, Ge, As and Sn). *Electron. Struct.* **3**, 045001 (2021).
22. Jeitschko, W., Nowotny, H. & Benesovsky, F. Ti₂AlN, eine stickstoffhaltige H-phase. *Monatshefte für Chem. verwandte Teile anderer Wissenschaft.* **94**, 1198 (1963).
23. Toth, L. High superconducting transition temperatures in the molybdenum carbide family of compounds. *J. Less Common Metals* **13**, 129 (1967).
24. Sakamaki, K., Wada, H., Nozaki, H., Ōnuki, Y. & Kawai, M. Carbosulfide superconductor. *Solid State Commun.* **112**, 323 (1999).
25. Lofland, S. *et al.* Electron–phonon coupling in M_{n+1}AX_n-phase carbides. *Phys. Rev. B* **74**, 174501 (2006).
26. Bortolozzo, A. *et al.* Superconductivity in the Nb₂SnC compound. *Solid State Commun.* **139**, 57 (2006).
27. Bortolozzo, A., Sant-Anna, O., Dos Santos, C. & Machado, A. Superconductivity in the hexagonal-layered nanolaminates Ti₂InC compound. *Solid State Commun.* **144**, 419 (2007).
28. Bortolozzo, A., Fisk, Z., Sant-Anna, O., Dos Santos, C. & Machado, A. Superconductivity in Nb₂InC. *Physica C* **469**, 256 (2009).
29. Bortolozzo, A. *et al.* Superconductivity at 7.3 K in Ti₂InN. *Solid State Commun.* **150**, 1364 (2010).
30. Bortolozzo, A., Sant-Anna, O., Dos Santos, C. & Machado, A. Superconductivity at 9.5 K in the Ti₂GeC compound. *Mater. Sci. Poland* **30**, 92 (2012).
31. Kuchida, S. *et al.* Superconductivity in Lu₂SnC. *Physica C* **494**, 77 (2013).
32. Li, J. *et al.* Appearance of superconductivity at 15.9 K in layered V₂AlN. *J. Supercond. Novel Magn.* **30**, 1 (2017).
33. Cover, M. F., Warschkow, O., Bilek, M. M. & McKenzie, D. R. Elastic properties of Ti_{n+1}AlC_n and Ti_{n+1}AlN_n MAX phases. *Adv. Eng. Mater.* **10**, 935 (2008).
34. Barsoum, M. W. & Radovic, M. Elastic and mechanical properties of the MAX phases. *Annu. Rev. Mater. Res.* **41**, 195 (2011).
35. Mauchamp, V. *et al.* Anisotropy of the resistivity and charge-carrier sign in nanolaminated Ti₂AlC: Experiment and ab initio calculations. *Phys. Rev. B* **87**, 235105 (2013).
36. Khazaei, M., Arai, M., Sasaki, T., Estili, M. & Sakka, Y. Trends in electronic structures and structural properties of MAX phases: A first-principles study on M₂AlC (M = Sc, Ti, Cr, Zr, Nb, Mo, Hf, or Ta), M₂AlN, and hypothetical M₂AlB phases. *J. Phys. Condens. Matter* **26**, 505503 (2014).
37. Surucu, G. Investigation of structural, electronic, anisotropic elastic, and lattice dynamical properties of MAX phases borides: An ab-initio study on hypothetical M₂AB (M = Ti, Zr, Hf; A = Al, Ga, In) compounds. *Mater. Chem. Phys.* **203**, 106 (2018).
38. Lepakova, O., Karakchieva, N., Golobokov, N., Galchenko, N. & Afanasev, N. High-temperature synthesis of Ti–Si–B and Ti–Al–B composites and coatings. *Int. J. Self Propag. High Temp. Synth.* **29**, 150 (2020).
39. Giannozzi, P. *et al.* Quantum Espresso: A modular and open-source software project for quantum simulations of materials. *J. Phys. Condens. Matter* **21**, 395502 (2009).
40. Giannozzi, P. *et al.* Advanced capabilities for materials modelling with Quantum Espresso. *J. Phys. Condens. Matter* **29**, 465901 (2017).
41. Migdal, A. Interaction between electrons and lattice vibrations in a normal metal. *Sov. Phys. JETP* **7**, 996 (1958).
42. Eliashberg, G. Interactions between electrons and lattice vibrations in a superconductor. *Sov. Phys. JETP* **11**, 696 (1960).
43. Baroni, S., Giannozzi, P. & Isaev, E. Density-functional perturbation theory for quasi-harmonic calculations. *Rev. Mineral. Geochem.* **71**, 39 (2010).
44. Perdew, J. P., Burke, K. & Ernzerhof, M. Generalized gradient approximation made simple. *Phys. Rev. Lett.* **77**, 3865 (1996).
45. Rappe, A. M., Rabe, K. M., Kaxiras, E. & Joannopoulos, J. Optimized pseudopotentials. *Phys. Rev. B* **41**, 1227 (1990).
46. Monkhorst, H. J. & Pack, J. D. Special points for Brillouin-zone integrations. *Phys. Rev. B* **13**, 5188 (1976).
47. Fröhlich, H. Theory of the superconducting state. I. The ground state at the absolute zero of temperature. *Phys. Rev.* **79**, 845 (1950).
48. Bardeen, J., Cooper, L. & Schrieffer, J. Theory of superconductivity. *Phys. Rev.* **108**, 1175 (1957).
49. Wang, J. *et al.* Discovery of hexagonal ternary phase Ti₂InB₂ and its evolution to layered boride TiB. *Nat. Commun.* **10**, 2284 (2019).
50. Allen, P. B. & Dynes, R. Transition temperature of strong-coupled superconductors reanalyzed. *Phys. Rev. B* **12**, 905 (1975).
51. Hadi, M. *et al.* Insights into the physical properties of a new 211 MAX phase Nb₂CuC. *J. Phys. Chem. Solids* **149**, 109759 (2021).
52. Allen, P. & Dynes, R. Superconductivity at very strong coupling. *J. Phys. C Solid State Phys.* **8**, L158 (1975).

Acknowledgements

This work was supported by the Scientific and Technical Research Council of Turkey (TÜBİTAK) (2219 International Post Doctoral Research Fellowship Programme Project Number 1059B191900055). P.J.H. was funded by an EPSRC RSE Fellowship (EPSRC Grant EP/R025770/1). P.J.B. was funded by the UKCP High End Compute Consortium (EPSRC Grant EP/P022561/1). This project was undertaken on the Viking Cluster, which is a high performance compute facility provided by the University of York. We are grateful for computational support from the University of York HPC service.

Author contributions

All authors co-wrote the paper. E.K. performed the DFT calculations, P.J.P.B. and P.J.H. gave theoretical and computational insights and guidance, M.I.J.P. conceived and designed the study.

Competing interests

The authors declare no competing interests.

Additional information

Supplementary Information The online version contains supplementary material available at <https://doi.org/10.1038/s41598-022-17539-8>.

Correspondence and requests for materials should be addressed to M.I.J.P.

Reprints and permissions information is available at www.nature.com/reprints.

Publisher's note Springer Nature remains neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Open Access This article is licensed under a Creative Commons Attribution 4.0 International License, which permits use, sharing, adaptation, distribution and reproduction in any medium or format, as long as you give appropriate credit to the original author(s) and the source, provide a link to the Creative Commons licence, and indicate if changes were made. The images or other third party material in this article are included in the article's Creative Commons licence, unless indicated otherwise in a credit line to the material. If material is not included in the article's Creative Commons licence and your intended use is not permitted by statutory regulation or exceeds the permitted use, you will need to obtain permission directly from the copyright holder. To view a copy of this licence, visit <http://creativecommons.org/licenses/by/4.0/>.

© The Author(s) 2022